

OFFICE OF NAVAL RESEARCH

CONTRACT N00014-89-J-1828

R&T Code 3132080

Abstract Report #6

FROM LIQUID CRYSTAL POLYMERS CONTAINING CROWN ETHERS TO
TAPERED BUILDING BLOCKS CONTAINING CROWN ETHERS WHICH
SELF-ASSEMBLE INTO TUBULAR SUPERMOLECULES

by

V. Percec and G. Johansson


Submitted

to

Macromolecular Symposia

in press

Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	



Department of Macromolecular Science
Case Western Reserve University
Cleveland, OH 44106-7202

May 9, 1995

19950516 053

Reproduction in whole or in part is permitted for any purpose of the United States Government

This document has been approved for public release and sale;
its distribution is unlimited.

DTIC QUALITY INSPECTED 5

REPORT DOCUMENTATION PAGE

FORM 100-100-100-100

OMB No 0704-0166

This report is to be filled out by the person who is responsible for the collection of information. It is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302 and to the Office of Management and Budget, Paperwork Reduction Project (0704-0166), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 5-9-95	3. REPORT TYPE AND DATES COVERED Abstract Report # 6	
4. TITLE AND SUBTITLE From Liquid Crystal Polymers Containing Crown Ethers to Tapered Building Blocks Containing Crown Ethers which Self-Assemble into Tubular...			5. FUNDING NUMBERS N00014-89-J-1828	
6. AUTHOR(S) V. Percec and G. Johansson				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Macromolecular Science Case Western Reserve University Cleveland, OH 44106-7202			8. PERFORMING ORGANIZATION REPORT NUMBER N00014-89-J-1828	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Department of Navy Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5000			10. SPONSORING/MONITORING AGENCY REPORT NUMBER Abstract Report #6	
11. SUPPLEMENTARY NOTES Macromolecular Symposia, in press.				
12a. DISTRIBUTION / AVAILABILITY STATEMENT			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Molecular recognition directed self-assembly of supramolecular architectures or noncovalent synthesis, and molecular recognition directed self-assembly of transition states or self-synthesis, are two of the most active topics of research in the area of supramolecular chemistry. We are concerned with the use of the simplest endo-receptor i.e., crown ether in the design of two classes of systems. The first one is a system which is externally regulated by molecular recognition processes via a crown ether endo-receptor. This system is based on various classes of liquid-crystalline polymers which exhibit phase transitions that are manipulated by the reversible complexation of the crown ether present in different parts of their repeat unit with metal salts. The information gained from these experiments is then exploited in the design of the second group of systems. This consists of self-assembling building blocks containing various combinations of crown ether as endo-receptor and a tapered group as exo-receptor. Upon complexation with metal salts, these building blocks self-assemble into tubular supramolecular architectures. Therefore, while the first system exhibits molecular recognition directed phase transitions, the second one self-assembles into tubular supramolecular architectures via various molecular recognition processes. These tubular supramolecular architectures display a thermotropic hexagonal columnar (Φ_h) liquid crystalline phase, which enables the structure of the self-assembled supramolecular architecture to be determined by X-ray diffraction experiments. Since the formation of a liquid-crystalline phase is a thermodynamically controlled process, its characterization eliminates many of the difficulties encountered in the characterization of self-assembled crystalline structures which are obtained by a kinetically controlled process. The goal of this paper is to discuss selected examples from these two groups of systems elaborated in our laboratory.				
14. SUBJECT TERMS			15. NUMBER OF PAGES	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT unclassified	20. LIMITATION OF ABSTRACT UL	

FROM LIQUID CRYSTAL POLYMERS CONTAINING CROWN ETHERS TO TAPERED BUILDING BLOCKS CONTAINING CROWN ETHERS WHICH SELF-ASSEMBLE INTO TUBULAR SUPERMOLECULES

V. Percec* and G. Johansson

The W. M. Keck Laboratories for Organic Synthesis, Department of
Macromolecular Science, Case Western Reserve University, Cleveland, OH 44106

INTRODUCTION

Molecular recognition directed self-assembly of supramolecular architectures or noncovalent synthesis (1), and molecular recognition directed self-assembly of transition states or self-synthesis (2), are two of the most active topics of research in the area of supramolecular chemistry (3). We are concerned with the use of the simplest endo-receptor i.e., crown ether in the design of two classes of systems. The first one is a system which is externally regulated by molecular recognition processes via a crown ether endo-receptor. This system is based on various classes of liquid-crystalline polymers which exhibit phase transitions that are manipulated by the reversible complexation of the crown ether present in different parts of their repeat unit with metal salts. The information gained from these experiments is then exploited in the design of the second group of systems. This consists of self-assembling building blocks containing various combinations of crown ether as endo-receptor and a tapered group as exo-receptor. Upon complexation with metal salts, these building blocks self-assemble into tubular supramolecular architectures. Therefore, while the first system exhibits molecular recognition directed phase transitions, the second one self-assembles into tubular supramolecular architectures via various molecular recognition processes. These tubular supramolecular architectures display a thermotropic hexagonal columnar (Φ_h) liquid crystalline phase, which enables the structure of the self-assembled supramolecular architecture to be determined by X-ray diffraction experiments. Since the formation of a liquid-crystalline phase is a thermodynamically controlled process, its characterization eliminates many of the difficulties encountered in the characterization of self-assembled crystalline structures which are obtained by a kinetically controlled process. The goal of this paper is to discuss selected examples from these two groups of systems elaborated in our laboratory.

LIQUID CRYSTALLINE POLYMERS CONTAINING CROWN ETHERS: SYNTHESIS AND MANIPULATION OF PHASE TRANSITIONS BY COMPLEXATION


Scheme 1 outlines the two major classes of liquid-crystalline polymers, i.e., main-chain and side-chain, and their architecture which is determined by the place of the repeat unit in which the crown ether endo-receptor is inserted. We have designed main-chain liquid-crystalline polymers containing crown ethers in their flexible spacer (4), and side-chain liquid-crystalline polymers containing crown ethers either in their backbone (5) or in their mesogenic side groups (6,7).

I. Main-Chain Liquid-Crystalline Polymers




II. Side-Chain Liquid-Crystalline Polymers

A. Crown ether ligand as part of the mesogenic unit




B. Crown ether ligand as part of the polymer backbone



Scheme 1. Various architectures of main-chain and side-chain liquid-crystalline polymers containing crown ethers


Scheme 2 outlines the synthetic procedure used in the preparation of the two monomers: 4-{2-[4'-(11-vinyloxyundecyloxy)biphenyl-4-yl]ethyl}benzo-15-crown-5 (**VE-BPE**) and 4-{2-[4'-(11-methacroyloxyundecyloxy)biphenyl-4-yl]ethyl}benzo-15-crown-5 (**MA-BPE**) (7b). The synthetic details of this reaction scheme are available in the original publication (7b). **VE-BPE** was polymerized by a cationic mechanism employing an initiating system based on $\text{CF}_3\text{SO}_3\text{H}/(\text{CH}_3)_2\text{S}$ in methylene dichloride at 0°C . Under these conditions a "living" polymerization is achieved for this functional monomer. The selection of this cationic initiator was based on the use of the soft nucleophile/base, $(\text{CH}_3)_2\text{S}$, which reacts selectively with the growing carbenium species in a reversible way and therefore, avoids the reaction between the propagating carbenium ions and other nucleophilic functional groups of the monomer which exhibit a harder nucleophilic/basic character. Details of this polymerization and additional demonstrations of the ability of this initiator to generate living cationic polymerizations for a large variety of functional mesogenic vinyl ethers were reviewed elsewhere (8).



Scheme 2. Synthesis of **VE-BPE** and **MA-BPE**.

Figure 1a illustrates the cationic polymerization of **VE-BPE** and the structure of the resulted polymer (**PVE-BPE**). **PVE-BPE** with DP = 19 exhibits a crystalline melting followed by an enantiotropic smectic A (S_A) mesophase. Figure 1b presents the influence of complexation of **PVE-BPE** (DP = 19) with NaSO_3CF_3 on the phase behavior of the resulting complex. With the increase of the amount of NaSO_3CF_3 complexed by the 15-crown-5 moiety of this polymer, both the glass transition and the S_A -isotropic transition temperatures increase. At the same time the crystalline melting decreases. At higher concentrations of salt, a second smectic mesophase is uncovered.

(a)



(b)





Figure 1: (a) Cationic polymerization of **VE-BPE** and the complexes of **PVE-BPE** with NaSO_3CF_3 . (b) The dependence of various transition temperatures of the complexes of **PVE-BPE** ($\text{DP}=19$) with NaSO_3CF_3 on the mole ratio $\text{NaSO}_3\text{CF}_3/\text{PVE-BPE}$ (i=isotropic; S and S_A =smectic and smectic A; k=crystalline).

The S - S_A transition temperature decreases with the increase of the amount of complexed salt. Figure 2a outlines the radical polymerization of **MA-BPE**. The resulting polymer **PMA-BPE** also exhibits a crystalline and a S_A phase. The effect of complexation of **PMA-BPE** with NaSO_3CF_3 on its phase transitions is presented in Figure 2b. The trend obtained from this figure is quite similar to that observed from Figure 1a.

(a)



(b)




Figure 2: (a) Radical polymerization of MA-BPE and the complexes of PMA-BPE with NaSO₃CF₃. (b) The dependence of various transition temperatures of the complexes of PMA-BPE with NaSO₃CF₃ on the mole ratio, NaSO₃CF₃ / PMA-BPE (i=isotropic, S and S_A=smectic and smectic A, k=crystalline).

The general message provided by these experiments is that complexation of the crown ether moiety of a side-chain liquid-crystalline polymer with metal salts enhances the stability of the lowest-order liquid-crystalline phase and decreases both the tendency towards crystallization as well as the tendency towards formation of higher-ordered liquid-crystalline phases. As a consequence, this molecular recognition effect can be expected to transform a crystalline polymer into a polymer displaying a monotropic or even an enantiotropic liquid-crystalline phase. For example, Figure 3a presents the heating and cooling differential scanning




Figure 3: (a) DSC analysis of PVE-BPE (DP=6) and of its complex, NaSO₃CF₃/PVE-BPE (1.0/1.0, mol/mol); CE is crown ether. (b) The dependence of various transition temperatures of the complexes of PMA-PA with NaSO₃CF₃ on the ratio NaSO₃CF₃/PMA-PA (mol/mol). All data were obtained with 20°C min⁻¹. Data from the second heating scan are: ○ - T_g; Δ - T_{k-i}; □ - T_{k-i}; ▲ - T_{i-k}; ■ - T_{i-φh}.

calorimetric (DSC) traces of **PVE-BPE** with DP = 6 which exhibits only a monotropic S_A phase. Upon complexation with 1.0 moles of NaSO_3CF_3 , this polymer exhibits an enantiotropic S_A and an additional unidentified (S) smectic mesophase (7b). This experiment demonstrates the transformation of a monotropic S_A phase into an enantiotropic one and of a virtual smectic phase (S) into a monotropic one. Figure 3b demonstrates the transformation of the crystalline polymer, poly[4-(2-{4-[11-(methacryloyloxy)undecyloxy]-phenyl}ethynyl)benzo-15-crown-5] (**PMA-PA**) (6a), into a polymer which exhibits an enantiotropic S_A phase (7a). This experiment demonstrates that complexation can transform a virtual mesophase into an enantiotropic one.

The ability to manipulate and to stabilize liquid-crystalline mesophases by complexation is strongly dependent on the size of the crown ether, of the cation, and on the nature of the counteranion.

MOLECULAR-RECOGNITION-DIRECTED SELF ASSEMBLY OF TAPERED GROUPS CONTAINING CROWN ETHERS INTO TUBULAR SUPRAMOLECULAR ARCHITECTURES

Scheme 3 outlines the synthesis of a series of self-assembling building blocks containing 15-crown-5 based endo-receptors and 3,4,5-tris(p-alkoxybenzyloxy)benzoate (i.e., **12-ABG-B15C5**, **4-ABG-15C5**, **6-ABG-15C5** and **12-ABG-15C5**) or 3,4,5-tris(dodecyloxy)benzoate (**12-AG-15C5**)-tapered side groups as exo-receptors (9). All of these building blocks form lamellar crystalline phases. However, upon complexation with alkali metal salts those with twelve carbons in their alkyl tails self-assemble into tubular supramolecular architectures which generate a hexagonal columnar (Φ_h) thermotropic mesophase. Figure 4a presents a representative example of a series of DSC traces for the complexes of **12-ABG-B15C5** with KSO_3CF_3 . The amount of salt in the complex is indicated on the figure. It is sufficient to add 0.1 moles of KSO_3CF_3 per crown ether to suppress the crystallization ability of **12-ABG-B15C5** and generate a supramolecular disordered structure which displays a glass transition temperature (T_g). The presence of a T_g indicates the creation of a polymer-like cooperative motion upon complexation. Addition of 0.2 moles of KSO_3CF_3 per crown ether produces a supramolecular tubular architecture. This amount of salt is sufficient to overcome the entropy loss required for the self assembly of **12-ABG-B15C5** into the tubular structure. Larger amounts of salt continue to stabilize the supramolecular tubular structure which is responsible for the formation of the Φ_h liquid-crystalline phase. Figure 4b plots the isotropic-hexagonal columnar ($T_{i-\Phi_h}$) transition temperature as a function of the amount of salt in the complex for a series of four self-assembling building blocks. The values of $T_{i-\Phi_h}$ for $\text{MSO}_3\text{CF}_3/\text{crown ether}$ (mol/mol) ratios larger than 1.0 are less reliable (9) since in some cases the resulting structures start to decompose. These data demonstrate that the wider **12-ABG**-tapered groups produce a more stable tubular structure than the **12-AG** groups.

12-ABG-B15C5





Figure 4: (a) Second DSC heating scans ($20^\circ\text{C min}^{-1}$) of 12-ABG-B15C5 and of its complexes with KSO_3CF_3 in the ratio, $\text{KSO}_3\text{CF}_3/12\text{-ABG-B15C5}$ (K/crown ether (CE), mol/mol). (b) The dependence of the isotropic-hexagonal columnar (T_i - Φ_h) transition temperatures of the complexes of various building blocks with NaSO_3CF_3 or KSO_3CF_3 on the ratio, $\text{MSO}_3\text{CF}_3/\text{crown-ether}$ (mol/mol): $\square$, 12-ABG-B15C5 $\cdot\text{NaSO}_3\text{CF}_3$; $\blacksquare$, 12-ABG-B15C5 $\cdot\text{KSO}_3\text{CF}_3$; $\bullet$, 12-ABG-15C5 $\cdot\text{NaSO}_3\text{CF}_3$; $\circ$, 12-AG-15C5- NaSO_3CF_3 .




Figure 5: Schematic representation of the self-assembly of tapered building blocks containing crown ethers into the tubular supramolecular architecture which is responsible for the generation of the hexagonal columnar (Φ_h) liquid-crystalline supramolecular assembly. The dimension, D , represents the diameter of the supramolecular column (middle) and is equal to the lattice parameter, a (right).

The shape and size of the brick determines the shape of the construction and also its stability, while the primary role of the cement is to enhance its stability. Co-assembly of these building blocks with other similar structures is controlled both by the nature of their endo- and exo-receptors (10). These self-assembling building blocks demonstrate a very simple system which contains all of the information required for the self-assembly in its components. At the same time the co-assembly of these tapered units demonstrates the concept of self-checking (10). Finally we would like to mention that these self-assembled tubular supramolecular architectures exhibit ionic conductivity which is strongly dependent on the shape of the supramolecular architecture and therefore, can be switched on or off by a phase transition which changes the supramolecular structure from tubular to lamellar or to a disordered isotropic structure (11). Additional examples of self-assembling building blocks from our (12) and from other (13) laboratories were reviewed elsewhere.

ACKNOWLEDGMENTS

Financial support by the National Science Foundation (DMR-92-06781) and the Office of Naval Research is gratefully acknowledged.

REFERENCES

- (1) For some brief reviews, see for example: (a) J. M. Lehn, *Makromol. Chem., Macromol. Symp.*, **69**, 1 (1993); (b) J. S. Lindsey, *New J. Chem.*, **15**, 153 (1991); (c) G. M. Whitesides, J. P. Mathias and C. T. Seto, *Science*, **254**, 1312 (1991); (d) G. M. Whitesides, E. M. Simanek, J. P. Mathias, C. T. Seto, D. N. Chin, M. Mammen and D. M. Gorman, *Acc. Chem. Res.*, **28**, 37 (1995).
- (2) For a few reviews, see: (a) D. Philp and J. F. Stoddart, *Synlett*, **445** (1991); (b) E. A. Wintner, M. M. Conn and J. Rebek, Jr., *Acc. Chem. Res.*, **27**, 198 (1994).
- (3) (a) J. M. Lehn, *Angew. Chem., Int. Ed. Engl.*, **27**, 89 (1988); (b) J. M. Lehn, *Angew. Chem., Int. Ed. Engl.*, **29**, 1304 (1990).
- (4) V. Percec and R. Rodenhouse, *Macromolecules*, **22**, 2043 (1989).
- (5) (a) R. Rodenhouse, V. Percec and A. E. Feiring, *J. Polym. Sci.: Part C: Polym. Lett.*, **28**, 345 (1990); (b) V. Percec and R. Rodenhouse, *Adv. Mater.*, **3**, 101 (1991).
- (6) (a) V. Percec and R. Rodenhouse, *Macromolecules*, **22**, 4408 (1989); (b) V. Percec and R. Rodenhouse, *J. Polym. Sci.: Part A: Polym. Chem. Ed.*, **29**, 15 (1991); (c) G. Ungar, V. Percec and R. Rodenhouse, *Macromolecules*, **24**, 1996 (1991); (d) R. Rodenhouse and V. Percec, *Makromol. Chem.*, **192**, 1873 (1991); (e) R. Rodenhouse and V. Percec, *Polym. Bull.*, **25**, 47 (1991).
- (7) (a) V. Percec, G. Johansson and R. Rodenhouse, *Macromolecules*, **25**, 2563 (1992); (b) V. Percec and G. Johansson, *J. Mater. Chem.*, **3**, 83 (1993).
- (8) V. Percec and D. Tomazos, *Adv. Mater.*, **4**, 548 (1992).

- (9) (a) V. Percec, G. Johansson, J. Heck, G. Ungar and S. V. Batty, *J. Chem. Soc. Perkin Trans. 1*, 1411 (1993); (b) G. Johansson, V. Percec, G. Ungar and D. Abramic, *J. Chem. Soc. Perkin Trans. 1*, 447 (1994).
- (10) D. Tomazos, G. Out, J. A. Heck, G. Johansson, V. Percec and M. Möller, *Liq. Cryst.*, **16**, 509 (1994).
- (11) G. Ungar, S. V. Batty, V. Percec, J. Heck and G. Johansson, *Adv. Mater. Opt. Electr.*, **4**, 303 (1994).
- (12) (a) V. Percec, J. Heck, G. Johansson, D. Tomazos and G. Ungar, *Macromol. Symp.*, **77**, 237 (1994); (b) V. Percec, J. Heck, G. Johansson, D. Tomazos, M. Kawasumi and G. Ungar, *J. Macromol. Sci. Pure Appl. Chem.*, **A31**, 1031 (1994); (c) V. Percec, J. Heck, G. Johansson, D. Tomazos, M. Kawasumi, P. Chu and G. Ungar, *J. Macromol. Sci. Pure Appl. Chem.*, **A31**, 1719 (1994); (d) V. Percec, J. Heck, G. Johansson, D. Tomazos, M. Kawasumi, P. Chu and G. Ungar, *Mol. Cryst. Liq. Cryst.*, **254**, 137 (1994).
- (13) V. Percec and G. Johansson, "Molecular, Macromolecular and Supramolecular Liquid Crystals Containing Macroheterocyclic Ligands", in *Macromolecular Design of Polymeric Materials*, K. Hatada, T. Katayama and O. Vogl, Eds., M. Dekker, N. Y., in press.