428	UNCLASSIFIED	
X- / X.		
	+ (CORRECT	
	STATES OF HER	
	UNCLASSIFIED	
	A	

DOW-24

Subject Category: CHEMISTRY

UNITED STATES ATOMIC ENERGY COMMISSION

THE RECOVERY OF URANIUM FROM COMMERCIAL 30% PHOSPHORIC ACID WITH ANTIMONY

Summary Status Report

By R. H. Bailes

DIIC QUALITY DESERVITED 2

February 23, 1950

Great Western Division Dow Chemical Company Pittsburg, California

Technical Information Extension, Oak Ridge, Tennessee



19970221 154

Date Declassified: December 28, 1955.

This report was prepared as a scientific account of Government-sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission makes any warranty or representation, express or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights. The Commission assumes no liability with respect to the use of, or from damages resulting from the use of, any information, apparatus, method, or process disclosed in this report.

This report has been reproduced directly from the best available copy.

Issuance of this document does not constitute authority for declassification of classified material of the same or similar content and title by the same authors.

Printed in USA, Price 20 cents. Available from the Office of Technical Services, Department of Commerce, Washington 25, D. C.

GPC 823215 - 1

DOW-24

SUMMARY STATUS REPORT

THE RECOVERY OF URANIUM FROM COMMERCIAL

30% PHOSPHORIC ACID WITH ANTIMONY

by

.R. H. Bailes

February 23, 1950

Great Western Division THE DOW CHEMICAL COMPANY Pittsburg, California

Contract No. AT-30-1-GEN-236

TABLE OF CONTENTS

1

		Page
Α.	SUMMARY	1
Β.	INTRODUCTION	2
C.	PROCESS FLOW	4
D.	DISCUSSION	7
Ε.	APPENDIX	8
F.	ACKNOWLEDGEMENT	14

A. <u>SUMMARY</u>

A preliminary estimate of the cost of recovering one pound of U₃O₈, in the form of a solid assaying 12% U₃O₈, from commercial 30% H₃PO4 by means of Sb₂O₃ is \$13.28. A plant costing \$496,000 would be required in order to process 500 tons of 30% H₃PO4 per day. As an alternative procedure, 3.2% of the 30% H₃PO4 output can be diverted to NH4H₂PO4 manufacture. One pound of U₃O8 in the same concentration plus 126 pounds of fertilizer-grade NH4H₂PO4 could then be produced for an estimated \$14.31 from a plant costing \$513,000. If a credit of \$0.05 per pound of NH4H₂PO4 produced can be accepted, the cost of U₃O₈ by this process would be reduced to about \$8.00 per pound. Ninety percent of the uranium in the phosphoric acid is recovered in either process.

Both of these estimated production costs are based on a plant producing 500 tons of 30% H₃PO4 per day with a U₃O8 assay of 0.00818 percent. Both include the sulfuric acid required to manufacture the phosphoric acid removed from the plant stream, but do not include costs of stepping up phosphoric acid production. In the first case production must be increased by 2.8 percent; in the second, by 3.2 percent.

In both processes the phosphoric acid is reduced with iron and is then agitated for a time with a small amount of antimony trioxide. The resulting solid is filtered off and is treated with dilute ammonia. When the ammonia is filtered, the filtrate contains 87% of the uranium originally in the phosphoric acid, and the residual solid consists of antimony trioxide, which is recycled. The phosphoric acid is returned to the plant.

Ammonia is stripped from the ammonia filtrate in a special plate column in the first process, and the resulting liquor is filtered, yielding the 12% U₃08 product. The filtrate is treated with lime and the dicalcium phosphate thus produced is collected and delivered to the phosphoric acid plant for conversion to phosphoric acid. The filtrate, which contains ammonia, is combined with the ammonia distillate from the plate column and recycled.

In the second process three-fourths of the ammonia filtrate is evaporated in a triple effect evaporator. The dilute ammonia boiled out is condensed and recycled. The thickened liquor if filtered, yielding the 12% U₃08 product. The filtrate from the 12% U₃08 product is mixed with phosphoric acid, refiltered to recover antimony thus precipitated, evaporated, and dried to recover 126 pounds of monobasic ammonium phosphate per pound of U₃08 recovered.

-1-

B. INTRODUCTION

Commercial 30% H₂PO4 contains small quantities of iron and vanadium which are present in such states that the oxidation state of about half of the uranium present is +6. In order to coprecipitate uranium from the acid with Sb₂O₂, it is necessary to have essentially all the uranium in the +4 oxidation state. Scrap iron provides the most economical means of accomplishing this. Two grams of iron are consumed per liter of 30% H₂PO4, and the oxidation potential of the acid is thus increased from -0.3 to 0.0 volt, as measured by the platinum-saturated calomel electrode couple.

Antimony trioxide reacts slowly with phosphoric acid according to the following reaction:

 $Sb_2O_3 + 2H_3PO_4 = 2SbOH_2PO_4 + H_2O$

No heat effects have been observed during the reaction. Uranium is coprecipitated along with the antimonyl di-hydrogen phosphate as uranous phosphate. Small portions of other cations are also coprecipitated. When 12.5 grams of powdered Sb₂O₃ are agitated with one liter of 30% H₂PO₄ (specific gravity = 1.21) which has been reduced as specified, 91 percent of the uranium is found in the SbOH₂PO₄ thus produced. This applies to a three-hour agitation period. From H₃PO₄ containing 0.10 gm. U₃O₈ per liter a precipitate is obtained which assays about 0.5% U₃O₈.

The precipitate is converted to Sb₂O₃ by dilute ammonia solutions, according to the reaction:

 $2SbOH_2PO_{l_1} + 4NH_4OH = Sb_2O_3 + 4NH_4^+ + 2HPO_{l_1}^- + 3H_2O_{l_2}^-$

The reaction is rapid and exothermic. If 100 percent excess 1 M ammonia is used, 95 percent of the uranium dissolves as a phosphate complex. The final pH of the system is about 9.5. About two percent of the antimony dissolves, presumably also as a phosphate complex.

When ammonia is boiled out of the solution a precipitate is obtained which assays 12% U308 (dry basis). Its properties resemble those of AlPO4, and in addition to aluminum it contains quantities of Sb, V, Cr, Fe, Ca, Al, Mg, and Ti. The only anion of importance is phosphate. The resulting solution has a pH of 6.5. Of the uranium present in the original ammoniacal solution, 96 percent reports in the precipitate. The mechanism seems to consist of a decrease in solubility of the uranous phosphate complex as the species of phosphate changes from 100 percent HPO4⁻⁻ to 84 percent $H_2PO_{l_1}$ and 16 percent HPO_{l_1} . Coprecipitation with the AlPO_{l_1} is also apparently involved.

Disposition can be made of the solution remaining after the 12% U₃O₈ is filtered off in two ways; lime treatment to remove phosphate, or addition of H₃PO4 and evaporation to produce fertilizer-grade NH4H₂PO4. If the latter is chosen, about twothirds of the antimony which dissolved in the ammonia can be recovered as SbOH₂PO4 after addition of the phosphoric acid.

-3-

C. PROCESS FLOW

The flow sheet for the two processes considered in this report is presented in Figures 1, 2, and 3. The first parts of the two processes are the same, and the flow sheet corresponding to them is given in Figure 1. The flow sheet for the first process, which produces C_2HPO_4 for return of phosphate to the plant, is completed in Figure 2. Figure 3 describes the last part of the second process, which produces $NH_4H_2PO_4$.

Antimony Trioxide Precipitation

Commercial 30% H₂PO₄ flows through a column containing scrap iron and is introduced into the Sb₂O₃ mixer, a 100-gallon vessel with provision for vigorous agitation. Vigorous agitation is necessary to prevent the Sb₂O₃, introduced in the make-up as a powder, from clumping and coating with SbOH₂PO₄, which would prevent further reaction. The thin slurry is led into three agitated 6000-gallon tanks arranged in series to provide an effective three-hour reaction period.

The slurry of 30% H₃PO4 and SbOH₂PO₄ is filtered, and the SbOH₂PO4 is washed and introduced into the NH₃ treatment vessel, which has a residence time of one hour. The H₃PO4, which has dissolved 0.12 gram Sb per liter, is returned to the plant with 91 percent of its uranium and 2.8 percent of its phosphate removed.

1.72 percent NHz solution in 100 percent excess is introduced into the NHz treatment vessel and the resulting slurry is filtered in the NHz filter. The solid from the filter is Sb_2O_3 , which is recycled. The filtrate, designated ammonia filtrate, is the source for uranium recovery by either of the two processes under consideration.

First Process - CaHPO4 Production

Twenty percent ammonia is stripped from the ammonia filtrate in a distillation unit consisting of a heat exchanger, distillation column, reboiler, and condenser. The distillation column must be of such design that solid particles which form during the distillation will not be trapped on the plates. Cooling water is assumed available at 75° F. with a 30 degree rise.

To the 20% NH₃ condensate is added sufficient anhydrous ammonia to make up for any lost ammonia and the mixture is dissolved in the 0.53% NH₃ from the CaHPO₄ filter. The resulting solution is cooled and recycled to the NH₃ treatment vessel. The bottoms from the distillation unit are filtered to recover the 12% U₂O₈ product, and the filtrate is mixed with lime in the lime tank. CaHPO4 is filtered off and delivered to the H₂PO4 plant for treatment with H₂SO4. The resulting H₂PO4 will contain nearly all the uranium originally in the CaHPO4.

Second Process - NHJ, HoPOJ, Production

The ammonia filtrate is preheated and evaporated to onefourth volume. The vapors are condensed to recovery ammonia, mixed with make-up ammonia and water, and cooled to produce the dilute ammonia solution required in the NH₂ treatment vessel. Standard vertical tube evaporators are specified because of the precipitation taking place during evaporation.

The thick liquor is filtered to obtain the 12% U₂O₈ product. Phosphoric acid is added to the filtrate, the result being a precipitate of mixed phosphates, which is filtered off and returned to the NH₃ treatment vessel. Thus, two additional pounds of U₂O₈ per day appear in the ammonia filtrate and consequently in the 12% U₃O₈ product.

After the SbOH₂PO₄ is filtered off, the solution is evaporated to produce 126 pounds of NH₄H₂PO₄ per pound of U₃O₈ produced.

D. DISCUSSION

The first process, which returns phosphate to the phosphoric acid plant in the form of CaHPO₄, requires a plant investment of \$496,000 and produces a solid assaying $12\% U_2O_6$ at a cost of \$13.28 per pound U_2O_8 . Tables I, II, and III detail the costs. The phosphate removal from the 30% H₂PO₄ amounts to 2.8 percent, and cost of the H₂SO₄ required to compensate for this removal is included in the estimate.

The second process, which manufactures $NH_4H_2PO_4$ instead of returning phosphate to the phosphoric acid plant, requires a plant costing \$513,000 and produces a solid assaying 12% U₃O₈ at a cost of \$14.31 per pound U₃O₈. 126 pounds $NH_4H_2PO_4$ are produced per pound U₃O₈. Table II itemizes the cost corresponding to the 3.2 percent phosphate removal.

No allowance was made in either estimate for the phosphate rock required to supply the phosphate. In the first process, this would amount to 0.2 percent, since phosphate is actually returned to the plant. In the second process, 3.2 percent of the phosphate rock costs are chargeable, but have been neglected. No charge was made for sizing or packaging the NH4H_2PO₄, since it was assumed that it would be used by the H₃PO₄ plant.

Because of the value of the antimony, no thickener was specified before filtration of the H₂PO₄. The slurry settles rapidly, but it leaves a colloidal suspension, which is slow to clarify, above the solid. The cost of a thickener of sufficient area to allow this suspension to clarify would be prohibitive.

The first process has one disadvantage. In order to distill out the ammonia from the ammonia filtrate, it is necessary to use a column designed to avoid clogging by the particles of 12% U₃O₈ product precipitated simultaneously, and plate efficiency would have to be sacrificed. This column and associated equipment must also be cleaned out regularly.

Substantial economies could be effected in both processes if either or both the settling and filtration characteristics of $SbOH_2PO_4$ were improved. If further research shows that the same uranium recoveries are obtainable from more concentrated ammonia treatments (the amount of NH_3 being the same), reductions in distillation equipment evaporator investment and steam consumption could be secured.

However, these processes require a rather large number of pieces of equipment to recover a very small amount of uranium, 12 tons per year, so there is a limit to the savings possible without change of process or increase in throughput. This limit is probably no greater than two dollars per pound U_308 .

E. <u>APPENDIX</u>

TABLE I

ESTIMATED COST OF PLANT TO RECOVER URANIUM FROM COMMERCIAL 30% H3PO4 BY MEANS OF ANTIMONY TRIOXIDE

Basis: 500 T 30% H₃PO₄ per day.

Source of Cost	CaHPO4 <u>Production</u>	NH4H2PO4 Production
Installed Process Equipment	\$157,000	\$165,000
Process Piping	47,000	50,000
Instrumentation	16,000	17,000
Manufacturing Buildings	47,000	50,000
Auxiliary Facilities	8,000	8,000
Outside Lines	8,000	8,000
Engineering and Construction	85,000	86,000
Contingency	85,000	86,000
Size Factor	43,000	43,000
Total	\$496,000	\$513,000

TABLE II

ESTIMATED COST OF RAW MATERIALS TO RECOVER URANIUM FROM COMMERCIAL 30% H3PO4 BY MEANS OF ANTIMONY TRIOXIDE

Basis: 500 T 30% H₃PO₄ per day. Assay of 0.00818 weight percent U₃O₈. Ninety percent stream efficiency. Recoveries indicated on figures.

		<u>Cost per 1b. UzC</u>	8 Produced
Raw Material	Cost per ton	CaHPO ₄ Production	Production
Scrap Iron	\$ 20	\$0.23	\$0.23
Sb203	540	1.2 ¹ +	.77
NH3	75	.07	•72
CaO	9	.24	.00
H ₂ SO4	10	.65	•8 ¹
		\$2.43	\$2.56

TABLE III

ESTIMATED COST OF PRODUCTION OF A SOLID ASSAYING 12% U₃O₈ FROM COMMERCIAL 30% H₃PO₁, BY MEANS OF ANTIMONY TRIOXIDE

Basis: 500 T 30% H₃PO₄ per day. Assay of 0.00818 weight percent U₃O₈. Ninety percent stream efficiency. Production as indicated on figures.

		Cost per 1b. Uz08 Produced		
Source of Cost	Basis	C ₂ HPO ₄ <u>Production</u>	NH _U H ₂ POU Production	
Operating Labor Supplies Utilities: Steam Electricity Water Fuel Maintenance Labor Maintenance Material Laboratory Insurance and Taxes Factory Expense Depreciation	Note (1) \$10 per man-mo. \$1/T 1.2¢/kwh. 5¢/M gal. \$2.40/bbl. 5% investment/yr. 5% investment/yr. Note (2) 2% investment/yr. 100% of labor 10% envestment/yr.	\$ 1.94 .05 .37 .12 .00 1.06 1.06 1.06 0.17 0.42 3.17 2.12	\$ 1.89 .05 1.08 .37 .30 .05 1.07 1.07 0.17 0.43 3.13 2.1 ⁴	
Total Processing Cost		\$ 10.85	\$ 11.75	
Raw Mate	rials	2.43	2.56	
Total Production Cost		\$ 13.28	\$ 14.31	

 \pm Less credit for 126 lbs. NH₄H₂PO₄

Notes: (1) 3 operators 24 hours per day at \$1.50 per hour plus one supervisor at \$6000 per year.

(2) Chemist at \$4000 per year.

-10-





ŧ



-13-

F. <u>ACKNOWLEDGEMENT</u>

The experimental work described in this report was performed by Eugene DeHaven.

٦

GPO 823215 · 2