

ARMY RESEARCH LABORATORY



Effect of a Warm, Moist Environment on JA2 Gun Propellant

by R. Pesce-Rodriguez, R. Leffers,
and P. Saguear

ARL-TR-1529

October 1997

19971124 014

DTIC QUALITY INSPECTED 2

Approved for public release; distribution is unlimited.

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-1529**October 1997**

Effect of a Warm, Moist Environment on JA2 Gun Propellant

R. Pesce-Rodriguez

Weapons and Materials Research Directorate, ARL

R. Leffers

Federal Armed Forces Technical Center for Weapons and Ammunition

P. Sagar

National Research Council Postdoctoral Associate

Abstract

Grains and sticks of JA2 propellant downloaded from a 120-mm tank round that had been subjected to conditioning at high temperature and humidity were observed to be discolored and covered with an unknown liquid. Analysis of the propellant indicated a decrease in the nominal diethylene glycol dinitrate (DEGDN) plasticizer content. The nitroglycerine (NG) content was not observed to deviate significantly from its nominal level. The cause of the discoloration of the propellant was traced to its high moisture content. The liquid covering the material was determined to be a mixture of water and DEGDN. In follow-up experiments, it was determined that JA2 propellant can absorb an excess of 13 wt-% moisture. It was also learned that graphite glaze can reduce the tendency of a grain to absorb moisture for grains immersed in water. When conditioned in a high-humidity environment, graphite glaze appeared to have no effect on the level of moisture absorbance. It is suspected that graphite serves to plug pores on the surface of the propellant and thereby inhibit, but not prevent, moisture absorption.

Acknowledgments

The authors are grateful to Mr. Ron Simmons of the Naval Surface Warfare Center/Indian Head Division for valuable discussions.

The authors also wish to thank the German Federal Office of Defense Technology and Procurement for providing support for Ms. Leffers.

This work was performed while Dr. Sagar was a National Research Council (NRC) U.S. Army Research Laboratory (ARL) Postdoctoral Research Associate.

INTENTIONALLY LEFT BLANK.

Table of Contents

	<u>Page</u>
Acknowledgments	iii
List of Figures	vii
List of Tables	vii
1. Introduction	1
2. Experimental	2
2.1 Samples	2
2.2 Instrumentation	3
2.3 Procedure	4
2.4 Instrument Calibration	5
3. Results and Discussion	5
3.1 Plasticizer Content	5
3.2 Stabilizer Content	7
3.3 Nitrocellulose Analysis	8
3.4 Identity of Unknown Liquid	9
3.5 Moisture Content	9
3.5.1 <i>Appearance of Wet Propellant</i>	9
3.5.2 <i>Desorption-GC-MS Data</i>	10
3.5.3 <i>Comparison of Desorption-GC-MS Data With Karl Fischer Data</i>	10
3.5.4 <i>Effect of Graphite Glaze on Moisture Absorption</i>	11
3.5.5 <i>Estimation of Drying Rate of Wet Propellant</i>	13
4. Conclusions	13
5. References	15
Distribution List	17
Report Documentation Page	23

INTENTIONALLY LEFT BLANK.

List of Figures

<u>Figure</u>	<u>Page</u>
1. Schematic Representation of Experimental Apparatus	4
2. Gas Chromatograms	6
3. Calibration Curve for Moisture Analysis Generated by Desorption of Water From Potassium Sodium Tartrate Tetrahydrate	7
4. FTIR Spectra of Standard and Downloaded JA2 Propellant	8
5. JA2 Propellant Recovered From Downloaded M829A2 Rounds	10
6. Moisture Content of JA2 Propellant Measured in Meppen (Using a Karl Fischer Method) and by ARL (Using the Desorption-GC-MS Method)	12
7. Cross-Sectioned JA2 Propellant That Had Been Stored in a Water Bath for 1 mo	12

List of Tables

<u>Table</u>	<u>Page</u>
1. Results for Moisture Analysis of JA2 Propellant	11

INTENTIONALLY LEFT BLANK.

1. Introduction

A solventless desorption gas chromatography mass spectroscopy (GC-MS) method for determination of moisture in solid gun propellants was developed in 1995 [1]. There are several traditional methods that might otherwise be used to determine moisture content of solid propellants (e.g., gravimetric techniques that involve heating the propellant and monitoring weight loss, and MIL-STD-2668 [2] or JANNAF 523.1 [3], which involve extracting water with dry solvents and then analyzing the extract by liquid or GC). The new desorption-GC-MS method was developed to meet the urgent request for analysis of JA2 samples suspected to have been exposed to excessive moisture. Conventional extraction methods could not be employed because there was neither time to dry the required solvents (MIL-STD-2668 recommends that solvents remain over molecular sieves for a minimum of two days before use) nor the local environmental conditions to keep the solvents dry (due to high, ambient humidity and the absence of adequate air conditioning). To meet the suspense for the required analyses, it was decided that an alternate, solvent-free technique be developed. This was successfully accomplished and yielded results in a relatively short period of time (instrument calibration plus approximately 30 sample runs in 10 hr). In addition, the method did not require the use of volatile organic compounds (VOCs) and consumed only small amounts of propellant. The main disadvantages of the method are that multiple analyses are required to assure representative results (since the test requires a very small sample size), and specialized instrumentation (e.g., a device in which materials may be desorbed from the propellant and then transferred directly into a GC-MS) is required.

Numerous samples of JA2 propellant have been analyzed using this convenient method. In most cases, the propellants were found to be within specifications. In one case, JA2 propellant that had been downloaded from a tank round that had been subjected to extreme temperature cycling at 95% relative humidity was analyzed and found to be several weight-percent below specifications with respect to plasticizer content and several weight-percent above specifications with respect to moisture content. The color of the samples was yellow/green, as opposed to the usual black/green color of "normal" JA2 propellant. When the yellow/green propellant was allowed to dry in a

desiccator, it was observed to turn black/green. A sample of the dried, black/green propellant, which was subsequently placed in a warm, high-moisture environment, was observed to absorb moisture and revert to the previous yellow/green color. "Standard" samples of JA2 propellant placed in the same environment underwent the same color change on absorption of moisture.

While the information regarding plasticizer content was of interest, it was perhaps of greater interest that JA2 could absorb enough water to result in a color change. The level of moisture found in the samples was well above that previously thought possible for JA2 propellant (i.e., ~1 wt-%). Given the significant effect that moisture can have on gun performance, it was decided that the issue of moisture absorption under "extreme" conditions deserved further attention. This report presents results of analyses of the downloaded propellant, as well as propellants conditioned in our laboratory. The goal of analyzing the latter was to provide a better understanding of the upper limit of moisture absorption by JA2, as well as the effect of graphite-glazing on moisture absorption. Also discussed is a method for instrument calibration that is an improvement over that described in Pesce-Rodriguez [1].

2. Experimental

2.1 Samples. Samples downloaded from a M829A2 120-mm armor-piercing, fin-stabilized, discarding sabot with tracer (APFSDS-T) tank round, including JA2 propellant, combustible cartridge case, adapter, propellant bag, and granular propellant bag, were made available by the Aberdeen Test Center (ATC) for analysis. The round had previously been subjected to temperature-cycling at 95% relative humidity for 28 days, following the outlined program as follows.

Step 1 - Propellant held at 21° C for 1 hr.

Step 2 - Temperature reduced to -54° C over the course of 2 hr.

Step 3 - Temperature held at -54° C for 5 hr.

Step 4 - Temperature raised to 71° C over the course of 3 hr.

Step 5 - Temperature held at 71° C for 13 hr.

Step 6 - Temperature reduced to -54°C over the course of 3 hr.

Step 7 - Repeat steps 3–6 until a total of 28 days has elapsed.

Note that the tank rounds were not in sealed canisters when tested; the only protection for the components within the round was the combustible case.

Samples conditioned in the lab were either hexagonal grains with 19 perforations and graphite glaze (1.1-cm diameter) or partially cut sticks with 19 perforations and no graphite glaze (1.7 mm-diameter). Propellant conditioned at 38% relative humidity (RH) was stored in an autodesiccator. Propellant conditioned at 92%-RH was stored over an 11% sulfuric acid solution. Measurements of percent-RH in both the autodesiccator and 92%-RH chamber were made using a Abbeon certified hygrometer (Model AB167B).

2.2 Instrumentation. Desorption was achieved via a CDS Model 122 Pyroprobe (coil type) connected to a heated interface chamber to the splitless injector of a Hewlett Packard GC-Fourier transform infrared (FTIR)-MS system (Model 5890 GC, Model 5970 MS detector [MSD], and Model 5965 infrared detector [IRD]). The GC column used for plasticizer analysis and initial moisture analyses was a Quadrex capillary column (0.32 mm $\times$ 25 m; 3 μm OV-17 film). Analysis of JA2 samples conditioned in the lab were analyzed using a J&W Scientific capillary column (0.25 mm $\times$ 15 m; 0.25 μm DB5 film). The choice of the column used was based solely on convenience. The GC injector temperature was 200°C . The oven-temperature program used was as follows: 50°C isothermal for 1 min, $70^{\circ}\text{C}/\text{min}$ to 250°C , 250°C for 4 min (total run time 7.86 min).

Analysis of downloaded JA2 propellant by FTIR microreflectance spectroscopy was performed using a Mattson Polaris FTIR spectrometer interfaced to a Spectra-Tech infrared (IR)-Plan IR microscope with a mercury-cadmium-telluride detector. The microscope was operated in reflectance mode, and aluminum foil was used to obtain a background spectrum. For all spectra, 32 scans were collected with a resolution of 8 cm^{-1} .

2.3 Procedure. Small samples of the solid propellant were cut using a razor blade, weighed, and placed into quartz tubes containing a plug of glass wool. The glass wool was used to prevent propellant from coming out of the tube. (Samples other than the JA2 propellant were not weighed before analysis.) The quartz tube was then placed within the coils of the pyroprobe heating element (see Figure 1), which was subsequently inserted into the pyroprobe interface and screwed into place. At the start of the GC run, a 150° C pulse (20-s duration) was given to the sample via the pyroprobe. It was confirmed that these conditions are sufficient for desorption of all moisture by giving a second pulse to the sample and observing no subsequent moisture desorption.




Figure 1. Schematic Representation of Experimental Apparatus.

For preparation of a calibration curve, known masses of potassium sodium tartrate tetrahydrate (PSTT) ($\text{KNaC}_4\text{H}_4\text{O}_6 \cdot 4\text{H}_2\text{O}$) were used. PSTT melts at 70–80° C, loses 3 H_2O at 100° C, and becomes anhydrous at 130–140° C. Desorption of the water of hydration of PSTT was achieved by pulsing at 150° C in a 150° C interface. The PSTT standards were analyzed in the same manner described previously.

Total ion chromatograms (TICs), based on MS response, were collected; selected ion chromatograms (SICs) were also obtained to distinguish between response due to desorbed water and plasticizer (the peaks partially overlap with one another). Integration of the $m/z = 18$ SIC yielded the peak area for water. An example of a TIC and SIC is given in Figure 2. For analysis of plasticizer content, m/z values of 58 and 73 were chosen for NG and DEGDN respectively. (For a description of the method for instrument calibration for plasticizer determination, please see Pesce-Rodriguez et al. [4, 5].)


2.4 Instrument Calibration. The moisture calibration curve obtained by analysis of known masses of PSTT is given in Figure 3. (For examples of calibration curves used for determination of plasticizer content, see Pesce-Rodriguez et al. [4, 5].)

Calibration curves obtained using the method described in Pesce-Rodriguez [1] were prepared by desorption of water that had been transferred to a plug of glass wool in a quartz tube by means of a microsyringe. Attempts to use the same method for the current analysis were complicated by the fact that the small quantities of water used tended to evaporate quickly in the low, ambient humidity of the laboratory. (Previous experiments had been performed during the summer when the ambient humidity was relatively high.)


3. Results and Discussion

3.1 Plasticizer Content. Since the focus for this report is on the determination of moisture absorption by JA2 under extreme conditions, plasticizer analysis was performed only on propellant downloaded from the M829A2 rounds. Samples conditioned in the lab were not analyzed for plasticizer content.

Downloaded propellant was found to contain the nominal level of NG. The DEGDN level was found to be between 2 and 6 wt-% less than the nominal value. Variation in the DEGDN levels are suspected to depend on the location in the tank round from which it had been sampled.



(a) Total Ion Chromatogram (TIC).



(b) Selected Ion Chromatogram (SIC) ($m/z = 18$, Water).

Figure 2. Gas Chromatograms.




Figure 3. Calibration Curve for Moisture Analysis Generated by Desorption of Water From Potassium Sodium Tartrate Tetrahydrate.

3.2 Stabilizer Content. Unfortunately, no analysis of stabilizer (Arkadit) content was performed; so, it is impossible to comment on the effect of high moisture content on stabilizer content and, therefore, on propellant stability. It is reasonable to assume that absorption of even a small amount of water will increase the likelihood of hydrolysis of nitrate bonds (assuming the presence of trace residual acid from nitration of cellulose). While the same should be true for absorption of large amounts of water (i.e., ~10 wt-%), it is also possible that the large, excess moisture may actually serve to stabilize the propellant, at least in the short term, by acting as a heat sink for exothermic decomposition reactions or other possible ignition sources.

(On a related note: Analysis of World War II munitions recovered from the Baltic Sea in 1993 indicated that sea water markedly slowed the decomposition rate of diphenyl amine [DPA] stabilizer by preventing oxygen from reaching the propellant. The percent nitration of the NC in the

propellant, however, was observed to be significantly decreased. Confirmation of the effect of oxygen on DPA decomposition was confirmed by subsequent control experiments [6].)

3.3 Nitrocellulose Analysis. Comparison of the IR spectra of downloaded JA2 with that of a standard JA2 sample indicate that the downloaded samples had not undergone a detectable degree of denitration as evidenced by the absence of carbonyl peaks (which absorb near $1,700\text{ cm}^{-1}$) in their spectrum (see Figure 4). The presence of carbonyl peaks would have been indicative of the loss of nitrate functional groups with the resultant formation of aldehyde functional groups. No measurements of the molecular weight of the NC were made.




Figure 4. FTIR Spectra of Standard and Downloaded JA2 Propellant. (Circles indicate the region of the spectrum in which carbonyl functional groups would absorb if they were present in the samples.)

3.4 Identity of Unknown Liquid. Desorption GC-MS analysis of the liquid found on the surfaces of the downloaded propellant and other components of the round revealed that the liquid was a mixture of water and DEGDN. No NG was detected in the liquid.

It is suspected that DEGDN is responsible for most of the water absorption. DEGDN is more likely than NG to form hydrogen bonds with water. Nitrocellulose propellant containing only NG is known to be quite water resistant (and was, at one time, advertised as being "waterproof") [7], whereas neat nitrocellulose is very water absorbent. DEGDN has a much higher vapor pressure than NG (3.6 vs. 0.2 torr at 20° C for DEGDN and NG, respectively) and is known to exude from propellants stored at elevated temperatures.

As a note of interest, [7] there is a sample of 100-yr-old double-base flake propellant (40% NG) at the Hercules Plant in Kenvil, NJ, which was made at the Laflin and Rand Haskell plant (also in NJ) that has been stored under water for most of its lifetime. After being dried in an oven overnight and fired in the small-caliber gun that it was originally designed for, the ballistics have not changed since the day it was made.

3.5 Moisture Content.

3.5.1 Appearance of Wet Propellant. The initial motivation for the chemical characterization of JA2 propellant conditioned under high humidity was a concern of ATC personnel regarding the appearance of the propellant downloaded from M829A2 rounds; the propellant had changed from its initial black/green color to a yellow/green color. It was observed that downloaded propellant returned to its initial black/green color after storage under low humidity conditions. The propellant reverted to the yellow/green color after either soaking in a water bath or being exposed to a warm, moist environment. Photos of JA2 propellant in its "wet" and "dry" conditions are shown in Figure 5. (Note: Three different grain geometries are shown. Difference in size not due to swelling.)




Figure 5. JA2 Propellant Recovered From Downloaded M829A2 Rounds. Dry propellant stored under ambient conditions for several days subsequent to downloading. Wet propellant stored over water vapor (40° C), similar in appearance (color) to material originally downloaded from round. Difference in size not due to swelling.

3.5.2 Desorption-GC-MS Data. The moisture content of the downloaded JA2 propellant provided by the ATC was found to be on the order of 7 wt-%. Based on subsequent analyses of samples prepared in the laboratory, it is suspected that the moisture content of the sample might have been higher had the samples been analyzed immediately after the propellant was downloaded. Table 1 presents the results for moisture analysis of samples conditioned in our laboratory. Note that military specifications for JA2 propellant call for 0.5 ± 0.3 -wt-% moisture.

3.5.3 Comparison of Desorption-GC-MS Data With Karl Fischer Data. Although the desorption-GC-MS measurements of moisture content reported in Table 1 were not compared with side-by-side measurements by a traditional method, the results from propellant conditioned at both 38%-RH and 92%-RH are about what one would expect, based on data obtained using a Karl Fischer method by a laboratory that routinely performs such analyses (i.e., the Gun and Rocket Propellant Lab of the Federal Armed Forces Technical Center for Weapons and Ammunition, Meppen, Germany). In Figure 6, moisture determinations made by the Meppen lab for two "typical" JA2 lots conditioned over the range of 10 %-RH to 95 %-RH are compared with results obtained at the U.S. Army Research Laboratory (ARL) for propellant conditioned at 38%-RH and 92 %-RH.

Table 1. Results for Moisture Analysis of JA2 Propellant

Sample Identity/Remarks (all samples conditioned for 1 mo)	Peak Area (arbitrary units)	Mass (mg)	Water (wt-%)
38%-RH, 22° C; no graphite glaze	17.1	7.900	0.35
38%-RH, 22° C; no graphite glaze	11.1	5.756	0.26
92%-RH, 22° C; no glaze; small piece	50.3	8.848	1.14
92%-RH, 22° C; no glaze; small piece	32.4	5.340	1.15
92%-RH, 22° C; glazed; full grain	36.5	5.923	1.19
92%-RH, 22° C; glazed; full grain	44.1	7.452	1.17
water bath; 22° C; no glaze; small piece	318.4	5.020	13.71
water bath; 22° C; no glaze; small piece	376.9	6.325	12.91
water bath; 22° C; glazed; full grain	128.6	7.290	3.73
water bath; 22° C; glazed; full grain	90.3	6.049	3.11
water bath; no glaze; full grain (t = 0.00 hr at 45%-RH)	416.4	7.991	11.3
water bath; no glaze; full grain (t = 0.48 hr at 45%-RH)	151.3	7.749	4.16
water bath; no glaze; full grain (t = 0.82 hr at 45%-RH)	130.7	6.531	4.24
water bath; no glaze; full grain (t = 0.90 hr at 45%-RH)	174.3	9.926	3.87
water bath; no glaze; full grain (t = 19.0 hr at 45%-RH)	25.1	11.796	0.38
water bath; no glaze; full grain (t = 19.3 hr at 45%-RH)	19.1	10.870	0.30

3.5.4 Effect of Graphite Glaze on Moisture Absorption. As indicated in Table 1, unglazed JA2 propellant can absorb on the order of 13-wt-% moisture when stored under extreme conditions (i.e., in a water bath for 1 mo). Under the same conditions, a glazed grain of JA2 propellant absorbs less than 4-wt-% moisture. It is suspected that the graphite serves to plug pores at the propellant surface and thereby inhibits moisture absorption. A photograph of cross-sectioned glazed and unglazed propellant is shown in Figure 7. Note that the glazed grain (which absorbed only 4-wt-% moisture) is much darker than the unglazed grain (which absorbed 11.3-wt% moisture). As in Figure 5, differences in size are not due to swelling, but different initial grain geometries.

When stored at 92%-RH, both glazed and unglazed propellant absorbed on the order of 1.1-wt-% moisture. In this case, it is suspected that even with many pores plugged with graphite, there are still sufficient sites available for the moisture content to reach 1 wt-%. No color difference was observed between the glazed and unglazed samples stored at 92%-RH.




Figure 6. Moisture Content of JA2 Propellant Measured in Meppen (Using a Karl Fischer Method) and by ARL (Using the Desorption-GC-MS Method).




Figure 7. Cross-Sectioned JA2 Propellant That Had Been Stored in a Water Bath for 1 mo. Left: JA2 hexagonal grain (exterior has graphite glaze, 19 perf, and 1.1-cm diameter). Right: JA2 stick (exterior has no graphite glaze, 19 perf, and 1.7-cm diameter). Difference in size not due to swelling.

3.5.5 Estimation of Drying Rate of Wet Propellant. While no formal kinetic study of the drying rate of JA2 propellant was made, it was qualitatively observed (see data in the bottom block of Table 1) that the moisture content of a thin slice of propellant initially containing approximately 11-wt-% moisture drops to approximately 4-wt-% moisture when allowed to dry under ambient conditions (i.e., 43%-RH, 22° C) for just 1 hr. After 20 hr, the moisture content drops to 0.30 wt-% and is probably as low as it will ever be under those ambient conditions.

4. Conclusions

A new technique for calibration of a desorption-GC-MS method was developed. Water desorbed from a hydrated salt (potassium sodium tartrate tetrahydrate) was used to generate a calibration curve that was successfully used to calculate the moisture content of JA2 propellant. The calibration technique was more convenient than one previously described [1].

Conditioning of JA2 propellant (in a fully loaded M829A2 tank round), under conditions of high humidity and temperatures for a period of 28 days, resulted in a depletion of the nominal level of DEGDN plasticizer, but appeared to have no effect on the level of NG plasticizer. No analysis of stabilizer content or NC molecular weight was performed. Analysis of the propellant by microreflectance FTIR spectroscopy suggested that no gross chemical changes had occurred. Changes in coloration of the propellant were ascribed to moisture absorption.

While the "common knowledge" regarding moisture absorption by JA2 was that the propellant does not absorb more than ~1-wt-% water, it has been shown that moisture levels in excess of 13 wt-% are possible.

Color changes (from black/green to yellow/green) are concomitant with absorption of large amounts moisture by JA2 propellant. A return to the original black/green color occurs when the propellant is allowed to dry.

Graphite glaze was found to inhibit absorption of water when propellant is submerged in water, but appears to have little effect when propellant is exposed to high humidity (at room temperature).

5. References

1. Pesce-Rodriguez, R. A., and R. S. Cumpton. "Solventless Method for Determining Moisture Content of Solid Propellants." *Proceedings of the 1995 JANNAF Propellant Development and Characterization Subcommittee Meeting*, CPIA Pub. 625, pp. 225–228, Jet Propulsion Laboratory, Pasadena, CA, April 1995; see also ARL-MR-290, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, 21001.
2. U.S. Army Armament Command. "Total Velocities by a Gas Chromatographic Method." MIL-STD-2668, Method T103.51, 20 December 1976.
3. CPIA Pub. "Moisture Analysis by a Gas Chromatography Method." *JANNAF Propellant Characterization Subcommittee Handbook*, June 1978.
4. Pesce-Rodriguez, R. A., N. F. Fell, Jr., J. M. Widder, and R. Greer. "Plasticizer Migration in Nitrocellulose-Based Propellants." *Proceedings of the 1996 JANNAF Propellant Development and Characterization Subcommittee Meeting*, CPIA Pub. 642, pp. 97–106, Fort Jackson, Columbia, SC, April 1996.
5. Pesce-Rodriguez, R. A., W. F. Oberle, M. DelGuercio, N. F. Fell, R. Leffers, and R. Green. "Review of Efforts to Reduce Migration in Layered Propellants." U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, in press.
6. Leffers, R., R. Scheibel, and H. Jahnk. "Überwachung der Treibladungspulver im Rahmen der Munitionsüberwachung." *Propellant Surveillance in the Scope of Ammunition Surveillance*, DEA 1218, WTD 91, Meppen, Germany, June 22–26, 1993.
7. Simmons, R. L. Private Communication. Naval Surface Warfare Center, Indian Head, MD, April 1997.

INTENTIONALLY LEFT BLANK.

NO. OF COPIES	ORGANIZATION
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC DDA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDQ DENNIS SCHMIDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	CECOM SP & TRRSTR L COMMCTN DIV AMSEL RD ST MC M H SOICHER FT MONMOUTH NJ 07703-5203
1	PRIN DPTY FOR TCHNLGY HQ US ARMY MATCOM AMCDCG T M FISETTE 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	PRIN DPTY FOR ACQUSTN HQS US ARMY MATCOM AMCDCG A D ADAMS 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	DPTY CG FOR RDE HQS US ARMY MATCOM AMCRD BG BEAUCHAMP 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	DPTY ASSIST SCY FOR R&T SARD TT T KILLION THE PENTAGON WASHINGTON DC 20310-0103
1	OSD OUSD(A&T)/ODDDR&E(R) J LUPO THE PENTAGON WASHINGTON DC 20301-7100

NO. OF COPIES	ORGANIZATION
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN PO BOX 202797 AUSTIN TX 78720-2797
1	USAASA MOAS AI W PARRON 9325 GUNSTON RD STE N319 FT BELVOIR VA 22060-5582
1	CECOM PM GPS COL S YOUNG FT MONMOUTH NJ 07703
1	GPS JOINT PROG OFC DIR COL J CLAY 2435 VELA WAY STE 1613 LOS ANGELES AFB CA 90245-5500
1	ELECTRONIC SYS DIV DIR CECOM RDEC J NIEMELA FT MONMOUTH NJ 07703
3	DARPA L STOTTS J PENNELLA B KASPAR 3701 N FAIRFAX DR ARLINGTON VA 22203-1714
1	SPCL ASST TO WING CMNDR 50SW/CCX CAPT P H BERNSTEIN 300 O'MALLEY AVE STE 20 FALCON AFB CO 80912-3020
1	USAF SMC/CED DMA/JPO M ISON 2435 VELA WAY STE 1613 LOS ANGELES AFB CA 90245-5500
1	US MILITARY ACADEMY MATH SCI CTR OF EXCELLENCE DEPT OF MATHEMATICAL SCI MDN A MAJ DON ENGEN THAYER HALL WEST POINT NY 10996-1786

NO. OF
COPIES ORGANIZATION

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CS AL TP
2800 POWDER MILL RD
ADELPHI MD 20783-1145

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CS AL TA
2800 POWDER MILL RD
ADELPHI MD 20783-1145

3 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CI LL
2800 POWDER MILL RD
ADELPHI MD 20783-1145

ABERDEEN PROVING GROUND

4 DIR USARL
AMSRL CI LP (305)

<u>NO. OF PAGES</u>	<u>ORGANIZATION</u>
1	HQDA SARD TT DR F MILTON WASH DC 20310-0103
1	HQDA SARD TT MR J APPEL WASH DC 20310-0103
1	HQDA OASA RDA DR C H CHURCH PENTAGON ROOM 3E486 WASH DC 20310-0103
4	COMMANDER US ARMY RESEARCH OFC R GHIRARDELLI D MANN R SINGLETON R SHAW P O BOX 12211 RESEARCH TRIANGLE PARK NC 27709-2211
1	DIRECTOR ARMY RESEARCH OFFICE AMXRO RT IP LIB SRVCS P O BOX 12211 RESEARCH TRIANGLE PARK NC 27709-2211
2	COMMANDER US ARMY ARDEC AMSTA AR AEE B D S DOWNS PICATINNY ARSENAL NJ 07806-5000
2	COMMANDER US ARMY ARDEC AMSTA AR AEE J A LANNON PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF PAGES</u>	<u>ORGANIZATION</u>
3	COMMANDER US ARMY ARDEC AMSTA AR AEE BR L HARRIS SMCAR AEE WE D ROBERTSON SMCAR CCH V F HILDERBRANT PICATINNY ARSENAL NJ 07806-5000
3	COMMANDER US ARMY MISSILE COMMAND AMSMI RD PR E A R MAYKUT AMSMI RD PR P R BETTS AMSMI RD PR T J G CARVER REDSTONE ARSENAL AL
1	OFFICE OF NAVAL RESEARCH DEPARTMENT OF THE NAVY R S MILLER CODE 432 800 N QUINCY STREET ARLINGTON VA 22217
1	COMMANDER NAVAL AIR SYSTEMS COMMAND J RAMNARACE AIR-54111C WASHINGTON DC 20360
1	OSD SDIO IST L CAVENY PENTAGON WASHINGTON DC 20301-7100
1	COMMANDANT USAFAS ATSF TSM CN FORT SILL OK 73503-5600
1	PRINCETON COMBUSTION RSRCH LABORATORIES INC N A MESSINA PRINCETON CORPORATE PLAZA BLDG IV SUITE 119 11 DEERPARK DRIVE MONMOUTH JUNCTION NJ 08852
1	BRIGHAM YOUNG UNIVERSITY DEPT OF CHMCL ENGNRNG M W BECKSTEAD PROVO UT 84058

<u>NO. OF PAGES</u>	<u>ORGANIZATION</u>
1	UNIV OF SOUTHERN CA DEPT OF CHEMISTRY R BEAUDET LOS ANGELES CA 90007
1	UNIV OF DELAWARE T BRILL CHEMISTRY DEPARTMENT NEWARK DE 19711
1	THE JOHNS HOPKINS UNIV CPIA J FILLBEN 10630 LTLE PTXNT PKWY STE 202 COLUMBIA MD 21044-3200
1	PA STATE UNIVERSITY DEPT OF MCHNCL ENGNRNG K KUO UNIVERSITY PARK PA 16802
1	PRIMEX TECHNOLOGIES B PERKINS 10101 NINTH ST N MLK ST N ST PETERSBURG FL 33716
1	HERCULES INC R V CARTWRIGHT 100 HOWARD BLVD KENVIL NJ 07847
1	OLIN ORDNANCE V MCDONALD LIBRARY P O BOX 222 ST MARKS FL 32355-0222
1	PAUL GOUGH ASSOCIATES INC P S GOUGH 1048 SOUTH STREET PORTSMOUTH NH 03801-5423
1	FRE LIN ASSOC F ROBBINS 4411 QUAKER HILL CT HAVRE DE GRACE MD 21078
1	ROCKWELL INTRNTNL CORP ROCKETDYNE DIVISION J E FLANAGAN HB02 6633 CANOGA AVENUE CANOGA PARK CA 91304

<u>NO. OF PAGES</u>	<u>ORGANIZATION</u>
1	THIOKOL CORPORATION ELKTON DIVISION TECH LIB P O BOX 241 ELKTON MD 21921
1	THIOKOL CORPORATION WASATCH DIVISION TECH LIBRARY P O BOX 524 BRIGHAM CITY UT 84302
1	UNITED TECHNOLOGIES CORP CHEMICAL SYSTEMS DIVISION R R MILLER P O BOX 49028 SAN JOSE CA 95161-9028
1	VERITAY TECHNOLOGY INC E B FISHER 4845 MILLERSPORT HWY P O BOX 305 EAST AMHERST NY 14051-0305
1	FREEDMAN ASSOCIATES E FREEDMAN 2411 DIANA ROAD BALTIMORE MD 21209-1525
1	BENET LABORATORIES SAM SOPOK AMSTA AR CCB B WATERVLIET NY 12189
2	NVL SURFACE WARFARE CTR INDIAN HEAD DIVISION CODE 6210F D LEE PROP AND EXPLOSIVES R SIMMONS INDIAN HEAD MD 20640-5000
2	ALLIANT TECH SYSTEMS D POLLOCK ROUTE 114 PO BOX 1 RADFORD VA 24141-0100

<u>NO. OF PAGES</u>	<u>ORGANIZATION</u>	<u>NO. OF PAGES</u>	<u>ORGANIZATION</u>
2	GEOCENTERS INC K SHAW L KANSAS 200 VALLEY RD STE 102 MOUNT ARLINGTON NJ 07856		L.D. SEGER J.A. VANDERHOFF D. VENIZELOS
2	ABERDEEN TEST CENTER STEAC TS PC B363 A RAUNIG P MARSH APG MD 21005-5059		
	<u>ABERDEEN PROVING GROUND</u>		
35	DIR, USARL ATTN: AMSRL-WM-P, A.W. HORST AMSRL-WM-PC, B.E. FORCH W.R. ANDERSON R.A. BEYER S.W. BUNTE C.F. CHABALOWSKI K.P. MCNEILL- BOONSTOPPEL A. COHEN R. DANIEL D. DEVYNCK R.A. FIFER J.M. HEIMERL B.E. HOMAN A. JUHASZ A.J. KOTLAR E. LANCASTER W.F. MCBRATNEY K.L. MCNESBY M. MCQUAID M.S. MILLER A.W. MIZIOLEK J.B. MORRIS J.E. NEWBERRY S.V. PAI R.A. PESCE-RODRIGUEZ J. RASIMAS P. REEVES B.M. RICE P. SAEGAR R.C. SAUSA M.A. SCHROEDER R. SCHWEITZER		

INTENTIONALLY LEFT BLANK.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE October 1997	3. REPORT TYPE AND DATES COVERED Final, Jul 96 - Mar 97		
4. TITLE AND SUBTITLE Effect of a Warm, Moist Environment on JA2 Gun Propellant		5. FUNDING NUMBERS 1L161102AH43		
6. AUTHOR(S) R. Pesce-Rodriguez, R. Leffers*, and P. Saguear**				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-PC Aberdeen Proving Ground, MD 21005-5066		8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-1529		
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES * Federal Armed Forces Technical Center for Weapons and Ammunition (WTD 91) Meppen, Germany ** National Research Council Postdoctoral Associate				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.		12b. DISTRIBUTION CODE		
13. ABSTRACT (Maximum 200 words) Grains and sticks of JA2 propellant downloaded from a 120-mm tank round that had been subjected to conditioning at high temperature and humidity were observed to be discolored and covered with an unknown liquid. Analysis of the propellant indicated a decrease in the nominal diethylene glycol dinitrate (DEGDN) plasticizer content. The nitroglycerine (NG) content was not observed to deviate significantly from its nominal level. The cause of the discoloration of the propellant was traced to its high moisture content. The liquid covering the material was determined to be a mixture of water and DEGDN. In follow-up experiments, it was determined that JA2 propellant can absorb an excess of 13 wt-% moisture. It was also learned that graphite glaze can reduce the tendency of a grain to absorb moisture for grains immersed in water. When conditioned in a high-humidity environment, graphite glaze appeared to have no effect on the level of moisture absorbance. It is suspected that graphite serves to plug pores on the surface of the propellant and thereby inhibit, but not prevent, moisture absorption.				
14. SUBJECT TERMS solid propellant, moisture content, nitroglycerine, diethylene glycol dinitrate, moisture absorption, humidity			15. NUMBER OF PAGES 26	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-1529 (Pesce-Rodriguez) Date of Report October 1997

2. Date Report Received _____

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)


DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

**DIRECTOR
US ARMY RESEARCH LABORATORY
ATTN AMSRL WM PC
ABERDEEN PROVING GROUND MD 21005-5066**



**NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES**

