REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188
Public reporting burden for this collection of gathering and maintaining the data needed, collection of information, including suggesti Davis Highway, Suite 1204, Artington, VA 2	Information is estimated to average 1 hour per and completing and reviewing the collection o ons for reducing this burden to Washington Her 2202-4302, and to the Office of Management	r response, including the time for review f information. Send comments regardlin adquarters Services, Directorate for Info and Burdnet Panenork Berturtion Pro-	ing Instructions, searching existing data sources, ing Instructions, searching existing data sources, ing this burden estimate or any other aspect of this ormation Operations and Reports, 1215 Jefferson er (0700-01189). Wachington, DC 2050
1. AGENCY USE ONLY (Leave blank	2. REPORT DATE November 16, 199	8 3. REPORT TYPE AN 8 Technical Repo	D DATES COVERED ort # 43
4. THE AND SUBTILE J- Aggregates of Conjugated Polymers			5. FUNDING NUMBERS N00014-94-1-0540 Kenneth J. Wynne R & T Code 3132111
Samson A. Jenekhe, Xuej	un Zhang and X. Linda Che	en	
7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES)			8. PERFORMING ORGANIZATION
University of Rochester			REPORT NUMBER
Department of Chemical Engineering			# 43
206 Gavett hall, Box 270166			
Rochester. NY 14627-016	56		
9. SPONSORING / MONITORING AGENCY NAMES(S) AND ADDRESS(ES) 10			10. SPONSORING / MONITORING
Office of Naval Pacaarah			AGENCY REPORT NUMBER
800 North Quincy Street			
Arlington, VA 22217-500	0		
		100	81120 150
Submitted to J. Amer. Chem. Soc			01120 177
Deproduction in whole and			12. DISTRIBUTION CODE
States Government This c	In part is permitted for any plocument has been approved	d for public release	
and sale; its distribution is	unlimited.	a for public release	
13. ABSTRACT (Maximum 200 words)		
The first observation of I-	aggregates of conjugated r	olymers in solution is	reported Concentrated estations
(1-8.8 mM) of conjugated	l polyguinolines 1a and 1 h	exhibited narrow in	tense and red shifted absorption
bands, smaller Stokes shi	fts, and shortened fluores	cence lifetimes, comp	pared to isolated chains in dilute
solution, which are chara	cteristic of J-aggregation.	In the solid state 1	b formed highly luminescent J-
aggregates whereas 1a for	med excimers, reflecting the	he greater intermolecu	lar distance in 1b. The excitonic
role of intermolecular inter	-aggregates was estimated	to be 15-24. These re	esults provide new insights on the
design of more efficient electroluminescent polymers organic lasing materials and ave implications for the			
materials.	recurrent mineseent porymer	s, organic fasting mate	alais, and cubic nonlinear optical
4. SUBJECT TERMS			15. NUMBER OF PAGES
J-aggregates; macromolecular aggregates; excimer formation; intramolecular			20
meractions; conjugated po	iymers; iuminescent polyme	ers; polyquinolines.	16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT	18. SECURITY CLASSIFICATION OF THIS PAGE	19. SECURITY CLASSIFIC OF ABSTRACT	ATION 20. LIMITATION OF ABSTRACT
Unclassified	Unclassified	Unclassified	Unlimited
			Standard Form 298 (Rev. 2-89) Prescribed by ANISE Sad Z39-18 298-102

, ,

DTIC QUALITY INSPECTED S

OFFICE OF NAVAL RESEARCH

GRANT NO: N00014-94-1-0540

R&T Code 3132111 Kenneth J. Wynne

Technical Report NO. 43

J-Aggregates of Conjugated Polymers

By

Samson A. Jenekhe, Xuejun Zhang and X. Linda Chen Prepared for Publication

In

J. Amer. Chem. Soc.

Department of Chemical Engineering and Center for Photoinduced Charge Transfer University of Rochester, New York 14627

November 16, 1998

Reproduction in whole or in part is permitted for any purpose of the United States Government

This document has been approved for public release and sale; its distribution is unlimited.

J-Aggregates of Conjugated Polymers

Samson A. Jenekhe*, Xuejun Zhang, and X. Linda Chen

Departments of Chemical Engineering and Chemistry and Center for Photoinduced Charge Transfer, University of Rochester, Rochester, New York 14627-0166

Abstract

The first observation of J-aggregates of conjugated polymers in solution is reported. Concentrated solutions (1–8.8 mM) of conjugated polyquinolines **1a** and **1b** exhibited narrow, intense, and red shifted absorption bands, smaller Stokes shifts, and shortened fluorescence lifetimes, compared to isolated chains in dilute solution, which are characteristic of J-aggregation. In the solid state **1b** formed highly luminescent Jaggregates whereas **1a** formed excimers, reflecting the greater intermolecular distance in **1b**. The excitonic delocalization size of the J-aggregates was estimated to be 15–24. These results provide new insights on the role of intermolecular interactions on the luminescence of conjugated polymers and have implications for the design of more efficient electroluminescent polymers, organic lasing materials, and cubic nonlinear optical materials.

J-Aggregates of Conjugated Polymers

Samson A. Jenekhe*, Xuejun Zhang, and X. Linda Chen

Departments of Chemical Engineering and Chemistry and Center for Photoinduced Charge

Transfer, University of Rochester, Rochester, New York 14627-0166

The nature of the photophysics of conjugated polymers and how molecular and supramolecular structures influence it are questions of growing fundamental and practical interest.¹⁻⁶ Although conjugated polymers are promising for light-emitting diodes,⁷ solid state lasers,⁸ and xerographic photoreceptors,⁹ how to fundamentally improve their electronic and optical properties for these and other applications remains a challenging problem. Here, we report the first observation of J-aggregates of conjugated polymers in solution. We also show that J-aggregation and excimer formation in conjugated polymers can be regulated through side group substitution which controls the intermolecular distance in the solid state. The results provide new insights on the role of intermolecular interactions on the luminescence of conjugated polymers and have implications for the design of more efficient electroluminescent polymers, organic lasing materials, and cubic nonlinear optical materials.

The observation of new emission bands and significant luminescence quenching in thin films of conjugated polymers, compared to their dilute solutions, led to the suggestion^{1(a)} that "the fundamental approach to efficient photophysical processes in conjugated polymers is through control of the supramolecular structure and morphology of the materials." Many experimental¹⁻⁴ and theoretical^{5,6} studies have since confirmed various effects of intermolecular interactions on the absorption and emission properties of conjugated polymers. Emissive excited state complexes (excimers, exciplexes)¹ and ground state complexes ("aggregates")²⁻⁴ have been

reported in solid films of different polymers. One challenging question of continuing debate is how to distinguish excimers from aggregates of conjugated polymers.¹⁻⁶ The well-known characteristic absorption features of J- or H-aggregates of dye molecules¹⁰ have not yet been similarly observed in solution or solid state forms of conjugated polymers. Recently, laser-like emission spectral narrowing have been observed in various conjugated polymer thin films.⁸ One of the leading interpretations of this phenomenon is superfluorescence (SF) or superradiance (SR) that arises from cooperative emission from "aggregates".^{8(b),11} However, the nature of the emissive aggregates is yet to be established. Studies aimed at a better understanding of the various electronic ground state and excited state supramolecular assemblies of conjugated polymers are thus warranted.



We investigated absorption and emission properties as a function of intermolecular separation in solutions and thin films of two conjugated polymers: poly(2,2'-(p-phenyl)-6,6'-bis(4-phenylquinoline)) (PPPQ, **1a**) and poly(2,2'-(p-phenyl)-6,6'-bis(3-(n-nonyl)-4-(p-tert-butyl)phenyl quinoline)) (BuN-PPQ,**1b**). We have previously reported the synthesis¹² and electroluminescent^{12(b),13} properties of**1a**,**1b**, and other related polyquinolines. Because of the side group substitutions in**1b**the minimum separation distance between adjacent chains is larger than in**1a** $. By varying the concentration from ~1 <math>\mu$ M to 20 mM, based on repeat unit, we also

regulated the intermolecular separation between chains in formic acid solutions. Polymer thin films on silica substrates were spin coated from the most concentrated solutions and vacuum dried overnight at 60 °C to remove residual solvent. Photoluminescence emission (PL) and excitation (PLE) spectra were obtained at room temperature by using the front face configuration and a Spex Fluorolog-2 spectrofluorimeter. Details of PL decay dynamics measurement via laser excitation in time-correlated single photon counting experiments are as previously reported.¹⁴

The evolution of PLE spectra with solution concentration of 1a is shown in Figure 1. In the most dilute solution (0.65 μ M), a broad absorption band with λ_{max} at 407 nm and a full-width at half-maximum (FWHM) of 93 nm is observed in the PLE spectrum. We assign this to the spectrum of isolated chains of 1a. The absorption spectrum (not shown) of this solution and other more concentrated ones were identical to this PLE spectrum. At higher concentration (9.8 µM), a Davydov split of the PLE spectrum into two narrow absorption bands with peaks at 330 and 436 nm is observed. The longer wavelength band is both narrower and more intense than the shorter wavelength component. Upon further increase of concentration to 8.8 mM the PLE spectrum showed only one intense absorption band with a peak at 466 nm and a FWHM of 19 nm. These excitation spectra features, particularly the narrow, red-shifted absorption bands of concentrated solutions, reveal J-aggregation of 1a. Assuming that the exciton delocalization theory for dye aggregates is applicable to these macromolecular aggregates, the linewidth of the excitonic J band is expected to be narrower than that of the isolated molecule by $-N_c^{1/2}$ where N_c is the number of coherently coupled molecules in the aggregate.^{10(c)} We estimated $N_c = 24$ from the observed PLE linewidth of the 8.8 mM solution of 1a.

The PL spectra of **1a** solutions were independent of concentration, having identical lineshape and emission peak at 498 nm (Figure 1, curves 4-6). The emission spectrum of **1a**

solutions was also independent of excitation wavelength, including direct excitation of the 436and 466-nm peaks we assigned to J-aggregate bands. Taken together with the PLE spectra the Stokes shift thus decreased from 0.57 eV in the most dilute to 0.17 eV in the most concentrated. Vanishing Stokes shift, shortened fluorescence lifetime, and enhanced luminescence are commonly observed in the highly ordered and strongly coupled J-aggregates of dyes.¹⁰ The PL decay dynamics monitored at 498 nm (350-nm excitation) was essentially monoexponential for all three **1a** solutions. The fluorescence lifetimes were 0.80, 0.75, and 0.68 ns, respectively, shortening with increasing concentration. These steady-state PL spectra and fluorescence lifetime results are also consistent with J-aggregation.

Also shown in Figure 1 is the PL spectrum of **1a** thin film. The very broad emission band with peak at 578 nm is significantly red-shifted from the J-aggregate emission spectra in solution. The PLE spectrum corresponding to the 578-nm emission (not shown) was identical to that of the most dilute solution (Fig. 1, curve 1) except that an additional weak absorption in the 450-500 nm was seen. A huge Stokes shift of 0.91 eV was thus observed in **1a** thin film. The weak emission band in the ~450-500 nm region is in the same position as the J-aggregate emission in the concentrated solutions. These emission spectral characteristics suggest the presence of two emitting species in thin films, one is clearly J-aggregates which is also the minority component. The thin film PL decay dynamics was best described by two fluorescence lifetimes of 4.29 ns (57%) and 0.96 ns (31%). By comparison with the solution data, the species with 0.96-ns lifetime can be assigned to the J-aggregates. The long-lived, dominant species with a large Stokes shift can be assigned to excimers or excited state complexes. **1**(a)

The solution PLE and PL spectra of **1b** are shown in Figure 2. From similar arguments made for **1a**, we conclude that the sharp, narrowed, and red-shifted PLE spectrum of 1mM **1b**

evidence J-aggregates. In this case, the J-band at 397 nm has a FWHM of 20 nm compared to 78 nm linewidth of the 1 μ M solution PLE spectrum. From this we estimate the effective excitonic delocalization size (N_c) in **1b** aggregates to be 15. The PL spectra of **1b** were independent of concentration and they have a peak at 470 nm (Fig. 2, curves 4-6). Interestingly, the thin film PL spectrum of **1b** with a peak at 454 nm essentially overlaps the solution spectra but was more intense, suggesting J-aggregation. The thin film emission band is, however, broader due to a blue shoulder which may indicate different aggregate supramolecular structures. All the solution PL decay dynamics were very similar and can be approximately described by one lifetime as exemplified by 4.84 ns for the 1 mM J-aggregates. In contrast, the thin film PL decay was non-exponential with two main lifetimes: 60 ps (56%) and 410 ps (26%). The dramatically shortened lifetime and enhanced luminescence in **1b** thin film compared to solution confirmed its J-aggregate nature.

Comparison of results for **1a** and **1b** shows that both spontaneously formed J-aggregates in concentrated solutions. However, in the solid state **1b** formed highly luminescent J-aggregates whereas **1a** formed primarily excimers with a small amount of J-aggregates. These findings demonstrate the control of the photophysics of luminescent conjugated polymers through synthetic regulation of supramolecular structure. Furthermore, contrary to previous thought^{2,3} excimers can form in aggregated conjugated polymers.

In summary, we have observed J-aggregates of conjugated polymers in concentrated solutions and in solid films. Narrow and red-shifted absorption bands resolved by PLE spectroscopy, shortened excited state lifetimes, and enhanced luminescence, compare to isolated chains, were characteristic features of these *macromolecular* J-aggregates. Excimer formation by **1a** and J-aggregation of **1b** in the solid state demonstrated the synthetic control of intermolecular

distances in supramolecular assemblies of conjugated polymers. Block copolymer self-assembly of various supramolecular aggregate morphologies represents an approach that could be used to further manipulate these new forms of conjugated polymers.¹⁵ Based on dye molecule precedents,¹⁶ enhanced cubic nonlinear optical properties are anticipated in J-aggregates of conjugated polymers.

Acknowledgment. This research was supported by the Office of Naval Research and in part by the National Science Foundation (CTS-9311741, CHE-9120001).

Supporting Information Available: Figures showing thin film or solution UV-Vis, PLE, and PL spectra, PL decay dynamics of **1a** and **1b**, and their textural description (8 pages). This material is contained in many libraries on microfiche, immediately follows this article in the microfilm version of the journal, can be ordered from the ACS, and can be downloaded from the Internet; see any current masthead page for ordering information and Internet access instructions.

References

(1) (a) Jenekhe, S. A.; Osaheni, J. A. Science **1994**, 265, 765. (b) Osaheni, J. A.; Jenekhe, S. A. Macromolecules **1994**, 27, 739.

(2) Lemmer, U.; Heun, S.; Mahrt, R. F.; Scherf, U.; Hopmeier, M.; Siegner, U.; Gobel, E. O.;
Mullen, K.; Bassler, H. Chem. Phys. Lett. 1995, 240, 373.

- (3) (a) Blatchford, J. W.; Gustafson, T. L.; Epstein, A. J.; VandenBout, D. A.; Kerimo, J.;
- Higgins, D. A.; Barbara, P. F.; Fu, D. K.; Swager, T. M.; MacDiarmid, A. G. Phys. Rev. B 1996,
- 54, R3683. (b) Blatchford, J. W.; Jessen, S. W.; Lin, L. B.; Gustafson, T. L.; Fu, D. K.; Wang, H.
- L.; Swager, T. M.; MacDiarmid, A. G.; Epstein, A. J. Phys. Rev. B 1996, 54, 9180.
- (4) Samuel, I. D. W.; Rumbles, G.; Collison, C. J.; Moratti, S. C.; Holmes, A. B. Chem. Phys. 1998, 227, 75.
- (5) Conwell, E. Trends Polym. Sci. 1997, 5, 218.
- (6) Cornil, J.; dos Santos, D. A.; Crispin, X.; Silbey, R.; Bredas, J. L. J. Am. Chem. Soc. 1998, 120, 1289.
- (7) Burroughes, J. H.; Bradley, D. D. C.; Brown, A. R.; Marks, R. N.; Mackay, K.; Friend, R.
 H.; Burn, P. L.; Holmes, A. B. *Nature* 1990, *347*, 539.
- (8) (a) Tessler, N.; Denton, G. J.; Friend, R. H. Nature 1996, 382, 695. (b) Frolov, S. V.;
- Vardeny, Z. V.; Yoshino, K. Phys. Rev. B 1998, 57, 9141. (c) Hide, F.; Diaz-Garcia, M. A.;
- Schwartz, B. J.; Anderson, M. R.; Pei, Q.; Heeger, A. J. Science 1996, 273, 1833.
- (9) Osaheni, J. A.; Jenekhe, S. A.; Perlstein, J. J. Phys. Chem. 1994, 98, 12727.
- (10) (a) Kasha, M. Radiation Research 1963, 20, 55. (b) Czikkely, V.; Forsterling, H. D.; Kuhn,
- H. Chem. Phys. Lett. 1970, 6, 11. (c) Knapp, E. W. Chem. Phys. 1984, 85, 73. (d) Spitz, C.; Daehne, S. Ber. Bunsenges. Phys. Chem. 1998, 102, 738.

(11) Long, X.; Malinowski, A.; Bradley, D. D. C.; Inbasekaran, M.; Woo, E. P. Chem. Phys. Lett. 1997, 272, 6.

(12) (a) Agrawal, A. K.; Jenekhe, S. A. Macromolecules 1993, 26, 895. (b) Shetty, A. S.;

Zhang, X.; Jenekhe, S. A. Mater. Res. Soc. Fall Meeting, Dec. 1-5, 1997: Boston, MA.

(13) Zhang, X.; Shetty, A. S.; Jenekhe, S. A. Acta Polymerica 1998, 49, 52.

- (14) Osaheni, J. A.; Jenekhe, S. A. J. Am. Chem. Soc. 1995, 117, 7389.
- (15) Jenekhe, S. A.; Chen, X. L. Science 1998, 279, 1903.
- (16) Spano, F. C.; Mukamel, S. Phys. Rev. A 1989, 50, 5783.

Figure Captions

Figure 1. PLE spectra (520-nm emission) of **1a** solutions (1) 0.65 μ M, (2) 9.8 μ M, (3) 8.8 mM; PL spectra (400-nm excitation) of **1a** solutions (4) 0.65 μ M, (5) 9.8 μ M, (6) 8.8 mM; and PL spectrum (400-nm excitation) of **1a** thin film (7).

Figure 2. PLE spectra (470-nm emission) of **1b** solutions (1) 1 μ M, (2) 100 μ M, (3) 1 mM; PL spectra (350-nm excitation) of **1b** solutions (4) 1 μ M, (5) 100 μ M, (6) 1 mM; and PL spectrum (350-nm excitation) of **1b** thin film (7).

Figure 1



,

Figure 2



,

J-Aggregates of Conjugated Polymers

Samson A. Jenekhe*, Xuejun Zhang, and X. Linda Chen

Departments of Chemical Engineering and Chemistry and Center for Photoinduced Charge Transfer, University of Rochester, Rochester, New York 14627-0166

Supporting Material

Figure S-1 shows optical absorption, PL, and PLE spectra of 1a thin film on silica substrate. The excitation wavelength is 400 nm and the emission wavelength is 578 nm. The absorption spectrum shows two peaks at 400 and 300 nm. It also shows a relatively sharp absorption edge at 445 nm. The corresponding PLE spectrum tracks the absorption spectrum very well except that it showed a split (400 and 422 nm) in the main peak and a hump in the 450 to 500 nm region. These new features not observed in the absorption spectrum indicate existence of J-aggregates in 1a (PPPQ) since the hump coincides with the J-aggregate band observed in solution PLE spectra. The PL spectrum of 1a film with emission peak at 578 nm showed a large Stokes shift of 0.91 eV. This peak is also redshifted about 70 nm compared to the aggregate emission peak (498 nm) in solutions. Therefore, the emission of 1a thin film is due to excimers. In this respect, we point out two things. First, J-aggregates clearly exist in 1a thin film as indicated by the 450-500 nm excitation and emission humps, but the emission is largely from excimers. Second, the Jaggregates are involved in excimer formation. This is evident from the independence of PL spectra with excitation wavelength (Figure S-2).

Absorption, PL, and PLE spectra of **1b** thin film are shown in Figure S-3. The absorption spectrum has two peaks at 275 and 347 nm. The PLE spectrum is identical to

1

the absorption except that the 347 nm peak is relatively more intense. The PL spectrum of **1b** has a peak at 454 nm. PLE spectra of two **1b** solutions (10 μ M and 20 mM) are also shown in Figure S-3. The 10 μ M **1b** solution has identical PLE spectrum to the 1 μ M solution with a peak at 353 nm. The 20 mM **1b** solution which is the most concentrated has a broad PLE spectrum with a peak at 360 nm. This rather broad excitation band suggests that considerable disorder has occurred; the supramolecular assemblies probably consists of more than one type of J-aggregate.

Time-resolved PL decay dynamics was measured by using the time-correlated single photon counting (SPC) technique. The excitation system consists of a cavity dumped dye laser (Coherent Model 703D) circulating rhodamine 6G, synchronously pumped by a mode-locked frequency doubled Nd:YAG laser (Quantronics Model 416). The dye laser pulses were typically 10 ps duration at a repetition rate of 38 MHz, and the samples were excited at 350 nm and monitored at the respective emission peaks of samples. The PL decay was detected at the emission peak wavelength. Figures S-4 to S-6 show PL decay dynamics of 1a and 1b solutions and thin films. For solutions, the decay dynamics can be best described by a single lifetime; for thin films, two lifetimes were needed to fit the data. The 1a solutions showed lifetimes of 0.68, 0.75, and 0.80 ns, respectively, for concentrations of 8.8 mM, 9.8 μ M, and 0.65 μ M. The 1b solutions showed lifetimes of 4.10, 4.84, 4.68, 4.72, and 4.72 ns, respectively, for concentrations of 20 mM, 1 mM, 0.1 mM, 10 μ M, and 1 μ M. The **1a** thin film had lifetimes of 4.29 (57%) amplitude) and 0.96 ns (31%). The 1b thin film had lifetimes of 410 (26%) and 60 ps (56%). The dramatic difference in fluorescence decay dynamics of 1a and 1b thin films is exemplified in Figure S-6.

2



ð

Figure S-1. Absorption, PLE, and PL spectra of **1a** (PPPQ) thin film on silica substrate. The excitation wavelength for PL was 400 nm and the emission wavelength for PLE was 578 nm.



Figure S-2. PL spectra of 1a (PPPQ) thin film with different excitation wavelengths

in the range of 350-480 nm.



۰.

۰.

Figure S-3. Absorption (1), PLE (2), and PL (3) spectra of 1b (BuN-PPQ) thin film on silica substrate and PLE spectra of 1b in formic acid solutions of 10 mM (4) and 20 mM (5). The excitation wavelength was 350 nm, and the monitoring emission wavelength was 470 nm.



Figure S-4. Photoluminescence decay dynamics of **1a** (PPPQ) solutions in formic acid. The excitation wavelength was 350 nm and the monitoring wavelength was 498 nm.



Figure S-5. Photoluminescence decay dynamics of **1b** (BuN-PPQ) solutions in formic acid. The excitation wavelength was 350 nm and the monitoring wavelength was 470 nm.



Figure S-6. Photoluminescence decay dynamics of **1a** (PPPQ) and **1b** (BuN-PPQ) thin films on silica substrates. The excitation wavelength was 350 nm. The monitoring wavelength was 578 nm for **1a** and 454 nm for **1b**.