

AFRL-ML-WP-TP-2006-418

**HOT WORKING OF HIGH-PURITY
NICKEL-NIOBIUM ALLOYS
(PREPRINT)**

**F. Montheillet, S. Girard, Ch. Desrayaud, J. Le Coze, and S.L.
Semiatin**



APRIL 2006

Approved for public release; distribution is unlimited.

STINFO COPY

This work has been submitted to TransTech Publications Ltd. for publication in the THERMEC' 2006 International Conference on Processing and Manufacturing of Advanced Materials Proceedings. One or more of the authors is a U.S. Government employee working within the scope of their Government job; therefore, the U.S. Government is joint owner of the work. If published, TransTech Publications Ltd. may assert copyright. The Government has the right to copy, distribute, and use the work. All other rights are reserved by the copyright owner.

**MATERIALS AND MANUFACTURING DIRECTORATE
AIR FORCE RESEARCH LABORATORY
AIR FORCE MATERIEL COMMAND
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750**

NOTICE AND SIGNATURE PAGE

Using Government drawings, specifications, or other data included in this document for any purpose other than Government procurement does not in any way obligate the U.S. Government. The fact that the Government formulated or supplied the drawings, specifications, or other data does not license the holder or any other person or corporation; or convey any rights or permission to manufacture, use, or sell any patented invention that may relate to them.

This report was cleared for public release by the Air Force Research Laboratory Wright Site (AFRL/WS) Public Affairs Office and is available to the general public, including foreign nationals. Copies may be obtained from the Defense Technical Information Center (DTIC) (<http://www.dtic.mil>).

AFRL-ML-WP-TP-2006-418 HAS BEEN REVIEWED AND IS APPROVED FOR PUBLICATION IN ACCORDANCE WITH ASSIGNED DISTRIBUTION STATEMENT.

*/Signature/

LEE SEMIATIN
Senior Scientist
Processing Section
Metals Branch

//Signature//

JEFFREY R. CALCATERRA, Chief
Processing Section
Metals Branch
Metals, Ceramics and NDE Division

//Signature//

GERALD J. PETRAK, Asst Chief
Metals, Ceramics and NDE Division
Materials and Manufacturing Directorate

This report is published in the interest of scientific and technical information exchange, and its publication does not constitute the Government's approval or disapproval of its ideas or findings.

*Disseminated copies will show “//Signature//” stamped or typed above the signature blocks.

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YY) April 2006		2. REPORT TYPE Conference Paper Preprint		3. DATES COVERED (From - To) N/A	
4. TITLE AND SUBTITLE HOT WORKING OF HIGH-PURITY NICKEL-NIOBIUM ALLOYS (PREPRINT)				5a. CONTRACT NUMBER FA8655-03-M-4061	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 6.1	
6. AUTHOR(S) F. Montheillet, S. Girard, Ch. Desrayaud, and J. Le Coze (Ecole des Mines) S.L. Semiatin (AFRL/MLLM)				5d. PROJECT NUMBER N/A	
				5e. TASK NUMBER N/A	
				5f. WORK UNIT NUMBER N/A	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Ecole Nationale Supérieure des Mines Centre SMS CNRS UMR 5146 158 cours Fauriel 42023 Saint-Etienne Cedex 2, France				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Materials and Manufacturing Directorate Air Force Research Laboratory Air Force Materiel Command Wright-Patterson AFB, OH 45433-7750				10. SPONSORING/MONITORING AGENCY ACRONYM(S) AFRL-ML-WP	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S) AFRL-ML-WP-TP-2006-418	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES This work has been submitted to TransTech Publications Ltd. for publication in the THERMEC' 2006 International Conference on Processing and Manufacturing of Advanced Materials Proceedings. One or more of the authors is a U.S. Government employee working within the scope of their Government job; therefore, the U.S. Government is joint owner of the work. If published, TransTech Publications Ltd. may assert copyright. The Government has the right to copy, distribute, and use the work. All other rights are reserved by the copyright owner. This paper contains color. PAO Case Number: AFRL/WS 06-0562, 27 Feb 2006.					
14. ABSTRACT The present work deals with the influence of niobium in solid solution on the dynamic recrystallization of pure nickel. High-purity nickel and two model nickel-niobium alloys were deformed to large strains via torsion at temperatures between 800 and 1000°C. Niobium additions considerably increased the flow stress, while they lowered the strain-rate sensitivity and increased the apparent activation energy. EBSD of the steady-state microstructures revealed strong grain refinement. Substructure development was favored, whereas thermal twinning was reduced by niobium. More generally, discontinuous recrystallization kinetics were considerably decreased.					
15. SUBJECT TERMS Nickel alloys, niobium, dynamic recrystallization, torsion testing					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT: SAR	18. NUMBER OF PAGES 12	19a. NAME OF RESPONSIBLE PERSON (Monitor) S.L. Semiatin 19b. TELEPHONE NUMBER (Include Area Code) N/A
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			

Hot Working of High-Purity Nickel-Niobium Alloys

F. Montheillet^{1,a}, S. Girard^{1,b}, Ch. Desrayaud^{1,c}, S.L. Semiatin^{2,d}
and J. Le Coze^{1,e}

¹Ecole Nationale Supérieure des Mines, Centre SMS, CNRS UMR 5146, 158 cours Fauriel,
42023 Saint-Etienne Cedex 2, France

²Air Force Research Laboratory, AFRL/MLLM, Wright-Patterson Air Force Base, OH, USA

^a montheil@emse.fr, ^bsgirard@emse.fr, ^ccdesrayaud@emse.fr, ^dlee.semiatin@wpafb.af.mil,
^elecoze@emse.fr

Keywords: hot torsion, nickel, model materials, dynamic recrystallization, grain refinement

Abstract. The present work deals with the influence of niobium in solid solution on the dynamic recrystallization of pure nickel. High-purity nickel and two model nickel-niobium alloys were deformed to large strains via torsion at temperatures between 800 and 1000°C. Niobium additions considerably increased the flow stress, while they lowered the strain-rate sensitivity and increased the apparent activation energy. EBSD of the steady-state microstructures revealed strong grain refinement. Substructure development was favored, whereas thermal twinning was reduced by niobium. More generally, discontinuous recrystallization kinetics were considerably decreased.

Introduction

Dynamic recrystallization (DRX) has been much less investigated in nickel-base superalloys than in steels. This is mainly due to the fact that such alloys contain a large number of additional elements, which may act in a complex way during hot deformation. In particular, the behavior of solid-solution niobium atoms is questionable; in spite of their low bulk diffusion rate, Nb solutes are able to interact with grain boundaries and reduce considerably grain-boundary mobility. Model materials were thus used, including high purity nickel and two Ni-Nb grades, in the present work to investigate the influence of Nb solutes on DRX during large-strain torsion tests under strain rate and temperature conditions similar to those in hot forging. The rheological behavior and steady-state microstructures of the three alloys were compared and interpreted.

Preparation and Conversion of the Model Materials

High-purity nickel (Ni) and two Ni-Nb alloys, containing nominally 0.1 wt% (Ni-0.1Nb) and 1.0 wt% (Ni-1Nb) niobium, were prepared. For Ni, electrolytic-purity nickel (containing 150 ppm Fe, still present after purification) was melted by induction in a cold silver crucible under a high-purity argon-hydrogen atmosphere. For the two alloys, high-purity niobium was added to the melt [1]. The final Nb contents were 0.092 % and 0.953 %, respectively and the level of metalloids (C, S, O, N) was generally below 5 ppm. Each of the three ingots weighed ~1.2 kg and was converted by forging at 1050°C into bars of diameter 14 mm, which were then reduced to a 10-mm diameter by hot swaging. After homogenization heat treatment of 1 h at 700°C, the grain size of Ni and Ni-0.1 Nb was close to 500 μm , while it was much smaller (50-100 μm) in the Ni-1Nb grade. According to the Ni-Nb phase diagram, Nb is entirely in solid solution within the investigated hot working range.

Hot Torsion Stress-Strain Curves

Torsion was used to achieve large strains under well-controlled (radial) strain-gradient conditions up to the steady-state flow stress domain at temperatures ranging between 800 and 1000°C (≈ 0.62 - $0.74 T_m$) and three (von Mises equivalent) strain rates, viz., 0.03, 0.10, and 0.30 s^{-1} . Specimens

were all quenched immediately after straining using a room-temperature flow of argon. Stress-strain curves are shown below for pure nickel (Fig. 1a) and the two Ni-Nb alloys (Fig. 1b, c) at the intermediate strain rate of 0.1 s^{-1} . There was no evidence of deformation heating at this strain rate.




Fig. 1. Stress-strain curves obtained from hot torsion tests on (a) pure nickel, (b) Ni-0.1Nb, and (c) Ni-1Nb at various temperatures and a strain rate of 0.1 s^{-1} .

The data revealed that the overall stress level was noticeably increased by Nb in solid solution. This was described empirically by a simple power-law equation:

$$\sigma = \sigma_0 + (\sigma_1 - \sigma_0)x^p, \quad (1)$$

in which x is the Nb content (wt%), and σ_0 and σ_1 denote the flow stresses of pure nickel and Ni-1Nb, respectively. Eq. 1 holds for both the peak and steady-state stresses; the values of exponent p were quite similar whatever the temperature, with an average of 0.38.

The shape of the flow curves was also strongly affected by the addition of niobium. For pure nickel, the steady-state flow stress was attained at strains of ~ 0.5 at 1000°C to 1.0 at 800°C , strains of 1 to 3 for Ni-0.1Nb, and strains of 2 to 3.5 for Ni-1Nb. All the flow curves exhibited single-peak behavior classically associated with discontinuous dynamic recrystallization; the slight irregular oscillations observed for some of the curves for Ni and Ni-0.1Nb were ascribed to experimental artifacts linked for instance to the large initial grain sizes. The present observations for high-purity nickel are in agreement with the results of Luton and Sellars [2]. These authors observed multiple-peak flow curves only when the large strain flow stress level was less than about 41 MPa , which

corresponds to the minimum steady-state flow stress reached in the present investigation (at 1000°C). For the Ni-Nb alloys, it is not surprising that multiple-peak flow curves were not observed, because niobium in solid solution is expected to decrease grain-boundary mobility, and thus to limit the increased grain size normally associated with wavy flow curves.

Strain Rate and Temperature Dependence of the Flow Stress

The strain rate sensitivity parameter $m = \partial \ln \sigma / \partial \ln \dot{\epsilon} \big|_{T, \epsilon}$ for the three materials was observed to increase slightly with temperature between 800 and 1000°C. The dependence of m on niobium content at 900°C is displayed in Fig. 2 for the maximum stress (which may not occur at constant strain strictly speaking) and the steady-state flow stress. The m values were much smaller for Ni-0.1Nb than for Ni, but further addition of niobium up to 1 % led to a limited decrease of m .




Fig. 2. Influence of niobium content on the strain-rate sensitivities for the maximum (m_M) and steady-state (m_S) flow stresses at 900°C.

The apparent activation energies of hot deformation were measured at $\dot{\epsilon} = 0.1 \text{ s}^{-1}$ for both the peak and steady-state stresses from $\ln \sigma - 1/T$ diagrams, where T is the absolute deformation temperature. The data were perfectly fit by straight lines in all cases. Thus, following the classical analysis of the strain-rate and temperature dependence of flow stress, this means that $mQ/R = \partial \ln \sigma / \partial (1/T) \big|_{\dot{\epsilon}, \epsilon}$ was independent of temperature, where R is the gas constant. The resulting activation energies Q_M and Q_S , pertaining to the maximum and steady state flow stresses, respectively, are plotted in Fig. 3 as a function of the niobium content. For pure Ni, $Q_M \approx 200 \text{ kJ/mol}$ is significantly less than the value of 234 kJ/mol found by Luton and Sellars [2]. For the two Ni-Nb alloys, Q_M and Q_S were much larger than the activation energies of pure nickel, but the main increase was produced by the presence of 0.1 %Nb, whereas the further addition of niobium to 1 % had much less effect on the level of Q .




Fig. 3. Influence of niobium content on the apparent activation energies Q_M and Q_S at 0.1 s^{-1} determined from the peak stress and steady-state stress, respectively.


Hot Deformation Microstructures

Microstructure and local texture investigations were carried out by electron backscatter diffraction (EBSD) on torsion specimens of each of the three materials deformed under the same conditions, viz., 900°C , 0.1 s^{-1} and a strain of 5, associated with steady-state flow stress (but not necessarily steady-state microstructure and texture). In Figures 4a-c, special boundaries are indicated by different colors: low-angle boundaries (LAB) are identified by a range of gray $\rightarrow$ pink $\rightarrow$ red lines corresponding to misorientation angles increasing from 2 deg (detection limit) to 15 deg. Ordinary high-angle boundaries (HAB) are shown in black. Green lines correspond in turn to twin boundaries (TB), *i.e.*, boundaries associated with a rotation of 60 deg around a $\langle 111 \rangle$ crystallographic axis. A more quantitative description of the fractional areas associated with the various types of boundary is given by the misorientation-angle distributions (Figure 4d-f). The various microstructural parameters are summarized in Table 1.


The results in Fig. 4 and Table 1 revealed that the addition of niobium favors substructure development, as shown by the fractions of LABs which increased from ~ 0.02 for pure nickel, to 0.16 for Ni-0.1Nb, and 0.32 for Ni-1Nb. This may be due to the stabilization of dislocation walls by niobium solutes (*i.e.*, decrease of dynamic-recovery kinetics) and/or the decrease of grain-boundary mobility, because substructure is usually swept out by moving grain boundaries.

By contrast, the twin-boundary area fraction (here, by convention, boundaries with $59 < \theta < 61$ deg) was strongly reduced by niobium, decreasing from 0.50 for pure nickel, to 0.28 for Ni-0.1Nb and 0.07 for Ni-1Nb at 900°C . The value of 0.50 for Ni is characteristic of a statically fully-recrystallized, low-stacking-fault-energy metal [3], which suggests that the microstructure in Fig. 4a had undergone some post-dynamic evolution before quenching. The reduction of twinning by solutes has been observed previously in other systems such as Cu-Sn alloys [4]. It may be attributed to the decrease of grain-boundary mobility because thermal twinning during deformation is associated with grain-boundary migration [5].


Finally, the grains appeared to be randomly oriented in deformed pure nickel, as a result of discontinuous DRX. By contrast, a strong texture was apparent for Ni-0.1Nb, and became very pronounced for Ni-1Nb. The main components belonged to the $\{111\}\langle uvw \rangle$ fiber. (Here, $\{hkl\}$ denotes the shear plane perpendicular to the z-axis, and $\langle uvw \rangle$ the shear direction parallel to the θ axis). Depending on the area of investigation and the temperature, they seem to oscillate between two orientations: $A_1^*/A_2^* \{111\} \langle 11\bar{2} \rangle$, where each of the two orientations A_1^* and A_2^* is *self-symmetric* in the sense that it fulfills by itself the symmetry requirements of the torsion test, and




(a)




(d)




(b)



(e)



(c)



(f)

Fig. 4. (a, b, c) EBSD maps and (d, e, f) misorientation angle distributions in (a, d) pure Ni, (b, e) Ni-0.1Nb, and (c, f) Ni-1Nb after torsion at 900°C and 0.1 s^{-1} to a strain of 5. Arrows indicate the shear direction. Black: ordinary HABs; green: twin boundaries; grey-pink-red: LABs. Subgrain boundaries are associated with gray bars in the histograms.

Table 1. Influence of Nb content and deformation temperature on the quantitative microstructure parameters

	Ni 900°C	Ni-0.1Nb 900°C	Ni-1Nb		
			800°C	900°C	1000°C
HAB intercept [μm]	152	16	4	6	13
LAB fraction	0.02	0.16	0.33	0.32	0.32
TB fraction	0.50	0.28	0.05	0.07	0.13

$A/\bar{A}\{111\}<1\bar{1}0>$, in which A and $\bar{A}$ must coexist for symmetry (*twin-symmetric* orientation). It should be noted, however, that EBSD texture measurement on limited areas might not reflect the average textures of the specimens. It is nevertheless remarkable that the above orientations are invariant by twinning on the $\{111\}$ plane that coincides with the shear plane, which may explain their resistance to DRX.

Conclusions

- 1) Stress-strain curves suggest that hot deformation of pure nickel, Ni-0.1 %Nb, and Ni-1 %Nb is associated with discontinuous dynamic recrystallization. With respect to pure nickel, the kinetics of flow softening are decreased by niobium solutes.
- 2) The product mQ of the strain-rate sensitivity and the apparent activation energy of deformation is remarkably independent of temperature, while m slightly increases (and therefore Q decreases) with test temperature within the investigated range 800-1000°C.
- 3) The strain-rate sensitivity m is significantly reduced by the presence of niobium in solid solution, whereas Q is increased. These variations with Nb content are more rapid between 0 and 0.1Nb than with further Nb additions, thus suggesting that a saturation effect occurs.
- 4) Deformation microstructures associated with the steady-state flow stress ($\varepsilon = 5$) are considerably refined by niobium solutes. Furthermore, the addition of Nb favors substructure development while it reduces thermal twinning during deformation.
- 5) Whereas deformation texture is eliminated by DRX in pure nickel, well developed components of the $\{111\}<uvw>$ family form in the Nb-containing alloys. They are partially stable with respect to twinning and are therefore able to resist DRX.

Further investigations involving model Ni-Nb alloys with lower or higher niobium additions (and thus Ni_3Nb precipitates) will now be carried out with the aim of better understanding and controlling the hot working of Ni-base superalloys.

Acknowledgements. The present research program was supported by the Air Force Office of Scientific Research under EOARD Contract FA8655-03-M-4061 (C.H. Ward, program manager).

References

- [1] J. Le Coze, R. Tardy, A. Kobylanski and M. Biscondi: 1st Int. Conf. on Ultra High Purity Base Metals (UHPM-94), Kitakyushu-City, The Japan Institute of Metals, Sendai, Japan (1995), p. 371
- [2] M.J. Luton and C.M. Sellars: Acta Metall. Vol 17 (1969), p. 1033
- [3] L. Gavard: PhD Thesis, Ecole des Mines de Saint-Etienne/INPG (2001)
- [4] B. Bayle, Ph. Bocher, J.J. Jonas and F. Montheillet: Mater. Sci. Technol. Vol. 15 (1999), p. 803
- [5] J.-Ph. Thomas, Ch. Dumont, F. Montheillet and E. Bauchet: 10th Int. Symp. on Superalloys, Seven Springs, PA, USA (2004), p. 959