

High-Performance 1645-nm Er:YAG Laser

25 September 2007

Prepared by

Da-Wun Chen, Todd S. Rose, Steven M. Beck,
and Milton Birnbaum (Consultant)
Electronics and Photonics Laboratory
Laboratory Operations

Prepared for

SPACE AND MISSILE SYSTEMS CENTER
AIR FORCE SPACE COMMAND
483 N. Aviation Blvd.
El Segundo, CA 90245-2808

20071108159

Engineering and Technology Group

This report was submitted by The Aerospace Corporation, El Segundo, CA 90245-4691, under Contract No. FA8802-04-C-0001 with the Space and Missile Systems Center, 483 N. Aviation Blvd., El Segundo, CA 90245. It was reviewed and approved for The Aerospace Corporation by B. Jaduszliwer, Principal Director, Electronics and Photonics Laboratory; and D. C. Marvin, Principal Director, Research and Program Development Office. Michael Zambrana was the project officer for the Mission-Oriented Investigation and Experimentation (MOIE) program.

This report has been reviewed by the Public Affairs Office (PAS) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nationals.

This technical report has been reviewed and is approved for publication. Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.


Michael Zambrana
SMC/EA

REPORT DOCUMENTATION PAGEForm Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. **PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.**

1. REPORT DATE (DD-MM-YYYY)

25-09-2007

2. REPORT TYPE**3. DATES COVERED (From - To)****4. TITLE AND SUBTITLE**

High-Performance 1645-nm Er:YAG Laser

5a. CONTRACT NUMBER

FA8802-04-C-0001

5b. GRANT NUMBER**5c. PROGRAM ELEMENT NUMBER****6. AUTHOR(S)**

Da-Wun Chen, Todd S. Rose, Steven M. Beck, and Milton Birnbaum

5d. PROJECT NUMBER**5e. TASK NUMBER****5f. WORK UNIT NUMBER****7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)**The Aerospace Corporation
Laboratory Operations
El Segundo, CA 90245-4691**8. PERFORMING ORGANIZATION
REPORT NUMBER**

TR-2007(8555)-6

9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)Space and Missile Systems Center
Air Force Space Command
483 N. Aviation Blvd.
El Segundo, CA 90245**10. SPONSOR/MONITOR'S ACRONYM(S)**

SMC

**11. SPONSOR/MONITOR'S REPORT
NUMBER(S)****12. DISTRIBUTION/AVAILABILITY STATEMENT**

Approved for public release; distribution unlimited.

13. SUPPLEMENTARY NOTES**14. ABSTRACT**

The efficiency and output of the resonantly fiber-laser-pumped Er:AYG laser at 1645 nm using 0.25% doped crystal outperformed the 0.5% doped crystal. In addition to the reported decrease in efficiency because of cooperative upconversion, a significant loss of laser output during Q-switched operation was observed and identified as two-photon absorption. This is deleterious in the short-pulse, high-intensity operational regime.

15. SUBJECT TERMS

Eyesafe laser, Solid-state laser, Infrared laser, Q-switched laser

16. SECURITY CLASSIFICATION OF:**a. REPORT**

UNCLASSIFIED

b. ABSTRACT

UNCLASSIFIED

c. THIS PAGE

UNCLASSIFIED

**17. LIMITATION
OF ABSTRACT****18. NUMBER
OF PAGES**

9

**19a. NAME OF
RESPONSIBLE PERSON**

Da-Wun Chen

**19b. TELEPHONE NUMBER
(include area code)**

(310)336-7952

Contents

1. Introduction	1
2. Experimental Set-up.....	3
3. Experimental Results	5
4. Summary/Conclusion.....	7
References.....	9

Figures

1. Schematic for end-pumped Er:YAG laser experimental set-up.....	3
2. Cw output power performance of Er:YAG rods versus input power.	5
3. Cw output power performance of Er:YAG samples versus absorbed power.....	5
4. Er:YAG laser Q-switched average power versus PRF for all rods except the 0.5% 40-mm rod pumped with 8.4 W	6
5. Er:YAG laser pulse energy and pulse width versus PRF for the 25% 40-mm rod at 13 W of pump power.	6

1. Introduction

High-peak-power, high-efficiency, eye-safe lasers operating near 1.5 μm are desirable for remote sensing applications. Recently, highly efficient operation was reported for 1645-nm Er:YAG solid-state lasers resonantly pumped with 1532-nm lasers.¹⁻⁴ Resonant pumping has the advantages of small quantum defect and small thermal load for the laser materials. High-brightness erbium fiber pump lasers at 1532 nm not only provide good absorption, but also the beam quality required for mode matching using low doping and long Er:YAG crystals. In this report, we present experimental results comparing the 0.25% and the 0.5% Er:YAG laser performance in cw and Q-switch operations. The use of a lower doping concentration reduces the deleterious effects of up-conversion and provides better thermal management.¹

2. Experimental Set-up

The schematic for the end-pumped Er:YAG laser set-up is shown in Figure 1. An IPG Photonics TEM₀₀ erbium fiber laser, which provided 20 W cw power at 1532.4 nm, was used in these experiments. This laser provides a 0.2-nm (FWHM) spectral linewidth with a 5-mm-dia, linearly polarized beam. The laser beam was shaped by a positive lens L₁ and a negative lens L₂ to match the laser mode diameter of the Er:YAG laser rod. An optical isolator (OI) prevented pump light from feeding back into the fiber laser. A half-wave plate was used to minimized the 45° beam splitter (BS) reflected loss of the pump beam. A flat input coupler mirror (IC) was coated for HT at 1532 nm (T = 95%) and HR at 1645 nm (R>99.5%).

Five 5-mm-dia Er:YAG rods were investigated: three rods (30-, 40-, and 45-mm lengths) at 0.25% erbium concentration and two rods (30- and 40-mm lengths) at 0.5%. All rods were broadband AR coated for 1.5–1.65 μm (R<0.1%). The Er:YAG crystals were placed in a copper mount and water cooled at 15°C. Output coupler mirrors (OC) were selected for optimized cw and Q-switched tests. A Brewster-cut quartz Q-switch was used for the Q-switch tests. A mirror with the same coating as the IC was used as a filter F to separate the pump beam and laser beam at the resonator output for measuring the output power.




Figure 1. Schematic for end-pumped Er:YAG laser experimental set-up.

3. Experimental Results

During the initial cw laser test, a flat input-coupler mirror (IC), and an ROC = 25-cm concave R = 88% output coupler at 1645 nm was used to form a mode diameter ($1/e^2$) of $\sim 580 \mu\text{m}$ with a cavity length of 10 cm. The lenses were adjusted to produce a pump beam diameter to match the cavity mode size. Figure 2 shows the laser performance of the five Er:YAG crystals pumped by the Er fiber laser.

The AO Q-switch was not in the cavity for cw operation. Figure 2 clearly shows that 0.25%, 40-mm and 45-mm rods outperform the other three rod samples. Its highest laser power up to 8.2 W at 1645 nm was obtained at 16 W of input power with a slope efficiency as high as 62%. There was no significant difference for the 0.25% 40-mm and 45-mm rods. However, if we compare their performances with the absorbed power instead of incident power (as shown in Figure 3), the data showed that 0.25% Er rods have a slope efficiency ($>78\%$) that is better than the 0.5% Er rods ($\sim 50\%$).

For the Q-switch test, we insert the AO Q-switch into the laser cavity and increase the pump laser beam diameter to $\sim 770 \mu\text{m}$ at the Er:YAG laser crystal, as shown in Figure 1. With a cavity length of 15.5 cm, the output coupler was replaced by a 50-cm concave 90% reflectivity mirror to better match the pump mode size. With this arrangement, the power performances of all rods were reduced about 25%. However, the 0.25% 40-mm and 45-mm Er:YAG rods still perform better than the other three rods; the 0.25% 30-mm rod also clearly performs better than the 0.5% rods. The power performance of these rods has the same order at various arrangements. Figure 4 shows the Q-switched average power versus PRF for the 0.25% 30-mm, 40-mm, and 0.5%, 30-mm rods. It also shows that the 0.25% 40-mm rod has the better average power at any PRF. The data shows that the higher the average power, the faster the power falls at lower PRF. Data also shows that the average power for the 0.25% 40-mm rod at 13 W of input power falls much faster than at 8.4 W input power. Figure 5 shows laser pulse width and pulse energy versus PRF at 13 W of pump power for the 0.25% 40-mm rod. As can be seen from the figure, 34-ns, 5.8-mJ pulses were obtained at a PRF of 400 Hz, where the highest laser peak power of 171 kW was achieved. Although shorter pulses (31-ns, 3.2-mJ) were generated by using R = 85% OC




Figure 2. Cw output power performance of Er:YAG rods versus input power.




Figure 3. Cw output power performance of Er:YAG samples versus absorbed power.




Figure 4. Er:YAG laser Q-switched average power versus PRF for all rods except the 0.5% 40-mm rod pumped with 8.4 W. Data for 25% 40-mm rod at 13 W pumping is also shown for comparison.




Figure 5. Er:YAG laser pulse energy and pulse width versus PRF for the 25% 40-mm rod at 13 W of pump power.

mirror with a 0.25%, 30-mm rod at 1250 Hz, the peak power (103 kW) was not as high (before the rod's coating was damaged).

During the Q-switched laser operation, much brighter green (550 nm) fluorescent emission was observed in comparison to the cw operation. The intensity of the green light gets brighter for lower PFR (higher pulse energy and shorter pulses, i.e., higher laser peak power). We believe the additional power loss for lower PRFs shown in Figure 4 may be, in part, attributed to two-photon absorption of the intracavity laser light.

4. Summary/Conclusion

In summary, our experimental results show that 0.25% Er:YAG crystals are more efficient than the 0.5% Er:YAG crystals. The 0.25% 40-mm rod may be close to optimal performance when the laser is resonantly pumped by an erbium fiber laser. CW laser power up to 8.3 W at 1645 nm was obtained at 17 W input power with slope efficiency as high as 62%. In Q-switched mode, 34-ns, 5.8-mJ pulses were obtained at a PRF of 400 Hz, where the highest laser peak power of 171 kW was achieved. An additional power loss for Q-switched operation at the lower PRFs may be attributed to the two-photon absorption of 1645-nm intracavity laser light. Further investigation is to be pursued.

References

1. Y. Young, S. Setzler, K. Snell, P. Budni, T. Pollak, and E. Chicklis, "Efficient 1645-nm Er:YAG laser," *Opt. Lett.* **29**, 1075 (2004).
2. K. Spariosu, V. Leyva, R. Reeder, and M. Klotz, "Efficient Er:YAG laser operating at 1645 and 1617 nm," *IEEE JQE* **42**, 182-185 (2006).
3. D. Shen, J. Sahu, and W. Clarkson, "Highly efficient in-band pumped Er:YAG laser with 60 W of output at 1645 nm," *Opt. Lett.* **31**, 754 (2006).
4. S. Setzler, K. Snell, T. Pollak, P. Budni, Y. Young, and E. Chicklis, "5-W repetitively Q-switched Er:LuAG laser resonantly pumped by an erbium fiber laser," *Opt. Lett.* **28**, 1787 (2003).

LABORATORY OPERATIONS

The Aerospace Corporation functions as an "architect-engineer" for national security programs, specializing in advanced military space systems. The Corporation's Laboratory Operations supports the effective and timely development and operation of national security systems through scientific research and the application of advanced technology. Vital to the success of the Corporation is the technical staff's wide-ranging expertise and its ability to stay abreast of new technological developments and program support issues associated with rapidly evolving space systems. Contributing capabilities are provided by these individual organizations:

Electronics and Photonics Laboratory: Microelectronics, VLSI reliability, failure analysis, solid-state device physics, compound semiconductors, radiation effects, infrared and CCD detector devices, data storage and display technologies; lasers and electro-optics, solid-state laser design, micro-optics, optical communications, and fiber-optic sensors; atomic frequency standards, applied laser spectroscopy, laser chemistry, atmospheric propagation and beam control, LIDAR/LADAR remote sensing; solar cell and array testing and evaluation, battery electrochemistry, battery testing and evaluation.

Space Materials Laboratory: Evaluation and characterizations of new materials and processing techniques: metals, alloys, ceramics, polymers, thin films, and composites; development of advanced deposition processes; nondestructive evaluation, component failure analysis and reliability; structural mechanics, fracture mechanics, and stress corrosion; analysis and evaluation of materials at cryogenic and elevated temperatures; launch vehicle fluid mechanics, heat transfer and flight dynamics; aerothermodynamics; chemical and electric propulsion; environmental chemistry; combustion processes; space environment effects on materials, hardening and vulnerability assessment; contamination, thermal and structural control; lubrication and surface phenomena. Microelectromechanical systems (MEMS) for space applications; laser micromachining; laser-surface physical and chemical interactions; micropropulsion; micro- and nanosatellite mission analysis; intelligent microinstruments for monitoring space and launch system environments.

Space Science Applications Laboratory: Magnetospheric, auroral and cosmic-ray physics, wave-particle interactions, magnetospheric plasma waves; atmospheric and ionospheric physics, density and composition of the upper atmosphere, remote sensing using atmospheric radiation; solar physics, infrared astronomy, infrared signature analysis; infrared surveillance, imaging and remote sensing; multispectral and hyperspectral sensor development; data analysis and algorithm development; applications of multispectral and hyperspectral imagery to defense, civil space, commercial, and environmental missions; effects of solar activity, magnetic storms and nuclear explosions on the Earth's atmosphere, ionosphere and magnetosphere; effects of electromagnetic and particulate radiations on space systems; space instrumentation, design, fabrication and test; environmental chemistry, trace detection; atmospheric chemical reactions, atmospheric optics, light scattering, state-specific chemical reactions, and radiative signatures of missile plumes.



2350 E. El Segundo Boulevard
El Segundo, California 90245-4691
U.S.A.