Report Documentation Page					Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.						
1. REPORT DATE		2. REPORT TYPE		3. DATES COVE	RED	
24 JUN 2005		Technical		22-10-2004	4 to 24-06-2005	
4. TITLE AND SUBTITLE		1		5a. CONTRACT	NUMBER	
Ceramic Machinin	g Evaluation			5b. GRANT NUN	/BER	
				5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S)				5d. PROJECT NU 04-0001-02	JMBER	
		5e. TASK NUMBER				
		5f. WORK UNIT NUMBER				
7. PERFORMING ORGANI National Center fo Technology Way,L	DRESS(ES) uring & Machining	5,1600 8. PERFORMING ORGANIZATION REPORT NUMBER				
9. SPONSORING/MONITO	AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)			
		11. SPONSOR/MONITOR'S REPORT NUMBER(S)				
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited						
13. SUPPLEMENTARY NOTES						
 14. ABSTRACT The US Army Research, Development and Engineering Command's (RDECOM) Aviation and Missile Research Development and Engineering Center's (AMRDEC) Manufacturing Science and Technology Division (MS&T) at Redstone Arsenal, AL, is engaged in a Ceramic Manufacturing Technology Program (CMTP). The objective of this effort is to assess current and newly developed ceramic machining technologies and 2) perform initial evaluation of various machining parameters and tooling. 						
^{15. SUBJECT TERMS} Success Stories; Aviation and Missile Research Development and Engineering Center; AMRDEC; Manufacturing Science and Technology Division; Redstone Arsenal						
16. SECURITY CLASSIFIC		17. LIMITATION OF	18. NUMBER	19a. NAME OF		
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified	- ABSTRACT 1	OF PAGES	KESPONSIBLE PERSON	

Standard Form 298 (Rev. 8-98) Prescribed by ANSI Std Z39-18



Ceramic Machining Evaluation

NCDMM Project No. NQ04-0001-02 Redstone



PROBLEM / OBJECTIVE

The US Army Research, Development and Engineering Command's (RDECOM) Aviation and Missile Research Development and Engineering Center's (AMRDEC) Manufacturing Science and Technology Division (MS&T) at Redstone Arsenal, AL, is engaged in a Ceramic Manufacturing Technology Program (CMTP). The objective of this effort is to 1) assess current and newly developed ceramic machining technologies and 2) perform initial evaluation of various machining parameters and tooling.

The light weight of ceramic materials and their outstanding resistance to wear and high temperatures make them increasingly preferred for industrial applications. However, machining ceramics is very costly and time consuming. Grinding, with its high cost and low volume material removal rate (MRR), is still the most common method used to finish machine sintered (fired) ceramic components [1].

New machining methods must be evaluated in order to produce ceramic components in a more timely, cost-effective manner.

ACCOMPLISHMENTS / PAYOFF



NCDMM created a "proof-of-concept" machining test using "bisque" silicon carbide and "bisque" silicon nitride ceramic material. All tests were performed on a Fryer MC-40 CNC machining center at NCDMM.

From the research conducted at NCDMM, most of the latest machining technologies for processing ceramic components focus on machining ceramic material after it has been sintered. Grinding, ultrasonic and rotary ultrasonic machining are among the most common methods used to finish sintered ceramic material. Laser assisted machining (LAM) shows some promise and has a higher MRR, but development of this technology is still in its infancy.

Process Improvement

The accompanying table of NCDMM test results shows that machining ceramic material in the presintered "bisque" state using Polycrystalline Diamond (PCD) tools produced a higher MRR (up to 250 or 1000 times greater if compared to grinding, depending on endmill size used) than machining sintered ceramics using other methods.

Machining Ceramic Material					
Bisque (Unsintered) Machining	MRR (in3/min [mm3/min])				
1/8" PCD Endmill	0.1500 [2458]				
1/4" PCD Endmill	0.6000 [9832]				
Finish (Sintered) Machining	~				
Grinding	< 0.0006 [10]				
Ultrasonic Machining (UM)	< 0.0031 [50]				
Rot. Ultrasonic Mach (RUM)	< 0.0305 [500]				
Laser Assisted Mach (LAM)	< 0.0610 [1000]				
<u>Reference</u>	~				
Turning Hardened Steels	~ 0.3051 [5000]				

Therefore, to minimize the time and cost associated with finish machining after sintering, ceramic materials should be machined in the bisque state with PCD tooling whenever possible.

Expected Benefits

- Reduced operation time by 90% by rough machining in bisque state, when compared to grinding
- Reduced labor costs
- Increased competitiveness of ceramic components

TIME LINE / MILESTONE

Start Date	October 04
End Date	June 05

PROJECT FUNDING

NCDMM funding\$ 100K

PARTICIPANTS

Fryer Machine Systems Inc. Kennametal Inc.

 H. Toenshoff, T. Lierse and I. Inaski, "Grinding of Advanced Ceramics" <u>Machining of Ceramics and Composites</u>, ed. S. Jahanmir et al, (New York-Basel, Marcel Decker, Inc.) 85-118 (1999).

For additional information concerning this project, contact the NCDMM at www.ncdmm.org