AEROSPACE REPORT NO. TR-2010(8550)-7

MicroTribological Performance of Au-MoS₂ and Ti-MoS₂ Coatings with Varying Contact Pressure

February 15, 2011

Pantcho Stoyanov¹, Richard R. Chromik¹, David Goldbaum¹, Jeffrey R. Lince², and Xiaolig Zhang³

¹McGill University Montreal, Quebec, Canada ²Space Materials Laboratory Physical Sciences Laboratories ³Teer Coating, Ltd. Worcestershire WR9 9AS, UK

Prepared for:

Space and Missile Systems Center Air Force Space Command 483 N. Aviation Blvd. El Segundo, CA 90245-2808

Authorized by: Engineering and Technology Group

20110930009

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED



This report was submitted by The Aerospace Corporation, El Segundo, CA 90245-4691, under Contract No. FA8802-09-C-0001 with the Space and Missile Systems Center, 483 N. Aviation Blvd., El Segundo, CA 90245. It was reviewed and approved for The Aerospace Corporation by Gary F. Hawkins, Principal Director, Space Materials Laboratory; and Warren G. Goda, Principal Director, Research and Program Development Office. David E. Davis was the project officer for the Mission-Oriented Investigation and Experimentation (MOIE) program.

This report has been reviewed by the Public Affairs Office (PAS) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nationals.

This technical report has been reviewed and is approved for publication. Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.

Juis Rodrigue for Mr. Davis SMC/EN July B. 2011

David E. Davis SMC/EA

DEPORT DOOLUMENTATION DAGE					Form Approved			
KE	PORT DOCU		OMB No. 0704-0188					
Public reporting burden for this collection of information is astimated to avarage 1 hour per responsa, including the tima for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and complating and reviewing this collection of information. Send commants regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defensa, Washington Headquarters Sarvices, Directorate for Information Reports (704-0188), 1215 Jefferson Davis Highway, Suite 1204, Artington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to complet with a collection of under a purcent of user on penalty for failing to								
1. REPORT DATE	(DD-MM-YYYY) 2-2011	2. REPORT TYPE		3. DATES	COVERED (From - To)			
4. TITLE AND SUE	BTITLE			5a. CONTR	RACT NUMBER FA8802-09-C-0001			
MicroTribologic with Varying Co	al Performance of An ntact Pressure	1-MoS ₂ and Ti-MoS ₂ C	Coatings	5b. GRAN	TNUMBER			
				5c. PROG	RAM ELEMENT NUMBER			
6. AUTHOR(S)				5d. PROJE	ECT NUMBER			
Pantcho Stoyano Jeffrey R. Lince,	v, Richard R. Chrom and Xiaolig Zhang	ik, David Goldbaum,		5e. TASK	NUMBER			
				5f. WORK UNIT NUMBER				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)				8. PERFOR	RMING ORGANIZATION TNUMBER			
Physical Science El Segundo, CA	s Laboratories 90245-4691				TR-2010(8550)-7			
9. SPONSORING / Space and Missil Air Force Space	MONITORING AGENO e Systems Center Command	Y NAME(S) AND ADDR	ESS(ES)	10. SPONS	PONSOR/MONITOR'S ACRONYM(S) SMC			
483 N. Aviation El Segundo, CA	Blvd. 90245			11. SPONS NUMB	1. SPONSOR/MONITOR'S REPORT NUMBER(S)			
12. DISTRIBUTION	VAVAILABILITY STAT	EMENT						
Approved for public release; distribution unlimited.								
13. SUPPLEMENT	ARY NOTES							
14. ABSTRACT								
Solid lubricant coatings with co-sputtered metal and MoS_2 have shown favorable macrotribological properties at a wide range of contact stresses and humidity levels. These materials are also candidates for use in microcontacts and micro-electromechanical systems (MEMS), but their performance at this scale is poorly understood. For this study, microtribological properties of Au- MoS_2 and Ti- MoS_2 coatings, with varying metal additives of less than 15 at%, were examined using a nanoindentation instrument. Titanium and gold were chosen for this study as metal additives due to their different influence on the mechanical properties of the coating. The hardness and reduced modulus of the coatings increased with the addition of metal, when compared to pure MoS_2 . Reciprocating microscratch tests were performed with two spherical diamond tips (50 and 10 μ m radii) in dry air. A range of normal loads were used between 0.2 and 5.0 mN. Friction and wear measurements were analyzed with respect to the variation in the contact pressure and compared to literature studies performed at the macroscale. Correlations were found between the coating mechanical properties, tip-coating adhesion, interfacial shear strength, and the formation of transfer films and tribofilms.								
16. SECURITY CL.	ASSIFICATION OF:		OF ABSTRACT	OF PAGES	PERSON			
a. REPORT	b. ABSTRACT	c. THIS PAGE	Leave blank	13	19b. TELEPHONE NUMBER (include area code)			
UNCLASSIFIED	UNCLASSIFIED	UNCLASSIFIED			(310)336-4464			

Standard Form 298 (Rev. 8-98)

Note

Document entitled "Microtribological Performance of Au-MoS2 and Ti-MoS2 Coatings with Varying Contact Pressure," by Pantcho Stoyanov, Richard R. Chromik, David Goldbaum, Jeffrey R. Lince, and Xiaoling Zhang originally printed in *Tribol Lett* (2010) 40:199–211. © Springer Science+Business Media, LLC 2010

ORIGINAL PAPER

Microtribological Performance of Au–MoS₂ and Ti–MoS₂ Coatings with Varying Contact Pressure

Pantcho Stoyanov · Richard R. Chromik · David Goldbaum · Jeffrey R. Lince · Xiaoling Zhang

Received: 28 March 2010/Accepted: 5 July 2010/Published online: 18 July 2010 © Springer Science+Business Media, LLC 2010

Abstract Solid lubricant coatings with co-sputtered metal and MoS₂ have shown favorable macrotribological properties at a wide range of contact stresses and humidity levels. These materials are also candidates for use in miand micro-electromechanical crocontacts systems (MEMS), but their performance at this scale is poorly understood. For this study, microtribological properties of Au-MoS₂ and Ti-MoS₂ coatings, with varying metal additives of less than 15 at%, were examined using a nanoindentation instrument. Titanium and gold were chosen for this study as metal additives due to their different influence on the mechanical properties of the coating. The hardness and reduced modulus of the coatings increased with the addition of metal, when compared to pure MoS₂. Reciprocating microscratch tests were performed with two spherical diamond tips (50 and 10 µm radii) in dry air. A range of normal loads were used between 0.2 and 5.0 mN. Friction and wear measurements were analyzed with respect to the variation in the contact pressure and compared to literature studies performed at the macroscale. Correlations were found between the coating mechanical properties, tip-coating adhesion, interfacial shear strength, and the formation of transfer films and tribofilms.

P. Stoyanov · R. R. Chromik (⊠) · D. Goldbaum Department of Mining and Materials Engineering, McGill University, Montreal, QC H3A 2B2, Canada e-mail: richard.chromik@mcgill.ca

J. R. Lince

Tribology Section, Spacecraft Materials Laboratory, The Aerospace Corporation, El Segundo, CA 90245, USA

X. Zhang

Teer Coating, Ltd., West Stone House, Berry Hill Industrial Estate, Droitwich, Worcestershire WR9 9AS, UK

Keywords Solid lubrication friction · Solid lubrication mechanisms · Molybdenum disulfide · Microtribology

1 Introduction

For a little more than a decade, the testing of nano- and micro-scale sliding contacts has been an important research area that seeks to improve the tribological performance of nano/micro-devices and to have a better understanding of a material's behavior during single and multi-asperity contacts [1-17]. Due to their applications in hard drives, diamond-like carbon (DLC) coatings have been well studied for their tribological behavior at these small length scales [12-18]. More recently, interest in other materials for microtribological applications has arisen. The demonstration of atomic-layer deposition of chalcogenides [19, 20], such as WS₂, has provided the opportunity to include these materials, as solid lubricants, in micro-electromechanical system (MEMS). Additionally, there has been interest in using high-metal additions to MoS₂ [8, 10] for the possible use of these coatings in micromotors, switches or actuators.

Co-sputtered metal-MoS₂ solid lubricant coatings have shown favorable macrotribological properties at a wide range of contact stresses and humidity levels [21-31]. However, their microtribological performance is not nearly as well studied. Previous research has been performed using an atomic force microscope (AFM) [8] and a nanoindentation instrument [32, 33] to investigate the influence of the gold content on the microtribological properties of MoS₂. It has been shown that higher gold content (i.e. 84 at% Au) shows the most promise for microtribological systems due to the better performance (i.e. lower coefficient of friction and lower wear rate) in humid environments and at higher contact pressure [32]. Other recent studies [34, 35] have focused on lateral force microscopy of nanoparticles of MoS₂.

The co-sputtering of titanium with molybdenum disulfide results in similar effects on the macrotribological properties as the Au dopant. The addition of titanium increases the hardness and the wear resistance of the coating and makes it less sensitive to humid environments during tribological testing, as shown by Renevier [24]. While varying the Ti content between 3 and 11 at%, Simmonds [25] illustrated that there was a significant increase in the endurance life with the lower Ti content. No reports in the literature were found on the microtribology of these coatings.

At present, it is well known that the low friction and high-endurance life of metal-MoS₂ coatings are accomplished by the early formation of a stable and uniform transfer film (i.e. MoS₂ is transferred to the counterface) and tribofilm (i.e. a thin crystalline MoS₂ layer is formed on the worn surface), which can be directly correlated to a low interfacial shear strength. However, it still remains unclear if and how these tribological mechanisms change when decreasing the contact size to the microscale. The goal of this study was to investigate the influence of gold and titanium content on the microtribological properties of the co-sputtered molybdenum disulfide coatings developed by Lince [23] and Teer [28], and to compare the results to previous literature at the macro-scale. The friction measurements were analyzed as a function of the contact pressure and were correlated to the interfacial shear strength, the wear volume, and Raman spectroscopy of the wear track.

2 Experimental Procedure

Three coatings were studied in this work: sputtered MoS₂, co-sputtered Ti-MoS₂ (3.8 at% Ti), and co-sputtered Au-MoS₂ (11.2 at% Au). The gold and titanium concentration was measured using an energy dispersive spectrometer (EDS) on a field emission gun scanning electron microscope (Hitachi 4700-S FEG-SEM, Japan). The Au-containing and pure MoS₂ samples were produced at the Space Materials Laboratory of The Aerospace Corporation (El Segundo, CA, USA) using a custom sputter deposition system [23]. Briefly, coatings were deposited onto polished Si (100) wafers in a load-locked deposition chamber with a base pressure of 1.33×10^{-7} Pa $(1 \times 10^{-9} \text{ Torr})$. Separate Au and MoS₂ radio frequency sputtering sources were used, which were operated in unbalanced mode to increase the ion flux on the substrate surface during deposition. Argon (99.999% nominal purity) was used as the sputtering gas, and the Ar pressure in the

during chamber deposition was typically 4 Pa $(3 \times 10^{-3} \text{ Torr})$. The Au and MoS₂ sputtering power densities were 0.25 and 3.0 W/cm², respectively. The titanium content samples were produced by Teer Coatings, Ltd. (Worcestershire, UK) using a close field unbalanced magnetron sputtering ion plating (CFUBMSIP) system operated in DC mode [28]. The preliminary chamber pressure before deposition was $5-6 \times 10^{-6}$ Torr. The argonsputtering pressure was approximately 3.0×10^{-3} Torr. The distance between the target and substrates was about 150 mm. Substrates were rotated in front of each of the targets in turn in a speed of 4.0 rpm. A pulsed DC power supply provided -350 V bias on the substrates during the 15 min pre-cleaning and -30 V during deposition. A thin adhesion layer of Ti was produced first and followed by the Ti-MoS₂ coatings. The substrate temperature during the deposition process was lower than 200 °C.

The films were characterized with various methods to determine their structure, coating thickness, and roughness. Phase identification, bonding, and degree of crystallinity were examined using a inVia-Raman microscope (Renishaw, Gloucestershire, UK) with a 514.5 nm Ar + laser and X-ray diffraction (Bruker D8 Discover, Germany) in a standard Θ -2 Θ geometry and with a Co-K α X-ray source. The roughness of the coatings was measured using an atomic force microscope (AFM) (Veeco Dimension 3100, Santa Barbara, CA, USA) operated in contact mode using up to 50 µm by 50 µm scan size. The thickness of the coatings was measured from cross-sectional images obtained at high magnification using the FEG-SEM described above.

The mechanical properties of the coatings were measured with a Ubi 3 nanoindentation instrument (Hysitron, Inc. Minneapolis, MN, USA) with a 1D transducer and a diamond Berkovich tip. The hardness and reduced modulus values presented in this article are averages taken from roughly ten indentations using indentation depths of up to 56, 43, and 180 nm for the pure MoS₂, Au-MoS₂, Ti-MoS₂ coating, respectively. The same nanoindentation instrument and transducer were used for surface pull-off force measurements with a spherical diamond tip (50 μ m tip radius) and the instrument in displacement control feedback mode. The maximum displacement throughout the test was 60 nm with a hold time of 1 s. The pull-off force was measured from the retracting adhesion force on the unloading curve [36].

The shape of the two diamond tips (10 and 50 μ m radii) that were used for microtribology were characterized with an AFM (Veeco Nanoman 3100, Santa Barbara, CA, USA) operated in closed loop scanning in tapping mode. Scans were used to characterize the radius, roughness, and the area function of the spherical tips. This characterization was performed because, at smaller length scales, diamond

indenters typically deviate from the ideal spherical shape due to the difficulty of machining them [37]. Therefore, it is crucial to obtain an accurate area function (which is the cross-sectional area of the tip as a function of depth) in order to do any calculations that include the area of the tip as a variable. Over the depth range used for our tribological studies, the RMS roughness of the two tips were between 40 and 60 nm for the 10 μ m tip and 5 and 15 nm for the 50 μ m tip.

Tip area functions for both tips were produced using the AFM images and a custom-built pixel-counting algorithm created in Matlab Version 7.5.0 (The Mathworks, Natick, MA, USA). This procedure was similar to the one described by Bushby and Jennett [37]. The diamond tips were stationed vertically in a tip holder, without the ability of lateral and vertical movement. The indenter tips were scanned in the X and Y direction with scan sizes ranging from 5 to 30 µm. The scans were exported from the AFM software and converted into ASCII text files containing a 256×256 matrix. Each number in the matrix represents the height value, with the middle number in the matrix being the top of the tip. The column and row number represent the number of pixels as a function of the distance in the X and Y direction, respectively. In other words, each pixel represents a small square with the lengths being the scan size divided by 256 (i.e. the size of the matrix). Thus, using this matrix, the cross-sectional area of the tip can be calculated at any given depth, where the depth is the value in the matrix. Figure 1a and b shows the AFM images of

201

the tips and plots of the area functions obtained from our pixel-counting algorithm compared to the ideal area functions for the 50 μ m tip and the 10 μ m tip, respectively.

Microtribological testing with the spherical diamond tips was conducted using a Ubi 3 nanoindentation instrument with a 2D transducer. Sliding tests were performed under controlled ambient temperature and a relative humidity between 3.0 and 5.0%. The relative humidity was controlled by flowing compressed air, which passed through anhydrous CaSO₄ (desiccant) and into the instrument enclosure at a high-flow rate for a few minutes and then a constant low flow rate throughout the sliding experiments.

The sliding experiments were conducted with an 8 µm track length at a constant velocity of 4 µm/s. All sliding experiments were repeated at least two times, and for some conditions, the sliding tests were repeated up to four times. The normal loads used for the experiments were varied between 0.2 and 5.0 mN, which resulted in a contact pressure between 0.4 and 3.5 GPa and a contact radius between 0.2 and 1.1 µm for the different tips. The total number of sliding cycles was 800, but due to limitation by the instrument software, only 400 cycles were performed at a time, and were repeated on the same position in order to achieve a total of 800 cycles. Each sliding test consisted of three phases, (1) a pre-scan, to image the topography at a 20 μ N load, (2) an oscillating scratch, where the sample is worn under a constant load higher than 20 µN for 800 sliding cycles, and (3) a post-scan with 20 µN load to image the topography of the resulting wear trace. The

Fig. 1 Tip area function vs. depth obtained using an AFM scan for (a) the 50 μ m tip and (b) the 10 μ m tip



D Springer

experimental method is described in more detail elsewhere [32].

The results from the sliding experiments were analyzed using a custom-built analysis code written with Matlab software. The coefficient of friction was calculated from the lateral force divided by the normal force. The average friction coefficient for each cycle was calculated from 75 (± 2) data points corresponding to the central 5 µm of the track. For ex situ examination of wear, the wear track was scanned using an AFM operated in contact mode, and the wear volume was calculated from the cross-sectional area in the middle of the track multiplied by the length of the wear track.

3 Results

3.1 Coating Characterization and Properties

Table 1 shows the properties of the coatings that were tested for this study. The hardness and the reduced modulus increased with the addition of metal to MoS_2 . Also, the Ti-MoS₂ coating revealed higher reduced modulus and hardness values when compared to the Au-containing coating.

Figures 2a, b, and c shows Raman spectra for the MoS_2 , Au-MoS₂, and Ti-MoS₂ samples, respectively. For the MoS₂ coating, the scan revealed peaks which are consistent with the Raman active modes for $MoS_2(2H)$ [38-40]. A small peak at 408 cm⁻¹ was also observed with the Ti-MoS₂ sample, however, no distinct MoS_2 peaks were observed with the Au content samples for the as-prepared coating. The broad features between 250 and 500 cm⁻¹ are commonly seen in MoS_2 coatings that have a low degree of crystallinity. Results from X-ray diffraction measurements (not shown) revealed no peaks for crystalline phases in any of the coatings. Based on these two techniques, the coatings appear to be primarily amorphous, consistent with previous publications on these materials [23, 28].

3.2 Coefficient of Friction

Figure 3a, b, and c shows the average coefficient of friction versus the cycle number using a 50 μ m tip for the MoS₂, Au-MoS₂, and Ti-MoS₂ samples, respectively. While

Table 1 Coating properties of co-sputtered MoS $_2,$ Au–MoS $_2,$ and Ti–MoS $_2$

Sample	E _r (GPa)	H (GPa)	Thickness (nm)	RMS roughness (nm)
MoS ₂	29 (±5)	1.2 (±0.4)	770	4.9
Au-MoS ₂	68 (±8)	3.3 (±0.7)	330	5.2
Ti-MoS ₂	118 (±9)	5.4 (±0.3)	870	3.3



Fig. 2 Film characterization on the unworn surface using a Raman microscope for the (a) MoS_2 , (b) $Au-MoS_2$, and (c) $Ti-MoS_2$ coating. Micro Raman scans show bands which are consistent with crystalline MoS_2 for the pure MoS_2 sample, however, no MoS_2 peaks are observed with the metal content samples

three normal loads are plotted for each coating, sliding tests using normal loads in between and above the ones plotted were also performed and were used for the analysis in the discussion section. For all samples, both the run-in and steady-state coefficients of friction decrease with increasing normal load, which is typically observed for MoS_2 coatings.

A different behavior in the coefficient of friction is observed with the 10 μ m tip sliding against the MoS₂, Au-MoS₂, and Ti-MoS₂ samples (see Fig. 4a, b, and c, respectively). The coefficient of friction does not decrease as significantly with increasing the normal load. In fact, the Au-MoS₂ sample reveals a higher friction coefficient with the highest normal load (see Fig. 4b). Furthermore, the MoS₂ sample shows an increase in the coefficient of friction with increasing the cycle number at the highest normal load (see Fig. 4a). Only the Ti-MoS₂ coating shows a similar, but not as significant, trend with the 10 μ m tip (see Fig. 4c) when compared to the 50 μ m tip (see Fig. 3c).

Overall, higher coefficients of friction are observed with the MoS_2 coating compared to the coatings with Au or Ti. Figure 5a and b shows the difference in coefficient of friction between the metal containing coatings and the pure MoS_2 coating, calculated from averaging the last 100 cycles. The difference in coefficient of friction between the MoS_2 sample and the metal containing samples decreases with increasing the normal load for the 50 µm tip. However, with increasing normal load for the 10 µm tip, the differences in coefficients of friction remain relatively similar. In some instances, the comparisons made in Fig. 5 are not representative of steadystate friction. That is, the friction coefficient for the MoS_2 sample never reaches steady state with the lowest normal load for the 50 µm tip, as it continuously increases throughout the whole test (see Fig. 3a).





Fig.. 3 Average coefficient of friction vs. cycle number for the 50 μ m using a normal load of 0.2mN, 1.0mN, and 5.0mN for (a) pure MoS₂, (b) Au-MoS₂, and (c) Ti-MoS₂ [Contact Stress: 0.4–1.2 GPa]

3.3 Wear Results

Figure 6a, b, and c shows cross-sectional profiles of the wear tracks on the MoS_2 , $Au-MoS_2$, and $Ti-MoS_2$ coatings, respectively. Results are provided for both tips, each at three different loads. In most cases, there is a clear trend of increasing wear depth and volume with increasing load. However, for the largest load with the 10 μ m tip on the Au-MoS₂ coating, there are flat regions within the wear track that correspond to the Si substrate. Wear data for these instances of coating failure were not used for further

Fig. 4 Average coefficient of friction vs. cycle number for the 10 μ m using a normal load of 0.2mN, 1.0mN, and 5.0mN for (a) pure MoS₂, (b) Au-MoS₂, and (c) Ti-MoS₂ [Contact Stress: 1.2-3.5GPa]

analysis. Figure 7a and b shows the wear volume for the 50 and 10 μ m tip, respectively. The wear volume was plotted against the normal load, which varies between 0.2 and 5.0 mN. This corresponds to an initial Hertzian contact pressure between 0.4 and 1.2 GPa for the 50 μ m tip and between 1.2 and 3.5 GPa for the 10 μ m tip. For normal loads up to 1.0 mN with the 50 μ m tip, very little wear is observed with the metal containing samples. In comparison to the MoS₂ coating, a magnitude in the wear volume similar to that for the coatings with Au and Ti was observed at the lowest loads (i.e. 0.2 and 0.5 mN).

D Springer



Fig. 5 "Delta friction," comparing the friction coefficients for the metal containing to the pure MoS_2 coatings for (a) the 50 μ m Tip and (b) the 10 μ m Tip

However, with the higher normal loads/contact pressures, the wear volume for the MoS_2 sample shows a linear increase when using the 50 μ m tip, as seen in Fig. 7a.

The 10- μ m tip shows a different behavior in the wear volume, as shown in Fig. 7b. For all samples, an increase in the wear volume is observed with increasing the normal load/contact pressure. Furthermore, with the highest contact pressure, the MoS₂ sample reveals the highest wear. It should be noted that for the highest contact pressure, the wear depth on the MoS₂ coating is higher than the actual coating thickness, indicating that the tip is sliding on the substrate. However, in Fig. 6a, one can see that the substrate is not exposed in the same way as for the thinner Au-MoS₂ coating for the same sliding conditions.

3.4 Surface Characterization and Adhesion Measurements

Figure 8 shows the pull-off force measured for the three different coatings. The highest pull-off force was seen with the pure MoS_2 coating followed by the Au-MoS₂ sample. The smallest pull-off force was seen with the Ti-MoS₂ sample.



Fig. 6 Cross-sectional plots of the wear tracks, which were created using normal loads of 0.2, 1.0, and 3.0 mN and a tip radius of 10 and 50 μ m on (a) Pure MoS₂, (b) Au-MoS₂, and (c) Ti-MoS₂ coatings

Figure 9a shows the film characterization of the worn surface using a Raman microscope for 10 μ m tip using a normal load of 1.0 mN. For all the three coatings, the MoS₂ peaks observed for the worn surface are more distinct than prior to sliding (c.f. Fig. 2). Similar results were obtained for the 10 μ m tip using a normal load of 0.2 mN (see Fig. 9b). However, the peaks for the Au-MoS₂ coating remained rather indistinct for this sliding condition. For sliding with the 50 μ m tip on the Au-MoS₂ sample and



Fig. 7 Wear volume vs. normal load for the (a) 50 m tip and (b) 10 m tip



Fig. 8 Pull-off force measurements on the three different coatings

using a normal load of 5.0 mN, evidence of MoS_2 tribofilm formation was seen in as few as 20 cycles (see Fig. 9c).

4 Discussion

In comparing the performance of $Ti-MoS_2$ and $Au-MoS_2$ coatings to the pure MoS_2 coatings, it is first relevant to



Fig. 9 Film characterization of the worn surface using a Raman microscope for the (a) 10 μ m tip using a normal load of 1.0 mN, (b) 10 μ m tip using a normal load of 0.2 mN, and (c) 50 μ m tip on the Au-MoS₂ coating using a normal load of 5.0 mN after 20 cycles. Micro Raman scans show bands which are consistent with crystalline MoS₂ for all samples. Crystalline MoS₂ is also seen by as few as 20 cycles

compare to macrotribology results in the literature [25–27, 29]. In general, metal is added to MoS_2 to enhance the mechanical and tribological properties, especially in the regime of higher relative humidity. Simmonds et al. studied the tribology of both Au-MoS₂ [29] and Ti-MoS₂ [25] coatings in 50% RH with an initial contact stress of 1 GPa. For Au-MoS₂ coatings with a similar Au content to those studied here, they observed a reduction of the friction

D Springer

coefficient from 0.17 to 0.15 as compared to pure MoS₂ and an increase in the endurance. For Ti-MoS₂ coatings with a similar Ti content to those studied here, they observed a reduction of the friction coefficient from 0.18 to 0.07 as compared to pure MoS2. Zabinski et al. [26] studied Au-MoS₂ coatings with pin-on-disk tribometry with an initial contact stress of 0.98 GPa and found a reduction in the friction coefficient compared to pure MoS₂ in both dry (3-5% RH) and ambient conditions. For the coatings studied here, previous macrotribology research on Au-MoS₂ [23] and Ti-MoS₂ [24, 28] demonstrated friction reduction and increase in endurance compared to pure MoS₂. The magnitude of the friction reduction in microtribology (c.f. Fig. 5) was found to be similar to the macrotribology results. For a load of 5.0 mN on the 50 µm tip and 0.2 mN on the 10 µm tip, the initial contact stress is 1.2 GPa, similar to the stress in the macroscopic studies. The reduction in friction coefficient observed here is between 0.05 and 0.1. Despite the significant differences in %RH, this result compares favorably to those of Simmonds et al. [25, 29], who saw a reduction in friction of 0.02 for Au-MoS₂ and 0.11 for Ti-MoS₂. Zabinski et al. [26] observed a reduction in friction of 0.03 in dry conditions for Au-MoS₂ compared to pure MoS₂. Thus, a similar friction-reducing capability of metal doping of MoS₂ is also observed for microtribology. Without running longer tests, it is not clear whether the same can be said for the effect on coating endurance. However, the wear for the Ti-MoS₂ and Au-MoS₂ coating were consistently less when compared to pure MoS₂ (c.f. Fig. 7), especially at higher contact stresses.

Other observations of the microtribology experiments on MoS₂ and metal-doped MoS₂ coatings showed both additional similarities and some subtle differences to macrotribology. The steady-state friction force (i.e. 800th cycle) was plotted against the normal force in log-log plots, Fig. 10a and b for the 50 and 10 µm tip, respectively. A linear fit was conducted on the results according to $F \propto L^m$, where m is the slope of the fit in the log-log scale. The linear fit showed that the m value was 0.94, 0.89, and 0.94 when using the 10 µm tip and 0.78, 0.79, and 0.84 when using the 50 µm tip for the MoS₂, Au-MoS₂, and Ti-MoS₂, coatings, respectively. This indicates that with the 10 μ m tip, all three coatings show higher m values when compared to the 50 µm tip. Furthermore, when using the 50 µm tip, the MoS₂ coating follows the relationship of $F \propto L^{0.78}$, which is closer to $F \propto L^{2/3}$ when compared to the other two coatings and the 10 µm tip. The Hertzian behavior of $F \propto L^{2/3}$ has been previously observed in macrotribology studies of MoS₂ coatings by Singer et al. [41, 42] and by several other authors [30, 43]. The higher m values with the 10 µm tip can be explained by the difference in the tip shape, as seen in Fig. 1b. The difference



Fig. 10 Friction force vs. Normal load for (a) the 50-µm tip a nd (b) the 10-µm tip for sputtered MoS₂ sample and co-sputtered Au-MoS₂ sample and co-sputtered Ti-MoS₂ sample

between the actual area function (i.e. measured using an AFM) and the ideal area function (i.e. ideal shape of a sphere) of the 10- μ m tip is greater than the 50- μ m tip. The 10- μ m tip deviates from a spherical shape, which can cause a different F to L relationship. It has previously been shown that even small deviations from a spherical tip shape can result in increasing m values as high as one [44], as seen in our case with the 10 μ m tip.

As described in the literature [41, 43, 45, 46], the shear strength has a pressure dependence which can be approximated by

$$S = S_0 + \alpha P \tag{1}$$

where S_0 is the interfacial shear strength also called the "velocity accommodation parameter," P is the mean pressure of the contact, and α represents the limiting coefficient of friction [41]. This equation is often cast in terms of the coefficient of friction, μ , such that

$$\mu = S_{\rm o}/P + \alpha \tag{2}$$

Thus, from Eq. 2, the coefficient of friction is inversely proportional to the pressure. This behavior was also confirmed when plotting the steady-state friction coefficient (800th cycle) versus inverse pressure for the 50- μ m tip on the MoS₂, Au-MoS₂, and Ti-MoS₂ coatings (see



Fig. 11 Coefficient of friction vs. inverse pressure using the 50 μ m for (a) sputtered MoS₂ sample and (b) co-sputtered Au-MoS₂ sample and (c) co-sputtered Ti-MoS₂ sample. Linear fit was performed on each coating and the slope (S₀) and intercept (α) were obtained following the equation of $\mu = S_0/P + \alpha$. The contact pressure is calculated at the 800th cycle using the actual area function of the tip

Figs 11a, b, and c, respectively). The pressure for this plot was calculated at the steady-state condition (800th cycle) using the normal force divided by the projected area of the tip. The area was determined from the results of the pixel-counting algorithm of AFM images (see Fig. 1). The value of the tip area at the 800th cycle was calculated using the elastic depth, which was obtained from the difference in the normal displacement of the post-scan (i.e. 3rd phase of the sliding experiment) and the last sliding cycle.

Least square fit of a straight line was performed on each sample for the 50 μ m tip, shown in Fig. 11a, b, and c. Reasonable fits were not obtained for the 10 μ m tip (not shown). This may be explained by the fact that not enough data points were used, because the tip was often in contact with the substrate at the higher normal loads. Furthermore, the higher contact pressures obtained with the 10 μ m tip could also result in higher plowing, which leads to difficulty in measuring the actual contact area.

The fit with the 50- μ m tip revealed a mean slope (S_o) and an intercept (α) for each sample, and the values are summarized in Table 2. The velocity accommodation parameter, So, decreases with the addition of metal to MoS_2 . Also, the mean slope S_0 shows the lowest value (15 MPa) with the Ti content sample when compared to the other two samples (39 and 23 MPa for the MoS₂ and the Au-MoS₂ samples, respectively). The y-intercept, α , showed similar values for all three coatings (see Table 2). The lower S_0 values for the Ti and Au coating compare favorably with S_o values obtained in macrotribology, for MoS₂ coatings, at low relative humidity levels [42] where low friction values were observed. The value for the pure MoS₂ coating is slightly higher than typically observed [41]. Considering that the higher wear at the larger normal loads for the MoS₂ coating may be affecting this analysis, a fit was conducted to the three data points for the lower normal loads. This results in a shear strength of 26 MPa, but with much higher uncertainty due to the large scatter in friction data for the lowest loads on the MoS₂ coating. Thus, we believe that the pure MoS₂ did give a similar response at the lower loads to the other coating and similar shear strength to the literature on macroscopic contacts on MoS₂.

Table 2 Microtribological properties summary for testing with the 50 μ m tip

	Wear volume (µm ³) [L: 3.0/5.0mN]	S _o (MPa)	α	Friction (μ) [L: 3.0/5.0 mN]	Friction force
MoS ₂	1.1/1.9	39 (±6)	0.07(±0.01)	0.15/0.14	$F \propto L^{0.78}$
Au-MoS ₂	0.3/0.5	23.2 (±0.4)	0.061(±0.002)	0.10/0.10	F a L ^{0.79}
Ti-MoS ₂	0.1/0.2	15 (±3)	0.079(±0.006)	0.11/0.10	F & L ^{0.84}

Further examination of data in Table 2 allows for comparisons of the hardness, velocity accommodation parameter (S_o) , wear volume, coefficient of friction, and friction force relationship with normal load. In terms of the relationship between the friction force and the normal force (i.e. $F \propto L^{m}$) the pure MoS₂ sample shows the closest value to 2/3, when compared to the two other coatings. However, the m value for the metal doped samples is very similar to the m value of the pure MoS_2 sample. Also, the limiting friction is similar for all coatings, and S_o is, in all cases, low and relatively comparable to measurements at macroscopic length scales [30, 41-43]. However, the hardness was observed to increase with the addition of metal to MoS₂, and the highest hardness value was obtained with the Ti content sample followed by the Au-MoS₂ coating. This can be directly correlated with the wear volume of the three different coatings. The wear volume decreases with the addition of metal to MoS₂ and therefore decreases with increasing the hardness. As seen with the hardness values, the highest wear resistance is also observed with the Ti content sample.

While the wear resistance of a coating can sometimes simply be explained by the hardness, further analysis of the wear mechanisms was carried out using a modified version of the technique of Kuster and Schiffmann [16]. In their method, the wear contribution is separated into two components and directly correlated to the total depth during a sliding process, which consists of three contributions: elastic deformation, plastic deformation, and removed material. Kuster and Schiffmann [16] used three depth values in order to calculate each wear contribution; the depth after the initial loading $(D_{\rm IL})$, the depth under normal load after the last cycle of the test $(D_{\rm LC})$, and the residual depth after unloading measured from the end scan $(D_{\rm RD})$. Using these measurements, the following equations can be derived:

Elastic deformation
$$= D_{\rm LC} - D_{\rm RD},$$
 (3)

Removed material = $D_{\rm LC} - D_{\rm IL}$, (4)

Plastic deformation =
$$D_{\text{RD}} - [\text{Removed material}]$$

= $D_{\text{RD}} - (D_{\text{LC}} - D_{\text{IL}}).$ (5

We used a slightly modified version of this method because it was difficult to measure the wear depth from the end scan of the sliding test (due to thermal drift and material pile up at the end of the wear track). Thus, the value of $D_{\rm IL}$ was calculated using the elastic-plastic wear depth from an indentation test and the value of $D_{\rm RD}$ was calculated using the wear depth obtained with an AFM.

The different depth contributions versus the normal loads for the 50-µm tip are plotted in Fig. 12a, b, and c for the pure MoS₂, Au-MoS₂, and Ti-MoS₂ coatings, respectively. The highest plastic deformation is observed with the pure MoS₂ coating, which can be explained by the lower



Fig. 12 Depth contribution during a sliding test using the 50 μm tip for (a) pure MoS₂, (b) Au-MoS₂, and (c) Ti-MoS₂

hardness value. The Au and Ti content samples show similar contribution of plastic deformation to the wear, which is a smaller when compared to the one of the pure MoS_2 samples. However, the removed material is slightly higher with the Au content sample when compared to the Ti content sample and the highest contribution of removed material to the total depth is seen with the pure MoS_2 sample. For those loads that could be analyzed for the





Fig. 13 Depth contribution during a sliding test using the 10 μm tip for (a) pure $MoS_2,$ (b) Au-MoS_2, and (c) Ti-MoS_2

10 μ m tip, similar results were observed (see Fig. 13a, b, and c for the pure MoS₂, Au-MoS₂, and Ti-MoS₂ coatings, respectively).

The removed material can be correlated to either plowed material or adhesive wear. While some plowing must occur during our tests, our steady-state analysis for the 50- μ m tip revealed a nearly Hertzian relationship between the friction and the normal load. The small deviation from $L^{2/3}$, while

possibly attributable to tip shape, may also be due to adhesion. Thus, differences in removed material might be also due to differences in the surface adhesion. As seen in Fig. 8, the highest pull-off force was seen with the pure MoS₂ coating followed by the Au-MoS₂ sample and the smallest pull-off force was seen with the Ti-MoS₂ sample. Thus, if adhesive wear is part of the removed material, these measurements help to explain the trend in wear resistance of the coatings. The adhesion measurements are also consistent with the velocity accommodation parameter, S_{0} , which shows the same trend with decreasing interfacial shear strength from MoS₂ to Au-MoS₂ to Ti-MoS₂. It has been previously suggested that the S_{0} value represents a property of the interfacial shear strength between the transfer film (i.e. MoS₂ transferred on the tip) and the tribofilm [41] (i.e. crystalline MoS₂ on the surface of the wear track), but could also include the shear strength of each film, depending on which velocity accommodation mode is active. The decrease in surface adhesion with the decrease in the S_0 value may indicate that the metal-doped samples form a uniform and stable transfer- and tribo-film, leading to lower interfilm shear strength.

It has been previously shown with macro- and nanotribology [8, 21], that a crystalline tribofilm is formed on the worn surface of the MoS₂ film, which contributes to a low shear stress and therefore a low coefficient of friction. This typically occurs in the run-in stage, where the basal planes become oriented in a parallel direction to the sliding path and transfer occurs to the counterface. Similar behavior on the wear track may also be expected with microtribology. While the spectra presented in Fig. 9 provide significant evidence of tribofilm formation on the wear track, additional experiments with Raman spectroscopy on the counterfaces revealed no peaks for MoS2. Of course, a transfer film could be present that is either in such small quantity or such an amorphous state as to be undetectable by Raman spectroscopy. It should also be mentioned that while the evidence in Fig. 9 was the predominant observation from the Raman studies, other tests revealed no peaks that would indicate tribofilm formation. Additional surface characterization experiments will be necessary to unambiguously determine the role of transfer films in microtribology on solid lubricant coatings such as those studied here.

5 Conclusion

The microtribological properties of co-sputtered Ti and Au with MoS_2 solid lubricants were investigated, with a wide range of contact pressures. It was observed that the small addition of Ti and Au to MoS_2 improved the tribological properties in dry air; the co-sputtered Ti and Au with MoS_2 solid lubricants showed lower friction and less wear

compared to the pure MoS_2 coating. The improved tribological properties with metal additions were attributed to an increase in the mechanical properties, decrease in adhesion, and a decrease in the interfacial shear strength or 'velocity accommodation parameter'. The interfacial shear strength for the Ti and Au content samples was similar to literature values obtained at the macroscale, indicating a similar sliding behavior. This was also confirmed with the evidence of a tribofilm on the surface of the wear tracks, which was seen with Raman spectroscopy.

Acknowledgments The authors gratefully acknowledge financial support from Fonds québécois de la recherche sur la nature et les technologies (FQRNT), program Établisssement de nouveaux chercheurs and Lorne Trottier for the graduate Fellowship (McGill Engineering Doctoral Award). This study was also supported under The Aerospace Corporation's Mission Oriented Investigation and Experimentation program, funded by the U.S. Air Force Space and Missile Systems Center under Contract No. FA8802-09-C-0001. The authors acknowledge Zachary Fishman for his collaboration with the Matlab code. The assistance of Francois Barthelet in conducting atomic force microscopy measurements is also gratefully acknowledged.

References

- Bhushan, B.: In: Bhushan, B. (ed.) Handbook of Micro/Nano Tribology, pp. 797–834. CRC Press, Boca Raton, FL (1999)
- Bora, C.K., Flater, E.E., Street, M.D., Redmond, J.M., Starr, M.J., Carpick, R.W., Plesha, M.E.: Multiscale roughness and modeling of MEMS interfaces. Tribol. Lett. (USA) 19(1), 37–48 (2005)
- Delrio, F.W., De Boer, M.P., Knapp, J.A., Reedy Jr, E. D., Clews, P.J., Dunn, M.L.: The role of van der Waals forces in adhesion of micromachined surfaces. Nat. Mater. 4(8), 629–634 (2005)
- Dugger, M.T.: Surface treatments for modifying the tribological behavior of microsystems. In: Proceedings of the World Tribology Congress III - 2005, pp. 711-713. American Society of Mechanical Engineers, New York, NY (2005)
- Gee, M.G., Gee, A.D.: A cost effective test system for microtribology experiments. Wear (Netherlands) 263(7-12 SPEC. ISS), 1484-1491 (2007)
- Liu, H.W., Bhushan, B.: Adhesion and friction studies of microelectromechanical systems/nanoelectromechanical systems materials using a novel microtriboapparatus. J. Vac. Sci. Technol. A 21(4), 1528-1538 (2003)
- Nosonovsky, M., Bhushan, B.: Scale effect in dry friction during multiple-asperity contact. Trans. ASME, J. Tribol. (USA) 127(1), 37-46 (2005)
- Kim, H., Lince, J.R.: Direct visualization of sliding-induced tribofilm on Au/MoS₂ nanocomposite coatings by c-AFM. Tribol. Lett. 26(1), 61–65 (2007)
- Schiffmann, K.I.: Microtribological/mechanical testing in 0, 1 and 2 dimensions: a comparative study on different materials. Wear (Netherlands) 265(11-12), 1826-1836 (2008)
- Lince, J.R., Kim, H.I., Adams, P.M., Dickrell, D.J., Dugger, M.T.: Nanostructural, electrical, and tribological properties of composite Au-MoS₂ coatings. Thin Solid Films 517(18), 5516– 5522 (2009)
- Deladi, S., Berenschot, J. W., De Boer, M. J., Krijnen, G. J. M., Elwenspoek, M. C.: In: Proceedings of the 17th IEEE International Conference on Micro Electro Mechanical Systems (MEMS), pp. 181-184. Institute of Electrical and Electronics Engineers Inc., Maastricht, Netherlands (2004)

- Ahmed, S.I.U., Bregliozzi, G., Haefke, H.: Microfrictional properties of diamond-like carbon films sliding against silicon, sapphire and steel. Wear (Netherlands) 254(11), 1076–1083 (2003)
- Bandorf, R., Luthje, H., Staedler, T.: Influencing factors on microtribology of DLC films for MEMS and microactuators. Diam. Relat. Mater. (Netherlands) 13(4-8), 1491-1493 (2004)
- Chromik, R.R., Wahl, K.J.: Friction of microscale contacts on diamond-like carbon nanocomposite coatings. In: Proceedings of the World Tribology Congress III - 2005, pp. 829–830. American Society of Mechanical Engineers, New York, NY (2005)
- Kuster, R.L.A., Schiffmann, K.I.: Nano-scratch testing on thin diamond-like carbon coatings for microactuators: friction, wear and elastic-plastic deformation. Z. Met.kd. (Germany) 95(5), 306-310 (2004)
- Bhushan, B.: Chemical, mechanical and tribological characterization of ultra-thin and hard amorphous carbon coatings as thin as 3.5 nm: recent developments. Diam. Relat. Mater. (Netherlands) 8(11), 1985-2015 (1999)
- Bhushan, B., Liu, H.W., Hsu, S.M.: Adhesion and friction studies of silicon and hydrophobic and low friction films and investigation of scale effects. J. Tribol. Trans. ASME 126(3), 583-590 (2004)
- Scharf, T.W., Prasad, S.V., Dugger, M.T., Kotula, P.G., Goeke, R.S., Grubbs, R.K.: Growth, structure, and tribological behavior of atomic layer-deposited tungsten disulphide solid lubricant coatings with applications to MEMS. Acta Mater. (UK) 54(18), 4731–4743 (2006)
- Scharf, T.W., Prasad, S.V., Dugger, M.T., Mayer, T.M.: Atomic layer deposition of solid lubricant thin films. In: Proceedings of the World Tribology Congress III - 2005, pp. 375-376. American Society of Mechanical Engineers, New York, NY (2005)
- Dvorak, S.D., Wahl, K.J., Singer, I.L.: In situ analysis of third body contributions to sliding friction of a Pb-Mo-S coating in dry and humid air. Tribol. Lett. 28(3), 263-274 (2007)
- Wahl, K.J., Seitzman, L.E., Bolster, R.N., Singer, 1.L.: Lowfriction, high-endurance, ion-beam-deposited Pb-Mo-S coatings. Surf. Coat. Technol. 73(3), 152-159 (1995)
- Lince, J.R.: Tribology of co-sputtered nanocomposite Au/MoS₂ solid lubricant films over a wide contact stress range. Tribol. Lett. (USA) 17(3), 419–428 (2004)
- Renevier, N.M., Fox, V.C., Teer, D.G., Hampshire, J.: Performance of low friction MoS2/titanium composite coatings used in forming applications. Mater. Des. 21(4), 337-343 (2000)
- Simmonds, M.C., Savan, A., Pfluger, E., Van Swygenhoven, H.: Mechanical and tribological performance of MoS2 co-sputtered composites. Surf. Coat. Technol. (Switzerland) 126(1), 15-24 (2000)
- Zabinski, J.S., Donley, M.S., Walck, S.D., Schneider, T.R., McDevitt, N.T.: Effects of dopants on the chemistry and tribology of sputter-deposited MoS₂ films. Tribol. Trans. 38(4), 894–904 (1995)
- Spalvins, T.: Frictional and morphological properties of Au-MoS₂ films sputtered from a compact target. Thin Solid Films 118(3), 375-384 (1984)
- Wang, X., Xing, Y., Ma, S., Zhang, X., Xu, K., Teer, D.G.: Microstructure and mechanical properties of MoS₂/titanium composite coatings with different titanium content. Surf. Coat. Technol. 201(9–11 SPEC. ISS), 5290–5293 (2007)
- Simmonds, M.C., Savan, A., Pflüger, E., Van Swygenhoven, H.: Microstructure and tribological performance of MoSx/Au co-sputtered composites. J. Vac. Sci. Technol. Part A Vac. Surf. Films 19(2), 609-613 (2001)

- Grosseau-Poussard, J.L., Moine, P., Brendle, M.: Shear strength measurements of parallel MoS_x thin films. Thin Solid Films (Switzerland) 307(1-2), 163-168 (1997)
- Lansdown, A.R.: Molybdenum disulphide lubrication. Elsevier Science B.V, Amsterdam (1999)
- Stoyanov, P., Fishman, J.Z., Lince, J.R., Chromik, R.R.: Microtribological performance of MoS₂ lubricants with varying Au content. Surf. Coat. Technol. (Switzerland) 203(5-7), 761-765 (2008)
- Stoyanov, P., Lince, J.R., Chromik, R. R.: Micro-scale sliding contacts on Au and Au-MoS₂ coatings. submitted to Surf. Coat. Technol. (2010)
- Sahoo, R.R., Biswas, S.K.: Microtribology and friction-induced material transfer in layered MoS₂ nanoparticles sprayed on a steel surface. Tribol. Lett. 37(2), 313–326 (2010)
- 35. Sahoo, R.R., Math, S., Biswas, S.K.: Mechanics of deformation under traction and friction of a micrometric monolithic MoS₂ particle in comparison with those of an agglomerate of nanometric MoS₂ particles. Tribol. Lett. **37**(2), 239-249 (2010)
- Nair, R.P., Zou, M.: Surface-nano-texturing by aluminuminduced crystallization of amorphous silicon. Surf. Coat. Technol. 203(5-7), 675-679 (2008)
- Bushby, A.J., Jennett, N.M.: Determining the area function of spherical indenters for nanoindentation. In: Baker, S.P., Cook, R.F., Corcoran, S.G., Moody, N.R. (eds.) Fundamentals of Nanoindentation and Nanotribology II, vol. 649, pp. Q7.17.11–Q17.17.16. Materials Research Society, Warrendale, PA (2001)
- Shin, H., Doer, H.J., Deshpandey, C., Fuqua, P., Dunn, B., Bunshah, R.F.: Effect of niobium doping on the properties of

molybdenum sulfides as cathode materials. Surf. Coat. Technol. 36(3-4), 859-865 (1988)

- Wahl, K.J., Dunn, D.N., Singer, I.L.: Effects of ion implantation on microstructure, endurance and wear behavior of IBAD MoS₂. Wear (Netherlands) 237(1), 1-11 (2000)
- Wieting, T.J., Verble, J.L.: Infrared and Raman studies of longwavelength optical phonons in hexagonal MoS₂. Phys. Rev. B 3(12), 4286 (1971)
- Singer, I.L.: Solid lubrication processes. In: Singer, I.L., Pollock, H.M. (eds.) Fundamentals of Friction, pp. 237-261. Kluwer Academic Publishers, Dordrecht (1992)
- Singer, I.L., Bolster, R.N., Wegand, J., Fayeulle, S., Stupp, B.C.: Hertzian stress contribution to low friction behavior of thin MoS₂ coatings. Appl. Phys. Lett. 57(10), 995–997 (1990)
- Briscoe, B.J., Smith, A.C.: The interfacial shear strength of molybdenum disulfide and graphite films. Tribol. Trans. 25(3), 349-354 (1982)
- Schwarz, U.D., Zwörner, O., Köster, P., Wiesendanger, R.: Quantitative analysis of the frictional properties of solid materials at low loads. I. Carbon compounds. Phys. Rev. B 56(11), 6987 (1997)
- Bridgeman, P.W.: Shearing phenomena at high pressure particularly in inorganic compounds. In: Proceedings of the American Academy of Arts and Sciences, vol. 71, p. 387 (1936)
- Erdemir, A., Erck, R.A., Robles, J.: Relationship of hertzian contact pressure to friction behavior of self-lubricating boric acid films. Surf. Coat. Technol. 49(1-3), 435-438 (1991)

PHYSICAL SCIENCES LABORATORIES

The Aerospace Corporation functions as an "architect-engineer" for national security programs, specializing in advanced military space systems. The Corporation's Physical Sciences Laboratories support the effective and timely development and operation of national security systems through scientific research and the application of advanced technology. Vital to the success of the Corporation is the technical staff's wide-ranging expertise and its ability to stay abreast of new technological developments and program support issues associated with rapidly evolving space systems. Contributing capabilities are provided by these individual organizations:

Electronics and Photonics Laboratory: Microelectronics, VLSI reliability, failure analysis, solid-state device physics, compound semiconductors, radiation effects, infrared and CCD detector devices, data storage and display technologies; lasers and electro-optics, solid-state laser design, micro-optics, optical communications, and fiber-optic sensors; atomic frequency standards, applied laser spectroscopy, laser chemistry, atmospheric propagation and beam control, LIDAR/LADAR remote sensing; solar cell and array testing and evaluation, battery electrochemistry, battery testing and evaluation.

Space Materials Laboratory: Evaluation and characterizations of new materials and processing techniques: metals, alloys, ceramics, polymers, thin films, and composites; development of advanced deposition processes; nondestructive evaluation, component failure analysis and reliability; structural mechanics, fracture mechanies, and stress corrosion; analysis and evaluation of materials at cryogenic and elevated temperatures; launch vehicle fluid mechanics, heat transfer and flight dynamics: aerothermodynamics; chemical and electric propulsion; environmental chemistry; combustion processes; space environment effects on materials, hardening and vulnerability assessment; contamination, thermal and structural control; lubrication and surface phenomena. Microelectromechanical systems (MEMS) for space applications; laser micromachining; laser-surface physical and chemical interactions; micropropulsion; micro- and nanosatellite mission analysis; intelligent microinstruments for monitoring space and launch system environments.

Space Science Applications Laboratory: Magnetospheric, auroral and cosmic-ray physics, wave-particle interactions, magnetospheric plasma waves; atmospheric and ionospheric physics, density and composition of the upper atmosphere, remote sensing using atmospheric radiation; solar physics, infrared astronomy, infrared signature analysis; infrared surveillance, imaging and remote sensing; multispectral and hyperspectral sensor development; data analysis and algorithm development; applications of multispectral and hyperspectral imagery to defense, civil space, commercial, and environmental missions; effects of solar activity, magnetic storms and nuclear explosions on the Earth's atmosphere, ionosphere and magnetosphere; effects of electromagnetic and particulate radiations on space systems; space instrumentation, design, fabrication and test; environmental chemistry, trace detection; atmospheric chemical reactions, atmospheric optics, light scattering, state-specific chemical reactions, and radiative signatures of missile plumes.