



AFRL-OSR-VA-TR-2014-0015

Linear and nonlinear plasmonics from isotropic and anisotropic integrated nanocomposites for quantum information applications.

Jorge-Alejandro Reyes-Esqueda

UNIVERSIDAD NACIONAL AUTÓNOMA DE MÉXICO

01/09/2014
Final Report

DISTRIBUTION A: Distribution approved for public release.

**AIR FORCE RESEARCH LABORATORY
AF OFFICE OF SCIENTIFIC RESEARCH (AFOSR)/IO
ARLINGTON, VIRGINIA 22203
AIR FORCE MATERIEL COMMAND**

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) 31072913		2. REPORT TYPE Final		3. DATES COVERED (From - To) 5/1/2012 to 07/31/13	
4. TITLE AND SUBTITLE Linear and nonlinear plasmonics from isotropic and anisotropic integrated nanocomposites for quantum information applications				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER FA9550-12-1-0235	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Dr. Jorge-Alejandro Reyes-Esqueda				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Instituto de Física, Universidad Nacional Autónoma de México (UNAM). Ciudad Universitaria, México,				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) AFOSR				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION / AVAILABILITY STATEMENT DIST A					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT General objective: Showing that our integrated plasmonic nanocomposites are candidates for new ultrafast quantum information nanodevices. Particular objectives: Showing that they are (enhanced) sources of individual photons.					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (include area code)

Linear and nonlinear plasmonics from isotropic and anisotropic integrated nanocomposites for quantum information applications.

Contact information

Dr. Jorge-Alejandro Reyes-Esqueda.
Assistant Professor.
Instituto de Física, Universidad Nacional Autónoma de México (UNAM).
Ciudad Universitaria, México, D. F. 04510.
Ph. +52 55 5622 5184
Cel. +52 55 3533 3153
Fax- +52 55 5616 1535
Email- reyes@fisica.unam.mx

Objective

General objective: Showing that our integrated plasmonic nanocomposites are candidates for new ultrafast quantum information nanodevices.

Particular objectives: Showing that they are (enhanced) sources of individual photons.

Scientific Report

a) Passivation effects and enhanced hydrogen diffusion: By varying the ion (Au or Ag) and its fluence when irradiating a system of silicon nanocrystals (Si-NCs) embedded in silica at high depth inside the matrix (1-2 μm), a noticeable increase of the amount of hydrogen, or nitrogen, that diffuses into the silica matrix is achieved. As a consequence, a much better passivation of defects of the Si-NCs is obtained, allowing also a large increment of the photoluminescence quantum efficiency and of the number of Si-NCs optically active of this system.

i) Journal of Nanotechnology 2013, 736478 (2013). <http://dx.doi.org/10.1155/2013/736478>

ii) Journal of Nanotechnology, in revision.

b) PL modification by plasmonic, surface and porosity roles: Colloidal Au nanoparticles (NPs) were added to luminescent porous silicon by drop casting. These NPs interact with this system by modifying its optical properties such as photoluminescence. The mechanisms by which occurs this modification would be the porosity of the silicon matrix, the effects of the surface chemical modification and the role played by the plasmonic effects of the metallic Au NPs. Although these mechanisms compete between themselves, it is evident that controlling the porosity would be the main asset to obtain the best effects on PL from the plasmonic phenomenon and the surface chemical modification.

i) Journal of Photoluminescence, in press. <http://dx.doi.org/10.1016/j.jlumin.2013.09.053>

c) Effects of size and shape on NLO response by Au NPs in sapphire: Nonlinear optical response of Au metallic NPs, synthesized and embedded in sapphire by using ion implantation, as a function of their size and shape were studied. The size of the Au NPs was varied by controlling the annealing time of the gold-irradiated sapphire in a reducing atmosphere. Their shape was changed from approximately spherical to prolate by swift heavy-ion irradiation using Si^{3+} , obtaining an anisotropic composite consisting in deformed

NPs, all oriented in the direction of the Si beam irradiation. At 532 nm and 26 ps pulses, the isotropic system shows negative nonlinear absorption increasing with size, and size independent positive nonlinear refraction. On the other hand, prolate nanoparticles show negative (null) absorption and null (positive) refraction for the minor (major) axis. This kind of system also shows figures of merit and relaxing times in the order of the picoseconds, appropriate for all-optical switching applications.

i) Optical Material Express, in press.

It still remains to be studied the statistics of the emitted photons by these combined systems. A Hanbury-Brown interferometer is in course of validation (using typical BBO crystals). Since this is the graduation work of one of my students, the validation and the measurement of the corresponding statistics should be finished as for March of the next year.