Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE <b>1994</b>	2. REPORT TYPE			3. DATES COVERED 00-00-1994 to 00-00-1994	
4. TITLE AND SUBTITLE				5a. CONTRACT NUMBER	
Preparation of Layered Sr2CuO3+8 by Pulsed Laser Deposition: Rational Synthesis and Doping of a Metastable Copper Oxide Material				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Harvard University,Department of Chemistry and Division of Applied Sciences,Cambridge,MA,02138				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF: 17. LI				18. NUMBER	19a. NAME OF
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified	Same as Report (SAR)	OF PAGES 2	KESPONSIBLE PERSON

Standard Form 298 (Rev. 8-98) Prescribed by ANSI Std Z39-18

## Preparation of Layered Sr<sub>2</sub>CuO<sub>3+δ</sub> by Pulsed Laser Deposition: Rational Synthesis and Doping of a Metastable Copper Oxide Material

## Alfredo M. Morales, Peidong Yang, and Charles M. Lieber\*

Department of Chemistry and Division of Applied Sciences Harvard University, Cambridge, Massachusetts 02138

## Received March 31, 1994

Herein we describe the first synthesis of the layered copper oxide material  $Sr_2CuO_{3+\delta}$  carried out under low-pressure and low-temperature conditions. Reaction under these mild conditions was achieved using the pulsed laser ablation and deposition (PLD) technique.<sup>1,2</sup> Structural analyses demonstrate that  $Sr_2CuO_{3+\delta}$ prepared by PLD adopts a layered tetragonal structure with a repeat unit consisting of a  $CuO_2$  plane and two  $SrO_{\delta}$  layers. Investigations of the growth mechanism show that this layered copper oxide phase is a kinetic product in contrast to the thermodynamic one typically produced in solid state reactions. We have exploited this kinetic growth mode to prepare  $Sr_{2-x}M_xCuO_{3+\delta}$  solids that have systematic variations in oxygen and cation stoichiometry.

The synthesis of solids using nontraditional reaction conditions can often yield new and exciting materials not accessible from high-temperature reactions typical of traditional techniques.<sup>3-17</sup> In the area of copper oxide superconductivity both low-pressure/ low-temperature thin film<sup>7-12</sup> and ultrahigh-pressure/hightemperature<sup>13-17</sup> approaches have yielded new solids that cannot be prepared by conventional methods. The  $Sr_{n+1}Cu_nO_{2n+2+\delta}$ family of solids ( $n = 1 - \infty$ ) are a particularly interesting case since they represent simple models of the high- $T_c$  materials that

(1) (a) Cheung, J. T.; Sankur, H. Crit. Rev. Solid State Mater. Sci. 1988, 15, 63. (b) Olander, D. R. High Temp. Sci. 1990, 27, 411

(2) (a) Laser Ablation for Materials Synthesis; Paine, D. C., Bravman, J. C., Eds.; Materials Research Society: Pittsburgh, 1990. (b) Laser Ablation in Materials Processing: Fundamentals and Applications; Braren, R., Dubowski, J. J., Norton, D.P., Eds.; Materials Research Society: Pittsburgh, 1990.

(3) (a) Kanatzidis, M. G.; Huang, S.-P. J. Am. Chem. Soc. 1989, 111, 760.
(b) Kanatzidis, M. G.; Park, Y. J. Am. Chem. Soc. 1989, 111, 3767. (c) Kanatzidis, M. G. Chem. Mater. 1990, 2, 253. (d) McCarthy, T. J.; Kanatzidis, M. G. Chem. Mater. 1993, 5, 1061.

(4) (a) Ham, W. K.; Holland, G. F.; Stacey, A. M. J. Am. Chem. Soc. 1988, 110, 5214. (b) Marquez, L. N.; Keller, S. W.; Stacey, A. M.; Fendorf, M.; Gronsky, R. Chem. Mater. 1993, 5, 761.

(5) (a) Sunshine, S. A.; Kang, D.; Ibers, J. A. J. Am. Chem. Soc. 1987, 109, 6202. (b) Keane, P. M.; Lu, Y.-J.; Ibers, J. A. Acc. Chem. Res. 1991, 24, 223.

(6) (a) Steigerwald, M. L.; Rice, C. E. J. Am. Chem. Soc. 1988, 110, 4228. (b) Steigerwald, M.L. Chem. Mater. 1989, 1, 52. (c) Brennen, J. G.; Siegrist, T.; Stuczynski, S. M.; Steigewald, M. L. J. Am. Chem. Soc. 1990, 112, 9233. (d) Banaszak-Holl, M. M.; Kersting, M.; Pendley, B. D.; Wolczanski, P. T. Inorg, Chem. 1990, 29, 1518. (e) Banaszak-Holl, M. M.; Wolczanski, P. T.;

Inorg. Cnem. 1990, 29, 1515. (e) Banaszak-Holl, M. M.; Wolczanski, P. T.;
Van Duyne, G. D. J. Am. Chem. Soc. 1990, 112, 7989.
(7) (a) Norton, D. P.; Lowndes, D. H.; Sales, B. C.; Budai, J. D.;
Chakoumakos, B. C.; Kerchner, H. R. Phys. Rev. Lett. 1991, 66, 1537. (b)
Fincher, C. R.; Blanchet, G.B. Phys. Rev. Lett. 1991, 67, 2902.
(8) Kanai, M.; Kawai, T.; Kawai, S. Appl. Phys. Lett. 1991, 58, 771.
(9) (a) Niu, C.; Lieber, C. M. J. Am. Chem. Soc. 1992, 114, 3570. (b) Niu,
C. Lieber, C. M. J. Am. Chem. Soc. 1992, 114, 3570. (b) Niu,

- C.; Lieber, C. M. J. Am. Chem. Soc. 1993, 115, 137.
   (10) Niu, C.; Lieber, C. M. Appl. Phys. Lett. 1992, 61, 712.
   (11) Norton, D. P.; Chakoumakos, B. C.; Budai, J. D.; Lowndes, D. H.

(11) Ivorton, D. 1., Chardoninakov, D. C., Datan, J. 2., Events, P. 1993, 62, 1679.
 (12) Laquês, M.; Xie, X. M.; Tebbji, H.; Xu, X. Z.; Mairet, V.; Hatterer,
 C.; Beuran, C. F.; Deville-Cavellin, C. Science 1993, 262, 1850.
 (13) Smith, M. G.; Manthiram, A.; Zhou, J.; Goodenough, J. B.; Markert,

J. T. Nature 1991, 351, 549.

(16) Adachi, S.; Yamauchi, H.; Tanaka, S.; Môri, N. Physica C 1993, 208, 226

(17) Hiroi, Z.; Takano, M.; Azuma, M.; Takeda, Y. Nature 1993, 364, 315.

contain only  $CuO_2$  and charge compensating Sr(O) layers.<sup>18</sup> This structural simplicity comes at a price: none of these layered copper oxide materials can be prepared by traditional high-temperature syntheses. In contrast, it has been possible to prepare the n = $\infty$  member of this family, SrCuO<sub>2</sub>, using both ultrahighpressure<sup>13-15</sup> and the relatively mild low-pressure/low-temperature conditions of PLD.9-11 Recent high-pressure studies also indicate that the n = 1 material,  $Sr_2CuO_{3+\delta}$ , can be stabilized in a layered structure,<sup>17,18</sup> although its synthesis has not been investigated using other approaches.

Our studies of the growth and doping of Sr<sub>2</sub>CuO<sub>3+8</sub> materials were carried out using a laser ablation system that has been described in detail previously.9,10 Briefly, targets containing the stoichiometry of metal ions desired in the final products were ablated with a frequency-doubled pulsed Nd:YAG laser, and the ablated material was deposited onto the (100) surface of heated SrTiO<sub>3</sub> substrates.<sup>19</sup> The Sr<sub>2-x</sub>M<sub>x</sub>CuO<sub>3+ $\delta$ </sub> (M = Ca<sup>2+</sup>, Nd<sup>3+</sup>) targets used in our studies were prepared using conventional hightemperature reactions from stoichiometric mixtures of metal carbonates and oxides.<sup>20</sup> X-ray diffraction (XRD) showed that the targets contained several phases, except for x = 0 where the known orthorhombic structure with a = 12.68 Å, b = 3.91 Å, and c = 3.48 Å was obtained.<sup>21</sup>

PLD syntheses carried out at 650-680 °C using these targets produced new single-phase products whose composition and structure were determined using Rutherford backscattering spectroscopy (RBS), XRD, and electron diffraction (ED) (Figure 1). The composition of the  $Sr_2CuO_{3+\delta}$  materials determined by RBS was the same  $(\pm 5\%)$  as the starting stoichiometry of the targets even when the targets contained multiple phases. The Sr:Cu stoichiometry of the film shown in Figure 1,  $(1.97 \pm 0.07)$ :  $(1.10 \pm 0.05)$ , is the same within experimental error as that of the target. More importantly, XRD and ED demonstrate that the materials obtained by PLD have the same structure as that proposed for the layered, n = 1 phase Sr<sub>2</sub>CuO<sub>3+ $\delta$ </sub>. The XRD peaks in Figure 1b can be indexed as the (00l), l = 2, 4, 6, 8, 10lines of the n = 1 phase. The *c*-axis length determined from this data is 12.88 Å. The observation of only (00*l*) peaks in  $\theta$ -2 $\theta$ XRD scans shows that the c-axis of  $Sr_2CuO_{3+\delta}$  is oriented perpendicular to the (100) SrTiO<sub>3</sub> substrate surface. This orientation effect is likely due to lattice matching of  $SrTiO_3$  (a = 3.905 Å) and Sr<sub>2</sub>CuO<sub>3+ $\delta$ </sub> (a = 3.76 Å). The structure of our materials was further characterized using transmission ED measurements made along the [001] zone axis. The ED patterns exhibit a square symmetry with a = 3.8 Å. The ED data are consistent with the tetragonal structure expected for the layered n = 1 phase, but are inconsistent with the orthorhombic structure of the starting material.<sup>22</sup> The XRD and ED results thus confirm that the materials prepared by PLD have the layered n = 1structure.

To rationalize the excellent synthetic control afforded by PLD, we have previously speculated that growth is kinetically con-

© 1994 American Chemical Society

<sup>(14) (</sup>a) Takano, M.; Takeda, Y.; Okada, H.; Miyamoto, M.; Kuraka, T. Physica C 1989, 159, 375. (b) Takano, M.; Azuma, M.; Hiroi, Z.; Bando, Y.; Takeda, Y. Physica C 1991, 176, 441

<sup>(15)</sup> Azuma, M.; Hiroi, Z.; Takano, M.; Bando, Y.; Takedo, Y. Nature 1992. 356, 775

<sup>(18)</sup> Radaelli, P. G.; Jorgensen, J. D. Nature 1993, 364, 286.

<sup>(19)</sup> Ablation was carried out using power densities of 1-2 J/cm<sup>2</sup> and a pulse repetition rate of 10 Hz. The target-substrate distance used in these experiments was 4 cm, although distances between 4 and 6 cm gave similar results. The O2 or N2O partial pressure and substrate temperature were varied as described in the text.

<sup>(20)</sup> Sr<sub>2</sub>CuO<sub>3</sub> targets were prepared from stoichiometric amounts of SrCO<sub>3</sub> (99.99% Johnson Matthey) and CuO (99.99% Johnson Matthey) that were ground and heated at 1000 °C for 48 h, reground, and heated at 1000 °C for an additional 48 h. The resulting polycrystalline material was ground into a pellet and sintered for 24 h at 1000 °C. Cation-substituted targets,  $Sr_{2-x}M_xCuO_x$  (M = Ca<sup>2+</sup>, Nd<sup>3+</sup>), were prepared in a similar manner using stoichiometric amounts of CaCO<sub>3</sub> or Nd<sub>2</sub>O<sub>3</sub>.

<sup>(21)</sup> Lobo, R. C.; Berry, P. J.; Greaves, C. J. Solid State Chem. 1990, 88, 513.

<sup>(22)</sup> If the XRD data was assigned to the (h00) peaks of the orthorhombic phase, the ED would yield a rectangular cell with b = 3.91 and c = 3.48 Å. Because our data show clearly a square structure, we can rule out this alternative explanation.



Figure 1. (a) RBS data obtained on a  $Sr_2CuO_{3+\delta}$  material grown in 210 mTorr of N<sub>2</sub>O at 665 °C on a (100) SrTiO<sub>3</sub> substrate. The fit (smooth solid line) to the experimental data corresponds to Sr = 1.97 and Cu = 1.10. The RBS data analysis was carried out using the program RUMP from the Department of Materials Science and Engineering, Cornell University. (b) XRD diffraction pattern recorded on a sample grown in 300 mTorr of O<sub>2</sub> at 680 °C. The SrTiO<sub>3</sub> substrate (h00) peaks are denoted with asterisks (\*).

trolled.<sup>9</sup> To test this idea we have grown amorphous films of  $Sr_2CuO_{3+\delta}$  at 400 °C and subsequently annealed them at temperatures up to 680 °C. Since the amorphous films contain Sr + Cu mixed in a 2:1 ratio on the atomic scale, this experiment allows us to determine, in the absence of diffusion constraints, the structure of the thermodynamic crystalline phase. We find that heating the amorphous films to 680 °C (a growth temperature that yields n = 1 phase by PLD) in either 200 mTorr of O<sub>2</sub> or 1 atm of air produces the orthorhombic phase. Furthermore, annealing crystalline n = 1 materials at  $\geq$ 700 °C leads to a conversion of the layered phase to the orthorhombic one. Hence, we conclude that the layered  $Sr_2CuO_{3+\delta}$  phase obtained by PLD is a kinetic product, while the thermodynamic product at our reaction temperatures is the orthorhombic phase.



Figure 2. Dependence of the c-axis on the  $O_2(\bullet)$  and  $N_2O(O)$  pressure used during film growth.

We have exploited the ability to grow phase pure materials under kinetic control to study doping in this system. Samples of the n = 1 layered phase were grown at 680 °C in O<sub>2</sub> and N<sub>2</sub>O pressures ranging from 95 to 350 mTorr to investigate oxygen doping. XRD and ED analyses show that these solids correspond to the pure n = 1 layered phase, and that the *c*-axis lattice parameter decreases as the pressure of oxidizing gas is increased (Figure 2).<sup>23</sup> We attribute the decrease in c-axis to a systematic increase in copper oxidation state as observed for other copper oxide materials.<sup>24,25</sup> The synthesis of cation-doped solids of the form  $Sr_{2-x}M_xCuO_{3+\delta}$  (M = Ca<sup>2+</sup>, Nd<sup>3+</sup>) has also been explored by PLD. Preliminary studies show that phase pure n = 1 layered materials are obtained at growth temperatures between 650 and 680 °C for x(M) = 0-0.15.<sup>26</sup> In comparison, high-pressure studies have found that  $Ca^{2+}$  destabilizes the n = 1 phase relative to the n = 2 phase, and to our knowledge Nd<sup>3+</sup> has not been successfully incorporated into this structure by other methods. Taken together, we believe that our studies illustrate clearly that PLD is powerful synthetic approach for solid state chemistry since it provides, through kinetic control, the ability to systematically explore the chemistry of a solid while maintaining a predictable structure.

Acknowledgment. We thank Z. J. Zhang, J. Chervinsky, and Y. Lu for helpful discussion. A.M.M. thanks the NSF for support through a predoctoral fellowship. C.M.L. acknowledges partial support of this work by the Office of Naval Research (N00014-94-1-0302).

<sup>(23)</sup> The c-axis contraction is linear in  $P(O_2)$  up to ca. 200 mTorr and saturates at higher pressure. This saturation indicates that oxygen doping does not increase above 200 mTorr in  $O_2$ . However, the c-axis continues to contract up to a pressure of 400 mTorr when the stronger oxidant N<sub>2</sub>O ( $E^{\circ}(N_2O) = 1.77$  V vs  $E^{\circ}(O_2) = 1.23$  V) is used during growth.

<sup>(24)</sup> Whangbo, M.-H.; Èvain, M.; Beno, M. A.; Geiser, U.; Williams, J. M. Inorg. Chem. 1988, 27, 467.

<sup>(25)</sup> Interestingly, resistivity anomalies suggestive of superconductivity are observed in samples prepared at the higher  $O_2/N_2O$  pressures. We believe that the nature of these anomalies warrants further investigation.

<sup>(26)</sup> Impurity phases are observed under these growth conditions when targets containing more than x = 0.15 are employed. It should be possible, however, to extend the range through variations in the growth conditions.