UNCLASSIFIED

AD NUMBER ADB014090 LIMITATION CHANGES TO: Approved for public release; distribution is unlimited. FROM: Distribution authorized to U.S. Gov't. agencies only; Test and Evaluation; OCT 1976. Other requests shall be referred to Army Edgewood Arsenal, Attn: SAREA-TS-R, Aberdeen Proving Ground, MD 21010. **AUTHORITY** ea, d/a ltr, 25 aug 1977

THIS REPORT HAS BEEN DELIMITED

AND CLEARED FOR PUBLIC RELEASE

UNDER DOD DIRECTIVE 5200.20 AND

NO RESTRICTIONS ARE IMPOSED UPON

ITS USE AND DISCLOSURE.

DISTRIBUTION STATEMENT A

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED.





EDGEWOOD ARSENAL CONTRACTOR REPORT EM-CR-76104

EXPLOSIVE CLASSIFICATION TESTING

OF

EXPERIMENTAL COLORED SMOKE COMPOSITIONS AND END ITEMS

By

F. L. McIntyre G. L. McKown

October 1976

DE FILE COF

NASA NAT**I**ONAL SPACE TECHNOLOGY LABORATORIES

GENERAL ELECTRIC COMPANY

Engineering and Science Services Laboratory

Bay Saint Louis, Mississippi 39520

Contract NAS8-27750 /





DEPARTMENT OF THE ARMY
Headquarters, Edgewood Arsenal

Aberdeen Proving Ground, Maryland 21010



Distribution limited to US Government agencies only because of test and evaluation; August 1976. Other requests for this document must be referred to Commander, Edgewood Arsenal, Attn: SAREA-TS-R, Aberdeen Proving Ground, Maryland 21010.

<u>Disclaime</u>r

- 1

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Disposition

Destroy this report when no longer needed. Do not return to originator.

	UNCLASSIFIED	
	SECURITY CLASSIFICATION OF THIS PAGE (When Date Entered)	
	(19) REPORT DOCUMENTATION PAGE	READ INSTRUCTIONS BEFORE COMPLETING FORM
(19)	A DEPORT NUMBER	S. RECIPIENT'S CATALOG NUMBER
10	EM CR-76104 Thinal tept. Ja	N-Jul 161
1	A. TITLE (and Subside)	Final Report; Jan 1976 -
1611	EXPLOSIVE CLASSIFICATION TESTING OF	July 1976
9	EXPERIMENTAL COLORED SMOKE COMPOSITIONS	THE PERFORMING ORG. REPORT NUMBER
	AND END ITEMS	EA-2400
	7. AUTHOR(a)	S. CONTRACT OR GRANT NUMBER(s)
(3)	The Art - To have a	MIPR 8166104601 F4W5
(10)	F. L. McIntyre G. L. McKown	NAS8-27750
CL	A CONTROLL ATION NAME AND ADDRESS	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
	NASA National Space Technology Laboratories	
	Bay St. Louis, MS 39520	PEMA 4932 Project 5761313
	11. CONTROLLING OFFICE NAME AND ADDRESS	October 176 12320
	Commander, Edgewood Arsenal	TS. NUMBER OF PAGES
	Attn: SAREA-TS-R Aberdeen Proving Ground, MD 21010	
	14. MONITORING AGENCY NAME & ADDRESS(If different from Controlling Office)	15. SECURITY CLASS. (of thie report)
	Commander, Edgewood Arsenal	UNCLASSIFIED
	Attn: SAREA-MT-TS	150. DECLASSIFICATION/DOWNGRADING
	Aberdeen Proving Ground, MD 21010 (CPO-Richard Belmonte, 671-3402)	SCHEDULE N A
	16. DISTRIBUTION STATEMENT (of thie Report)	
	Distribution limited to U.S. Government agencies only	because of test and evaluation
	August 1976. Other requests for this document must	be referred to Commander,
10	Edgewood Arsenal, Attn: SAREA-TS-R, Aberdeen Pr	oving Ground, Maryland 21010.
	17. DISTRIBUTION STATEMENT (of the ebetrect ratered in Block 20, if different from	m Report)
15	1 DO FH) 1212, AMA-	419137
(16)	1) DH-010T OT OV HILL	77500
0		
	18. SUPPLEMENTARY NOTES	
	None	
	19. KEY WORDS (Continue on reverse side it necessary and identify by block number	
	Colored smoke Detonation test Card ga	
	Colored Billone	and unconfirmed burning
• •	MILO BILLIANDE	sensitivity
	TB 700-2 testing Thermal stability Impact s	
	20 ABSTRACT (Continue on reverse elde if necessary and identify by block number	
	Bulk material and end item hazard classification test	s have been performed on four
	experimental M18 colored smoke formulations made	rom coarse ingredients. Com-
	pared to standard mixes, the new red, yellow, green	and violet smoke compositions
	yielded essentially identical test results for thermal tests but indicated greatly enhanced sensitivity towar	stability, card gap and burning
	tests but indicated greatly enhanced sensitivity towar	d impact. Deconation and excer-
	tests but mutcated grown statements	am the amanimental metanicle
	nal heat tests on packaged grenade end items made fr	com the experimental materials
	nal heat tests on packaged grenade end items made fr gave no evidence of interround propagation, explosion	com the experimental materials
	nal heat tests on packaged grenade end items made fr gave no evidence of interround propagation, explosion	com the experimental materials
	nal heat tests on packaged grenade end items made fr gave no evidence of interround propagation, explosion	n or fragment dispersal.

PREFACE

The work described in this report was authorized under US Army PEMA 4932, Project 5761313 and Technical Work Request EA-2400. It was performed at the NASA National Space Technology Laboratories (NSTL) for the Edgewood Arsenal Resident Laboratory (EARL) and NASA-NSTL by the General Electric Company under Contract NAS8-27750. This work was initiated in April 1976 and completed May 1976.

Reproduction of this document in whole or in part is prohibited except with permission of Commander, Edgewood Arsenal, Attn: SAREA-TS-R, Aberdeen Proving Ground, Maryland; however, DDC is authorized to reproduce the document for United States Government purposes.

The use of trade names in this report does not constitute an official endoresement or approval of the use of such commercial hardware or software. This report may not be cited for purposes of advertisement.

The information in this document has not been cleared for release to the general public.



TABLE OF CONTENTS

PARAGRAPH	NO. TITLE	PAGE
1.0	INTRODUCTION	5
1.1	Objective	5
1.2	Authority	5
1.3	Background	5
2.0	EXPERIMENTAL PROCEDURES	6
2.1	Bulk Compositions	6
2.2	End Item Munitions	7
3.0	RESULTS	8
3.1	Bulk Compositions	8
3. 2	End Item Munitions	11
4.0	DISCUSSION	12
5.0	REFERENCES	12
	APPENDIX A - DATA SHEETS - BULK COMPOSITIONS	13
	APPENDIX B - DATA SHEETS - END ITEM MUNITIONS	17
	APPENDIX C - SELECTED PHOTOGRAPHS	25
	DISTRIBUTION LIST	33
	LIST OF TABLES	
TABLE NO.	TITLE	PAGE
1	Ingredient Ratios for Standard and Experimental Grenade Formulations	6
2	Detonation Test Summary	8
3	Ignition and Unconfined Burning Test Summary	9
4	Thermal Stability Test Summary	9
5	Impact Sensitivity Test Summary	10
6	Card Gap Test Summary	10
7	Detonation Test A Summary	11
8	External Heat Test C Summary	11

EXPLOSIVE CLASSIFICATION TESTING OF EXPERIMENTAL COLORED SMOKE COMPOSITIONS AND END ITEMS

1.0 INTRODUCTION

- 1.1 Objective. The objective of this study was to provide results of classification testing, in accordance with US Army TB 700-2, Change 1, on the following Project 5751249 experimental bulk materials and end-item munitions:
 - Violet smoke mix
 - Yellow smoke mix
 - Red smoke mix
 - Green smoke mix
 - AN-M18 violet smoke grenade
 - AN-M18 red smoke grenade
 - AN-M18 yellow smoke grenade
 - AN-M18 green smoke grenade
- 1.2 <u>Authority</u>. The work described in this report was authorized by MIPR 8166104601 F4W5 and by Technical Work Request EA-2400.
- 1.3 <u>Background.</u> The Manufacturing Technology Directorate of Edgewood Arsenal is currently involved via MMT Project 5751249 in increasing the producibility and lowering the cost of standard M18 colored smoke grenades. To aid in processing of materials through automated blending and filling equipment, experimental colored smoke formulations that use coarse ingredients and are regranulated after compaction have been devised. These formulations also differ from the composition of standard M18 mixes in that the oxidizer/fuel ratios have been increased as shown in table 1 in order to obtain the required burn characteristics.

Extensive hazard classification testing has been performed for standard colored smoke bulk formulations (1, 2) and end item munitions (3) under former Project 57x4099. However, the variations noted above in composition and material characteristics of the experimental mixtures require a reassessment of sensitivity and output energy parameters. Based on these test results, assignment of hazard classification and compatibility indices for manufacturing, transportation and storage of the bulk materials and end item munitions may then be accomplished.

Table 1. Ingredient Ratios for Standard and Experimental Grenade Formulations

	Weight rat	io, KC10 ₃ /Sulfur	Weight ratio	o, KC1O ₂ /NaHCO
Smoke color	Standa rd	Experimental	Standard	Experimental
Red	2.98	3.33	1.04	1.30
Yellow	2.35	2. 82	0.61	0.80
Green	2.60	3.33	1.19	1.50
Violet	2.78	3.00	1.04	1.17

2.0 EXPERIMENTAL PROCEDURES

- 2.1 Bulk Compositions. Classification of a bulk pyrotechnic composition is currently accomplished by evaluation of test data obtained in accordance with Chapter 3, US Army TB 700-2. These tests are designed to determine the ease of initiation and the stability of a bulk pyrotechnic composition prior to shipping and handling. The following specific tests were accomplished:
 - (a) Detonation Test. A series of tests were performed to measure the sensitivity of the compositions to the reaction of a Number 8 blasting cap. A 5-cm (2-inch) cube sample was placed on top of a perpendicular 3.8 cm (1.5-inch) diameter by 10.2-cm (4-inch) long lead cylinder. The Number 8 blasting cap was placed perpendicular to and in contact with the top surface of the sample. A 5 cm (2-inch) wood cylinder with a hole drilled through its center was utilized to position and support the blasting cap. The cap was initiated by a suitable electrical current. Detonation of the sample was evidenced by the deformation (mushrooming) of the lead cylinder. This test was conducted a minimum of five times, or until detonation was evidenced, whichever was less. Observations were made to determine whether the sample exploded, burned, and/or fragmented.
 - (b) Ignition and Unconfined-Burning Test. These tests were conducted on single and multiple (four) 5-cm (2-inch) cube samples. The samples were placed on a bed of kerosene-soaked sawdust which was ignited with an electrically initiated match head igniter. This test was conducted a minimum of two times. The ignition and unconfined-burning-test data includes a report of occurrence of detonation or burning times of samples.
 - (c) Thermal Stability Test. 5.0-cm (2-inch) cube samples were subjected to elevated temperatures to permit the observance of characteristic tendencies to detonate, ignite, decompose or change in configuration under adverse storage conditions. The samples were placed in an explosion-proof oven in which the temperature was 75°C (167°F) and maintained at this temperature for a period of 48 hours. Oven temperature was continuously recorded throughout the test period. Observations

recorded were whether the test specimen exploded, ignited, and/or underwent a change in configuration such as weight loss or color change.

- (d) Impact Sensitivity Test. A series of twenty tests were performed to determine the sensitivity of the pyrotechnic compositions to mechanical shock (impact). These tests utilized the Bureau of Explosives impact test apparatus. A 10-mg sample was placed in the test cup, the test weight was dropped from a predetermined height to strike the sample. The results of the 20 tests per sample, 10 at 9.5-cm (3.75-inch) drop height and 10 at 25.4-cm (10-inch) drop height, were reported as the number of trials exhibiting (1) Explosion, (2) Decomposition, and (3) No Reaction.
- (e) Card Gap Test. The sample materials were placed in a 14-cm (5.5-inch) long cold-drawn seamless steel tube, composition 1015, having an OD of 4.76-cm (1.875-inches) and a wall thickness of 0.56-cm (0.219-inch). The assembly was placed on a 15-cm x 15-cm x 1-cm steel witness plate in such a manner as to have a 1.6-mm air gap between the tube and the witness plate. Two pentolite pellets (5-cm diameter x 2.5-cm high) were placed directly on top of the assembly and in contact with the sample material; i.e., without the intervention of any acetate cards between the sample and pellets. (Acetate cards are used only when evidence of a detonation occurs on the first test trial.) A J-2 Engineer's special blasting cap was positioned on top of the pentolite and the complete Card Gap test assembly was supported approximately 15-cm above the ground surface. The J-2 Engineer's special blasting cap was then initiated, causing detonation of the two pentolite pellets. This test was conducted three times per sample. Observations were recorded regarding whether detonation occurred and the required number of cards for 50 percent detonability (50 percent value).
- 2.2 End Item Munitions. Evaluation of pyrotechnic end item munitions is currently accomplished by the test data obtained in accordance with Chapter 4 of US Army TB 700-2. The end item munitions are tested to determine their tendency to propagate from one shipping or packing case to another, and to evaluate the reaction resulting from burning the munitions in an intense fire. The following specific tests were conducted:
 - (a) Detonation Test A. This test is conducted on items which are packaged with more than one item in the standard storage and shipping container to determine if functioning of one item will cause other items in the container to function. The most centrally positioned item within the package was primed by its own fuse. The results of the test determine occurrence of propagation within a single container, fragmentation, blast, and fire hazards. The test was conducted a minimum of five times or until communication to adjacent items occurred. Evidence of propagation between donor and acceptor rounds, blast overpressure, and fragmentation dispersal from container rupture were recorded.
 - (b) Detonation Test B. This test is conducted, in the event of positive indications from the A test series, to determine if functioning of items in one container will cause functioning of items in adjacent containers. Since the A tests resulted in no communication within the container and the container was not ruptured, these tests were omitted.

(c) External Heat Test C (Open Flame). This test is designed to simulate a condition wherein the containers of the explosive or pyrotechnic items are completely enveloped in a hot fire. Four containers of the end items were arranged in a compact stack, approximating a cube. The containers were then secured with steel bands in two directions to maintain stacking until initiation of one or more items occurred without significantly affecting dispersal of fragments. The stack of containers was placed on a wooden crib, the interior of which was filled with scrap lumber. The crib and stack of items to be tested were covered with additional combustible material sufficient to sustain a hot fire. The entire mass was then saturated with approximately 50 gallons of diesel fuel and ignited in two locations by electric squibs and two ounces of smokeless powder. Still photographs were taken before and after the test. Resulting fragments and missiles were identified and their location with respect to the test position was recorded.

3.0 RESULTS

3.1 Bulk Compositions (See Data Sheets in Appendix A)

(a) <u>Detonation Tests.</u> None of the pyrotechnic compositions exhibited characteristics of an explosion or produced fragmentation. Test results are summarized in table 2.

Table 2. Detonation Test Summary

Sample	Test	Material weight		Test resul	ts
designation	number	in grams	Exploded	Burned	Fragmented
	1	134.7	No	No	No
Violet Smoke	2	134.7	No	No	No
Mix	3	134.7	No	No	No
Project 5751249	4	134.7	No	No	No
	5	134.7	No	No	No
	1	129.5	No	No	No
Red Smoke Mix	2	129.5	No	No	No
Project 5751249	3	129.5	No	No	No
	4	129.5	No	No	No
	5	129.5	No	No	No
	1	140.5	No	No	No
Yellow Smoke	2	140.5	No	No	No
Mix	3	140.5	No	No	No
Project 5751249	4	140.5	No	No	No
	5	140.5	No	No	No
	1	141.8	No	No	No
Green Smoke	2	141.8	No	No	No
Mix	3	141.8	No	No	Ν̈́ο
Project 5751249	4	141.8	No	No	No
	5	141.8	No	No	No

(b) Ignition and Unconfined Burning Tests. None of the pyrotechnic compositions tested exhibited characteristics of an explosion. Test results are summarized in table 3.

Table 3. Ignition and Unconfined Burning Test Summary

			Test	Results
Sample designation	Material weight in grams	Test configuration	Exploded	Avg. burn time in seconds
Violet Smoke Mix Project 5751249	134.7 134.7 538.6	Single cube Single cube Multiple cube	No No No	48 40 67
Red Smoke Mix Project 5751249	129.5 129.5 518	Single cube Single cube Multiple cube	No No No	64 65 82
Yellow Smoke Mix Project 5751249	140.5 140.5 562	Single cube Single cube Multiple cube	No No No	38 37 56
Green Smoke Mix Project 5751249	141.8 141.8 567.2	Single cube Single cube Multiple cube	No No No	73 81 89

(c) Thermal Stability Tests. None of the pyrotechnic compositions exhibited characteristics of an explosion, ignited, or any significant change in configuration in any observable fashion. Test results are shown in table 4.

Table 4. Thermal Stability Test Summary

			Test result	s	
Sample designation	Sample weight in grams	Explosion	Ignition	Change in configuration	
Violet Smoke Mix Project 5751249	134.7	No	No	None	
Red Smoke Mix Project 5751249	129.5	. No	No	None	
Yellow Smoke Mix Project 5751249	140.5	No	No	None	
Green Smoke Mix Project 5751249	141.8	No	No	None	

(d) Impact Sensitivity Tests. All four pyrotechnic mixes exhibited characteristics of an explosion and/or decomposition in a significant number of trials at both specified drop heights. The test results are given in table 5.

Table 5. Impact Sensitivity Test Summary

			Test results *					
Sample	Weight in milligrams	9.5	9.5 cm (3.75")			25.4 cm (10")		
designation		E			E	D	N	
Violet Smoke Mix Project 5751249	10	3	3	4	4	6	0	
Red Smoke Mix Project 5751249	10	3	3	4	6	3	1	
Yellow Smoke Mix Project 5751249	10	3	5	2	9	1	0	
Green Smoke Mix Project 5751249	10	5	2	3	10	0	0	

*E = Explosion

D = Decomposition

N = No Apparent Reaction

(e) Card Gap Tests. None of the pyrotechnic compositions exhibited characteristics of mass detonation and zero card values were obtained. Test results are shown in table 6.

Table 6. Card Gap Test Summary

Sample	Test	Sample weight	Те	st results
designation	number	in grams	Detonation	50% Card value
Violet Smoke Mix	1	143	No	0
Project 5751249	2	137	No	0
Project 3/31243	3	138	No	0
Red Smoke Mix	1	140	No	0
Project 5751249	2	137	No	0
	3	141	No	0
Yellow Smoke Mix	1	137	No	0
Project 5751249	2	136	No	0
Project 5751249	3	132	No	0
Green Smoke Mix	1	150	No	0
Project 5751249	2	149	No	0
Project 9191249	3	149	No	0

- 3.2 End Item Munitions (See Data Sheets and Photographs in Appendixes B and C)
 - (a) Detonation Test A. The AN-M18 smoke grenades filled with the experimental coarse pyrotechnic mixtures did not exhibit characteristics of detonation or fragment dispersal. In none of the tests on the four colors (red, yellow, green or violet) was propagation observed from the donor round to adjacent acceptor rounds within the packing container, and no damage occurred to the exterior of the original shipping container. Results are summarized in table 7.

Table 7. Detonation Test A Summary

	Test results			
Sample designation	Propagation	Blast overpressure psig		
M-18 Green Test Grenade Project 5751249	None	0		
M-18 Violet Test Grenade Project 5751249	None	0		
M-18 Yellow Test Grenade Project 5751249	None	0		
M-18 Red Test Grenade Project 5751249	None	0		

(b) External Heat Test C. None of the four experimental colored smoke grenades exhibited characteristics of a mass detonation. There was no measurable blast overpressure nor fragments, and dispersal of the functioned grenades was limited to the immediate test area. The resultant reactions were not significantly different from those reported previously for standard M18 colored smoke grenades (3). Results are summarized in table 8.

Table 8. External Heat Test C Summary

	Test results					
Sample designation	Test duration minutes	Detonation	Blast overpressure psig	Remarks		
M18 Green Test Grenade Project 5751249	89	None	0	All consumed No fragments		
M18 Violet Test Grenade Project 5751249	58 ⁻	None	0	All consumed No fragments		
M18 Yellow Test Grenade Project 5751249	50	None	0	All consumed No fragments		
M18 Red Test Grenade Project 5751249	74	None	0	All consumed No fragments		

4.0 DISCUSSION

Except for increased sensitivity of the bulk materials toward impact, the four experimental compositions generally behaved similarly to standard M18 grenade smoke formulations during all TB 200-2 testing. However, two examples of unusual behavior were observed and are reported here for the information of the developing agency.

- (1) Visual observations of smoke production during tests on bulk mix and end items of the green formulation indicated poor performance in that grey to black smoke was produced during a significant fraction of the total burn time. The red, violet and yellow mixes did not exhibit this anomaly and appeared to produce acceptable smoke clouds.
- (2) Following completion of all tests, five cases of excess grenades of each color were disposed by normal functioning. During this disposal, two yellow and two red grenades exploded with perceptible audible reports following initiation of the fuse trains. One of these yellow grenades was ejected with high velocity from the disposal pit into which it had been thrown. The cause of this abnormal behavior is unknown, but it is possibly due to higher than normal quantities of first fire mix, introduced during pilot scale production of these experimental munitions, rather than to characteristics of the smoke compositions.

5.0 REFERENCES

- 1. Schmidt, R. E., Dabul, A., and McIntyre, F. L. Edgewood Arsenal Contractor Report EM-CR-75017, General Electric Co., Miss. Compilation and Preliminary Analysis of Sensitivity Data for Pyrotechnics. May 1975.
- 2. McIntyre, F. L. Edgewood Arsenal Contractor Report EM-CR-75001, General Electric Co., Miss. Identification and Evaluation of Hazards Associated with Blending of Violet Smoke Mix by the Jet Airmix Process. March 1975.
- 3. Koger, D. M. and King, P. V. General Electric (Miss.) Contractor Report GE-MTSD-R-035. Pyrotechnic Hazards Classification and Evaluation Program, Phase I, Final Report. May 1970.

APPENDIX A

DATA SHEETS - BULK COMPOSITIONS

Da t	e 5/24/76
Sponsoring Agency Edgewood Arsenal, Edge	ewood, Maryland
Contract No. NAS8-27750	
Propellant Identity (Type No.) Project 57512	49 M18 Colored Smoke Bulk Mix (Violet)
Propellant Spec.	Batch EA 3-76
Mfg Date 3-76	
Detonation Test Exploded	
No. 8 Blasting Cap Test I Yes No	<u> </u>
Test II X Test III X Test IV X Test V X	<u> </u>
Test IV X	<u>x</u> <u>x</u>
Test V x	$\frac{x}{x}$ $\frac{x}{x}$
Samples: Five 5 cm (2-inch) cubes Tes	st: One blasting cap per sample.
-0	oloded Average Burning Time No Seconds
One 5 cm (2-inch) cubes	x 48
One 5 cm (2-inch) cubes	<u>x</u> <u>40</u>
Four 5 cm (2-inch) cubes	<u>x</u> <u>67</u>
Samples: Six 5 cm (2-inch) cubes	st: Ignite & burn unconfined.
Thermal Stability Test Explo Test: 48 hrs at 75°C in vented oven. Yes One 5 cm (2") cube Samples: One 5 cm (2") cube	No Yes No Yes No
o to my outside No detending 50'	(No. of Carde) NA
Card Gap Test 3 trials, No detonation 50	% value (No. 01 Cards)
Impact Sensitivity Test	reau of Explosives Impact Apparatus
9.5 cm (3.75") Drop Test	25.4 cm (10.0") Drop Test 10 Trials
No. of Trails Exhibiting	No. of Trials Exhibiting
Explosion Decomposition No Reaction Flame and Smoke No Smoke Noise 3 No Noise 4	Explosion Decomposition No Reaction Flame and Smoke No Smoke Noise 4 No Noise 6 No Noise 0
Anarous	
Approved: Test Director 72m. Interno Te	st Department Head
Assigned Classification	DOD Approval
	ignature
	itle
ICC Class B	rganization

^{*}Shipping instructions are to be requested from ICC (para 3-13A (2).

	Date5/24/76			
Sponsoring Agency Edgewood Arsenal,	Edgewood, Maryland			
Contract No. NAS8-27750				
Propellant Identity (Type No.) Project 5	751249 M18 Colored Smoke Bulk Mix (Yellow)			
Propellant Spec.	Batch <u>EA 3-76</u>			
Mfg Date 3-76				
Detonation Test Explode	ad Burnal B			
Yes	No You No			
No. 8 Blasting Cap Test I	X X			
Test II	$\frac{x}{x} = \frac{x}{x}$			
Test III	X			
Test IV	<u>x</u> _ <u>x</u> _ <u>x</u>			
Test V	$\frac{x}{x} = \frac{x}{x}$			
Samples: Five 2-inch cubes	Test: One blasting cap per sample.			
Innition (Unreafined D				
	Exploded Average Burning Time			
One 2-inch cube	des No Seconds			
One 2-inch cube	<u>x</u>			
	<u> 37</u>			
Four 2-inch cubes	<u></u>			
Samples: Six 2-inch cubes	Test: Ignite & burn unconfined.			
One 2-inch cube Samples: One 2-inch cube	Plosion Ignition Change in Configuration No Yes No Yes No X X X Weight Change: None			
Card Gap Test				
Card Gap Test 3 trials	50% Value (No. of Cards)			
Impact Sensitivity Test				
	Bureau of Explosives Impact Apparatus			
9.5 cm (3.75") Drop Tes	t 25.4 cm (10.0") Drop Test 10 Trials			
No. of Trails Exhibiting	No. of Trials Exhibiting			
Explosion Decomposition No Reaction Flame and Smoke No Smoke Noise 3 No Noise 5 No Noise 2	Explosion Decomposition No Reaction Flame and Smoke No Smoke Noise 9 No Noise 1 No Noise 0			
Approved: Test Director 7 / /// Fity	Test Department Head			
Assigned Classification	DOD Approval			
	Prover			
ICC Forbidden Signature				
ICC Restricted*				
ICC Class A	Title			
ICC Class B				
	Organization			

^{*}Shipping instructions are to be requested from ICC (para 3-13A (2).

	Da	te	4/76	
Sponsoring AgencyEdgewood Arsena	d, Edge	wood, Maryl	and	
Contract No. NAS8-27750				
Propellant Identity (Type No.) Proj	ect 5751	249 M18 Col	ored Smoke Bul	k Mix (Red)
Propellant Spec.		Batch EA	376	
Mfg Date 3-76				
	ploded		_	
No. 8 Blasting Cap Test I Test II	No X X		<u>x</u>	No X X
Test III Test IV	- X X		<u> </u>	_ <u>X</u>
Test V	×		<u> </u>	_ <u>x</u> _x
Samples: Five 2-inch cubes	Te	st: One bla	sting cap per s	ample.
Ignition & Unconfined Burning Test	Ex Yes	-	Average B Sec	urning Time
One 2-inch cube		<u>x</u>		64
One 2-inch cube		_X_	····	65
Four 2-inch cubes Samples: Six 2-inch cubes	Te	st: Ignite	& burn unconfin	82 led.
Thermal Stability Test Test: 48 hrs at 75°C in vented oven. One 2-inch cube Samples: One 2-inch cube	. Yes	No Yes	No Yes	No x
Samples: One 2-inch cube	don so	Weight	Change: None	Condo) NA
Card Gap Test 3 trials, No detonat				Cards) IVA
Impact Sensitivity Test	Bu	reau oi Exp	losives Impact	Apparatus
9.5 cm (3.75") Dro	op Test	25.4 cm (1	0.0") 10 Tri	Drop Test
No. of Trails Exhibiting		No.	of Trials Exhi	biting
Explosion Decomposition No React No Isame and No Noise 3 No Noise 3	•	Explosion Flame and Noise 6	Decomposition Smoke No Noise 3	No Reaction No Smoke No Noise 1
Approved: Test Director 7 Kin Daty	Te	st Departme	nt Head	
Assigned Classification			DOD Approva!	
ICC Forbidden ICC Restricted*	S	ignature		
ICC Class A	T	itle		
200 01435 2	C	rganization		

^{*}Shipping instructions are to be requested from ICC (para 3-13A (2).

		Dat	e <u>5/24/7</u>	6	
Sponsoring A	Agency Edgewo	ood Arsenal, Edge			
Contract No.	NAS8-277 5)			
Propellant :	Identity (Type N	lo.) Project 57512	249 M18 Col	ored Smoke Bulk (Green)
Propellant S	Spec.		Batch <u>EA</u>	3-76	
Mfg Date	3-76				
Detonation 1	Test	Exploded Yes No	_		ted No
	ing Cap Test I Test II Test III Test IV Test V ve 2 -i nch cubes	<u>x</u> _x		X	x x x x x ple.
	Unconfined Burni	ing Test Ex	ploded	Average Bur	=
Samples: Si Thermal Sta	cube ch cubes x 2-inch cubes bility Test	Te:	st: Ignite		
One 2-inch		nted oven. Yes	<u>x</u>	No Yes X Change: None	No X
Card Gap Te	st 3 trials			(No. of Ca	rds)
Impact Sens	itivity Test	Bu	reau of Exp	losives Impact Ap	paratus
9.5 cr	n (3.75")	Drop Test Trials	25.4 c	m (10.0") 10 Trial	Drop Test s
No.	of Trails Exhi	oiting	No.	of Trials Exhibi	ting
Explosion Flame and Noise 5	Decomposition Smoke No Noise 2	No Reaction No Smoke No Noise 3	Explosion Flame and Noise 10	Smoke	No Reaction No Smoke No Noise
Approved: Test Dire	ctor <u>7211.</u>	Auty) Te	st Departme	nt Head	
Assis	med Classificat	ion		DOD Approval	
ICC Forbid ICC Restri ICC Class ICC Class	cted*	т	itle		
			g		

^{*}Shipping instructions are to be requested from ICC (para 3-13A (2).

APPENDIX B END ITEM MUNITIONS

Test Type TB 700-2 Standard End I	TB 700-2 Standard End Item Detonation Test A						
Sponsoring Agent Edgewood Arsenal, Edge	ewood, Marylar	ıd	Tes Num	Test 18-6-01A ₁ -A5 Number (5 each)			
Contract Number NAS8-27750		Designation	Project 5751249 AN-M18 Test Grenade (Green)				
Specification		Drawing Number					
Lot Number EA 3-76	11.	Manufacture Date	3-76				
	METEOROLO	OGICAL DATA					
Temperature 17.2°C	Humidity (61% RH	Barometric Pressure	101. 3 kPa			
Wind Direction (CW from north 30°)	Wind Velocit	4.12 m/sec				
	TEST S	SET UP					
Priming Atlas Matchhead Igniter		Location of Acceptor	Center mos	t grenade			
Booster 1 gm UTC 3001 Propella	nt	Confinement	None				
	TEST I	RESULTS					
Detonation Test A (5 total)	Detonati	ion Test B	Externa	l Heat Test "C"			
Propagation	Props	gation	E	cplosion			
YesNo_X	Yes	No.	Yes	No			
Attachments Map No Blast Press. No	Attachments	Photo Map Blast Press.	Attachments	Photo Map Blast Prass.			
Test Conductor	Project Engineer	1/1/2 Interes	Test Dept. Head				

Assigned Classification

ICC Forbidden	
	Signature
ICC Restricted *	
ICC Class A	Title
ICC Class B	

Organization

Cest Conductor		Project Engineer		Test Dept. Head			
Attachments	Photo Yes No Blast Press. No	Attachments	Photo Map Blast Press.	Attachments	Photo Map Blast Press.		
Yes	No X		No-	Yes	No		
	agation	Prop	agation	Ex	plosion		
Detonat (5 to	ion Test A tal)	De t on a t	ion Test B	Externa	Heat Test "C"		
		T EST	RESULTS				
Booster 1 gm	UTC 3001 Propel	lant	Confinement	None			
Priming Atlas	s Matchhead Ignite	r	Location of Acceptor	Center most	grenade		
		TEST	SET UP				
Wind Direct	ion (CW from nor 32°	th)	Wind Velocit	Wind Velocity 4.1 m/sec			
Temperature 21.7		Humidity	44% RH	Barometric 4% RH Pressure 101.2 kPa			
		METEOROI	LOGICAL DATA				
Lot Number EA	Lot Number EA 3/76 Manufacture Date 3-76						
Specificati	on		Drawing Number				
Contract Number NAS			Designation	Designation Project 5751249 AN-M18 Test Grenades (Yellow)			
	gent Edgewood Arsenal, Edgewood, Maryland						
Test Type TB	Dat	e 4/26/76					

A	2	i	on	ed	C.1	ass	4 4	Fi	~ 3	+ 4	
		-		cu	U I	a 53			(4	1 1	On

ICC Forbidden	
ICC Restricted	*
ICC Class A	
ICC Class B	

Signature

Title

	TB 700-2 Standard End Item Detonation Test A					
Sponsoring Agent Edgewood Arsenal,	Edgewood, Maryla	nd	Tes Nur	st 18-6-04A ₁ -A5 nber (5 each)		
Contract Number NAS8-27750		Designation Project 5751849 AN-M18 Test Grenade (Violet)				
Specification		Drawing Number				
Lot Number EA 3-76		Manufacture Date 3-76				
	METEOROLO	OGICAL DATA	Attinovis de la casa d			
Temperature 27.2°C	Humidity	54% RH	Barometric Pressure	101.6 kPa		
Wind Direction (CW from 1 150°	north)	Wind Velocity	5.14 m/sec			
	TEST S	SET UP				
Priming Atlas Matchhead Igni	iter	Location of Acceptor	Center most g	renade		
Booster 1 gm UTC 3001 Prop	ellant	Confinement	None			
	TEST F	ESULTS				
Detonation Test A (5 total)	Detonati	on Test B	Externa	1 Heat Test "C"		
Propagation	Propa	gation	E	xplosion		
Yes No X	Yes	No	Yes	No		
	O Attachments	Photo Map Blast Press	Attachment	Photo s Map Blast Press		
Test Conductor	Project , Engineer /Z	midity	Test Dept. Head			

ICC Forbidden	Cianatura
ICC Restricted *	Signature
ICC Class A	Title
ICC Class B	11616

Test Type TB 70	0-2 Standard End It	Date	4/28/76				
Sponsoring Agent Edgew	vood Arsenal, Edge	wood, Maryland	i	Test Numbe	18-6-05A ₁ -A5		
Contract Number NAS8-	-27750			Project 5751249 Grenades (Red)	ect 5751249 AN-M18 Test ades (Red)		
Specification	1						
Lot Number EA 3	3-76		Manufacture Date 3	-76			
		METEOROLO	GICAL DATA				
Temperature 25.6°	c	Humidity 589	% RH	Barometric Pressure 1	01.6 kPa		
Wind Direction	on (CW from nort 50°	h)	Wind Velocity	3.60 m/sec	11 - 11 - 11 - 11 - 11 - 11 - 11 - 11		
		TEST S	ET UP				
Priming Atlas	Matchhead Igniter		Location of Acceptor	Center most	grenade		
Booster 1 gm	UTC 3001 Propellar	nt	Confinement	None			
		TEST F	ESULTS				
Detonat (5 tot	Detonation Test A Detonation (5 total)			External Heat Test "C"			
Prop	Propagation Propaga			ation Explosion			
Yes_	No X	Yes	No	Yes	No		
Attachments	Photo Yes Map No Blast Press. No	Attachments	Photo	Attachments	Photo Map Blast Press		
Test Conductor		Project Engineer 77	Mi Diteri	Test Dept. Head			

ICC Forbidden	Signature
ICC Restricted *	5.5
ICC Class A	Title
ICC Class B	

est Type Standa	est Type Standard TB 700-2 External Heat Test C						
ponsoring Agent Edgew	ood Arsenal, Edg	ewood, Maryland		Test Number	21-6-03		
Contract Number NAS-2	27750		Designation	AN-M18 Green Project 5751249	M18 Green Smoke Grenade ect 5751249		
Specification			Drawing Number				
Lot Number EA	A 3-76		Manufacture Date 3-76				
		METEOROLOG	GICAL DATA				
Temperature	c	Humidity 36%	RH	Barometric Pressure 1	01. 3 kPa		
Wind Directio	on (CW from n 150°	orth)	Wind Velocity	3.60 m/sec			
	,	TEST S	ET UP				
	iters (55 gal) dies tric Match Igniter		Location of Acceptor	4 boxes of color banded inside p			
Booster 2 gm	UTC 3001 Propell	ant	Confinement None				
		TEST R	ESULTS				
Detonat	ion Test A	Detonati	on Test B	External Heat Test "			
Prop	agation	Propa	gation	Ext	losion		
Yes			No	Yes	No_X		
Attachments	Photo Map Blast Press.	Attachments	Photo Map Blast Press	Attachments	Photo 2 Map No Blast Press. No		
Test Conductor	K 250 M	Project Engineer	Mant.	Test Dept. Head			

ICC Forbidden		
ICC Restricted	*	
ICC Class A		
ICC Class B		

Signature Title

Test Type Standa	t Type Standard TB 700-2 External Heat Test C			Date	5/19/76
Sponsoring Agent Edgew				Test Numbe	er 21-6-04
Contract Number NAS8-	Number NASS-27750		N-M18 Yellow roject 5751249	N-M18 Yellow Smoke Grenades	
Specification N/A	1		Drawing Number N/A		
Lot Number EA	3-76		Manufacture Date 3-76		
		METEOROLO	OGICAL DATA		
Temperature 23.9°C	mperature Humidity 23.9°C 33% RH		Barometric Pressure 101.3 kPa		
Wind Direction	On (CW from nor	rth)	Wind Velocity 3.60 m/sec		
		TEST S	SET UP		
•	liters (55 gal) dies etric Match Igniter		Location of 4 boxes of colored smoke grenades banded inside pyre		
Booster 2 gm	n UTC 3001 Propel	lant	Confinement None		
		TEST F	RESULTS		
Detonati	ion Test A	Detonation Test B External Heat		Heat Test "C"	
Propa	agation	Propagation		Explosion	
Yes_	No	Yes	No	Yes	No X
Attachments	Photo Map Blast Press.	Attachments	Photo	Attachments	Photo <u>Yes</u> Map <u>No</u> Blast Press None
Test Conductor		Project Engineer	illi Duti	Test Dept. Head	

ICC Forbidden	
ICC Restricted *	
ICC Class A	•
ICC Class B	

Signature Title

est Type Standard TB 700-2 External Heat Test C			Date 4	/30/76		
Sponsoring Agent Edgewood Arsenal, Edgewood, Maryland			Test Number	r 18-6-07		
Contract Number NAS8-	Contract Designation Designati			AN-M18 Violet Smoke Grenade Project 5751249		
Specification N/A	1		Drawing Number N/A			
Lot Number EA 3-	Manufacture		3-76	6		
		met eorolo	GICAL DATA			
Temperature 23.3°	С	Humidity	Humidity Barometri 90% RH Pressure		404 0 1 73	
Wind Direction	on (CW from nort	ch)	Wind Velocity 6.2 m/sec		2	
	,	TEST S	ET UP			
	liters (55 gal) Die h Electric Match I		Location of Acceptor	4 boxes of Gre Inside Pyre	nades Banded	
Booster 2 gr	m UTC 3001 Prope	llant	Confinement None			
		TEST F	RESULTS			
Detonat	ion Test A	Detonation Test B External He		Heat Test "C"		
Prop	agation	Propagation		Exp	losion	
Yes		Yes No		Yes	No_X	
Attachments	Photo Map Blast Press.	Attachments	Photo Map Blast Press.	Attachments	Photo Yes Map No Blast Press. None	
Test Conductor		Project Engineer	i. M. July	Test Dept. Head		

ICC Forbidden		
ICC Restricted	*	4
ICC Class A	·	4
ICC Class B		

Signature Title

Organization

Test Type Stan	Standard TB 700-2 External Heat Test C			Date	4/30/76	
Sponsoring Agent			Test Numb	er 18-6-06		
Contract Number NAS8-27750		Designation AN-M18 Red Smoke Grenades Project 5751249				
Specification N/A	Specification N/A		Drawing Number N/A			
Lot Number EA S			Manufacture Date 3-76			
		METEOROLOG	ICAL DATA			
Temperature 26.1			% RH	Barometric RH Pressure 100.9 kPa		
Wind Direct:	ion (CW from nor 170°	th)	Wind Velocity	6.17 m/sec		
		TEST SE	T UP			
Priming 208	liters (55 gal) Dies tric Match Igniters	sel Fuel w/2 each	Location of Acceptor	4 boxes of G Inside Pyre	renades Banded	
Booster 2 gm	2 gm UTC 3001 Propellant		Confinement	· None		
		TEST RE	SULTS			
Detonat	ion Test A	Detonatio	Detonation Test B		External Heat Test "C"	
Prop	agation	Propagation		Explosion		
Yes	No	Yes	No-	Yes	No X	
Attachments	Photo Map Blast Press.	Attachments M	hoto ap last Press	Attachments	Photo Yes Map No Blast Press None	
Test Conductor	1.10]000		The Interior	Test Dept. Head		

ICC Forbidden	
ICC Restricted *	
ICC Class A	
ICC Class B	

Signature Title

Organization

APPENDIX C

SELECTED PHOTOGRAPHS



Figure 1. Typical Pretest Configuration, Detonation Test A.



Figure 2. Typical Posttest Configuration, Detonation Test A.



Figure 3. Typical Test Results, Green Smoke Grenades.



Figure 4. Typical Test Result, Violet Smoke Grenades.



Figure 5. Typical Test Result, Yellow Smoke Grenades.



Figure 6. Typical Test Result, Red Smoke Grenades.



Figure 7. Crib for External Heat Test C.




Figure 8. Typical Funeral Pyre for C Tests.




Figure 9. Typical Test Setup for C Tests.



Figure 10. Test Result for Green Smoke Grenades.



Figure 11. Test Result for Red Smoke Grenades.



Figure 12. Test Result for Yellow Smoke Grenades.



Figure 13. Test Result for Violet Smoke Grenades.

DISTRIBUTION LIST

ADDRESSEES	NO. OF COPIES		
Garage March Palmana d August			
Commander, Edgewood Arsenal			
Attn: SAREA-TS-L	3		
Attn: SAREA-TS-R	1		
Aberdeen Proving Ground, MD 21010			
Administrator			
Defense Documentation Center			
Attn: Accessions Division	2		
Cameron Station			
Alexandria, VA 22314			
Commander, U.S. Army Armament Command			
Attn: DRSAR-RDT	1		
Rock Island, IL 61201			
Commander, Edgewood Arsenal			
Attn: SAREA-MT-C	10		
Attn: SAREA-MT-TL	3		
Attn: SAREA-SA	2		
Aberdeen Proving Ground, MD 21010			
Commander, Edgewood Arsenal			
Attn: SAREA-MT-TR	10		
NSTL, Bay St. Louis, MS 39520			