Serial No.: <u>09/886,039</u>

Filing Date: 22 June 2001

Inventor: <u>Arthur W. Snow</u>

NOTICE

The above identified patent application is available for licensing. Requests for information should be addressed to:

> ASSOCIATE COUNSEL (PATENTS) CODE 1008.2 NAVAL RESEARCH LABORATORY WASHINGTON DC 20375

20010821 061

DISTRIBUTION STATEMENT A Approved for Public Release Distribution Unlimited PATENT APPLICATION/TECHNICAL DIGEST PUBLICATION RELEASE REQUEST

FROM: Associate Counsel (Patents) (1008.2) **TO:** Associate Counsel (Patents) (1008.2)

- Via: (1) Arthur Snow (Code 6120)
 (2) Division Superintendent (Code 6100)
 (3) Head, Classification Management & Control (Code 1221)
- REF: (a) NRL Instruction 5510.40C (b) Chapter 6, ONRINST 5870.1C

ENCL: (1) Copy of patent Application/Technical Digest

1. In accordance with the provision of references (a) and (b), it is hereby requested that the subject Patent Application/Technical Digest be released for publication.

2. It is intended to offer this Patent Application/Technical Digest to the National Technical Information Service, for publication.

3. This request is in connection with Navy Case No. 82,650

HN J. KARASEK

Associate Counsel (Patents)

FIRST ENDORSEMENT

Date:

FROM: Robert A. McGill (Code 6120) **TO:** Division Superintendent (Code 6100)

1. It is the opinion of the Inventor(s) that the subject Patent Application/Technical Digest (is) (is not) classified and there is no objection to public release.

Inventor's Signature

NDW-NRL 551/3001 (Rev. 6-89) (Page 1 of 2)

SECOND ENDORSEMENT

Date:

FROM: Division Superintendent (Code 6100) **TO:** Classification Management & Control (Code 1221)

1. Release of Patent Application/Technical Digest (is) (is not) approved.

2. To the best knowledge of this Division, the subject matter of this Patent Application/Technical Digest (has) (has not) been classified.

3. This recommendation takes into account military security, sponsor requirements and other administration considerations and there in no objection to public release.

Superintendent

THIRD ENDORSEMENT

Date:

FROM: Head, Classification & Control (Code 1221) **TO:** Associate Counsel (Patents) (1008.2)

1. This Patent Application/Technical Digest is authorized for public release.

ana Kmalluove

Head, Classification, Management & Control

1	
2	PHTHALOCYANINES WITH PERIPHERAL SILOXANE SUBSTITUTION
3	
4	Background of the Invention
5	1. Field of the Invention
6	The present invention relates to new compounds that are a combination of covalently linked
7	phthalocyanine and linear siloxane polymeric structures having a unique and novel combination of
8	optical and rheological properties which are useful in protective eye wear, nonlinear optical devices
9	and for optical data storage applications.
10	
11	2. Description of the Related Art
12	Previously developed phthalocyanine materials have not possessed the handling and
13	processing characteristics of a single-component fluid coupled with an optical transparency,
14	nonlinear optical absorption and refraction, chemical stability and moisture resistance. These are
15	desirable characteristics for use as thin films in nonlinear optical and optical recording applications.
16	Known methods for preparing phthalocyanines as thin films include vacuum deposition
17	(sublimation, molecular beam, laser desorption), spraying or casting of a fine suspension or solution,
18	Langmuir-Blodgett transfer, mechanical abrasion, and dispersion in a binder. The transparent thin
19	film is a highly desirable physical form for these materials as it allows utilization of the chromophore
20	in optical applications such as optical limiting and optical recording media which typically involve
21	a material response to irradiation with a laser.
22	The deposition method, optical quality, and stability of a phthalocyanine film are determined
23	by the molecular structure and properties of the material. Without peripheral substituents,
24	phthalocyanine compounds are microcrystalline and relatively insoluble. Thin film preparation by
25	vacuum deposition or high pressure abrasive techniques must frequently be accompanied by high
26	temperatures. The microcrystalline character and the presence of different crystalline polymorphs
27	contribute to optical scattering. These effects diminish the transparency of the phthalocyanine film.
28	Temperature variation and exposure to chemical vapors (including water) causes conversions

1

~~

between different crystalline forms further diminishing the quality of the film. (See M. S. Mindorff
 and D. E. Brodie, *Can. J. Phys.*, **59**, 249 (1981); F. Iwatsu, T. Kobayashi and N. Uyeda, *J. Phys. Chem.*, **84**, 3223 (1980); F. W. Karasek and J. C. Decius, *J. Am. Chem. Soc.*, **74**, 4716 (1952))

When peripheral substituents are bonded to the phthalocyanine, molecular packing efficiency 4 and crystallinity are reduced, and the resultant materials may be soluble in a variety of solvents. 5 Film forming techniques involving the use of solvents, such as simple evaporation methods and 6 Langmuir-Blodgett transfer techniques, are feasible processing methods. However, many 7 peripherally substituted phthalocyanines do not form films of good transparent optical quality. The 8 peripheral groups need to be large in size and preferably of mixed isomer substitution to be effective. 9 While crystalline packing is hindered by the presence of peripheral substituents, there are strong 10 attractive van der Waal forces at work between the planar faces of phthalocyanine rings which result 11 in the constituent molecules aggregating into ordered domains. These domains, if large enough, 12 cause optical scattering which strongly deteriorates the transparency and optical quality of thin films. 13 (See T. Kobayashi, in Crystals: Growth Properties and Applications, N. Karl, editor, Springer-14 Verlag, NY, Vol 13 (1991) pp. 1-63; A. Yamashita and T. Hayashi, Adv. Mater., 8, 791 (1996)). 15

The interaction between adjacent phthalocyanine rings in an aggregate also results in a strong
electronic perturbation of the molecular structure and a broadening of its absorption in the visible
spectrum. This interaction in many cases detracts from the sought after nonlinear optical properties.
(See S. R. Flom, J. S. Shirk, J. R. Lindle, F. J. Bartoli, Z. H. Kafafi, R. G. S. Pong and A. W. Snow,
in *Materials Res. Soc. Proc.*, Vol. 247, (1992) pp 271-276).

Control of phthalocyanine aggregation is important first to reduce the ordered domain size 21 below a threshold where optical scattering occurs and second to reduce the pertubation of the 22 phthalocyanine electronic structure to a level where spectral broadening and excited state lifetime 23 shortening do not seriously diminish the nonlinear optical absorption of the phthalocyanine 24 chromophore. The former is critical since optical transparency is required for a device of the current 25 invention to function. For sufficient control of optical scattering, the ordered molecular domain size 26 must be smaller than the light wavelength of application interest (usually in the 350 to 1500 nm 27 range). The latter is less critical, but significant improvement in nonlinear optical properties can be 28

1

realized if aggregation can be reduced to dimer formation or less.

Aggregation can be totally eliminated by blocking the co-facial approach of phthalocyanine 2 rings by axial substitution onto metal ions complexed in the phthalocyanine cavity. (See N. B. 3 McKeown, J. Mater. Chem., 10, 1979 (2000); M. Brewis, G. J. Clarkson, V. Goddard, M. Helliwell, 4 A. M. Holder and N. B. McKeown, Angew. Chem. Int. Ed., 37, 1092 (1998); A. R. Kane, J. F. 5 Sullivan, D. H. Kenny and M. E. Kenney, Inorg. Chem., 9, 1445 (1970)). However, this approach 6 is limited to a small number of tetravalent octahedrally coordinating metals such as silicon. For 7 reasons discussed below, the nonlinear optical properties of this small group of 8 metallophthalocyanines are not particularly useful. (See H. S. Nalwa and J. S. Shirk, in 9 Phthalocyanines: Properties and Applications, C. C. Leznoff and A. B. P. Lever, editors, VCH 10 Publishers, Inc., New York (1996) Ch. 3). 11

Another approach to aggregation control is to utilize very large peripheral substituent groups 12 that hinder the co-facial approach of phthalocyanine rings. Classes of such peripheral substituents 13 are flexible oligomers (see D. Guillon, P. Weber, A. Skoulios, C. Piechocki and J. Simon, Molec. 14 Cryst. Liq. Cryst., 130, 223 (1985); P. G. Schouten, J. M. Warman, M.P. Dehaas, C. F. van Nostrum, 15 G. H. Gelineck, R. J. M. Nolte, M. J. Copvyn, J. W. Zwikker, M. K. Engel, M. Hannack, Y. H. 16 Chang and W. T. Ford, J. Am. Chem. Soc., 116, 6880 (1994)), dendrimers (see M. Kimura, K. 17 Nakada, Y., Chem. Comm., 1997, 1215; M. Brewis, B. M. Hassan, H. Li, S. Makhseed, N. B. 18 McKeown and N. Thompson, J. Porphyrins Phthalocyanines, 4, 460 (2000); M. Brewis, M. 19 Helliwell, N. B. McKeown, S. Reynolds and A Shawcross, Tetrahedron Lett., 42, 813 (2000)), and 20 capping groups (see D. D. Dominguez, A. W. Snow, J. S. Shirk and R. G. S. Pong, J. Porphyrins 21 and Phthalocyanines, 5, 582 (2001)). Examples of these three types of peripheral groups have had 22 limited success in reducing aggregation. In many cases where the large peripheral groups have 23 significant structural symmetry and uniformity of size, liquid crystal formation with its consequent 24 optical scattering has resulted. (See N. B. McKeown, Phthalocyanine Materials: Synthesis, 25 Structure and Function, Cambridge University Press, Edinburgh (1998) pp. 62-86). The liquid 26 crystallinity has been avoided by utilizing peripheral groups with irregular symmetry combined with 27 hydrogen bonding functional groups (see R. D. George and A. W. Snow, Chem. Mater., 6, 1587 28

(1994)) or using a polydispersity of peripheral group chain lengths (see A. W. Snow, J. S. Shirk and 1 R. G. S. Pong, J. Porphyrins Phthalocyanines, 4, 518 (2000)). In the former case an epoxy-amine 2 chemistry was utilized and a non-birefringent organic glass was obtained, while in the latter case 3 polyethylene oxide chemistry was employed and an isotropic liquid was obtained. The organic glass 4 or liquid has very favorable melt processing characteristics. 5

Another requirement on the nature of the peripheral group is that it must be chemically inert 6 toward the metal ions complexed in the phthalocyanine cavity. Many of the metal ions that instill 7 very useful nonlinear optical properties to the phthalocyanine chromophore are moderately labile 8 and may be removed from the phthalocyanine cavity by competing complexing agents. This is 9 particularly true of the heavy metal ions. In previous work with phthalocyanine compounds having 10 polyethylene oxide peripheral groups, it was found that the ethylene oxide structure was a strong 11 enough competitor in complexing with a lead ion and remove it from the phthalocyanine cavity (E. 12 M. Maya, A. W. Snow, J. S. Shirk, S. R. Flom, R. G. S. Pong and G. L. Roberts, "Silicone 13 Substituted Phthalocyanines for Optical Limiting Applications" presented at 221st National 14 American Chemical Society Meeting, San Diego, CA, April 5, 2001). To be useful for the current 15 invention, the peripheral groups must not behave in this manner. 16

Regarding specific instances of tethering a siloxane group to a peripheral site of a 17 phthalocyanine compound, only one example is known (US Pat. 3,963,744). In this instance, the 18 siloxane group is a tris(trimethylsiloxy)silylalkyl structure which is connected through an 19 alkylsulfamide linkage to the phthalocyanine periphery. This material is claimed to be compatible 20 with cross-linked silicone polymers for the purpose of acting as a dye or a pigment. This 21 tris(trimethylsiloxy)silylalkyl structure is compact (highly branched with short-chains) and 22 nonlinear. A compound with these characteristics does not form useful transparent thin films. 23 Conversely, the present invention teaches linear polysiloxane structures. This linear quality is a 24 critical feature in thin film processing and nonlinear optical property enhancement. 25

26

Finally, the nonlinear optical properties of phthalocyanine materials are strongly dependent on the identity of the species complexed within its cavity. While this species may range from two 27 protons to a wide variety of transition and main group metal ions, phthalocyanines with complexed 28

heavy metal ions such as tin, bismuth, mercury, indium, tellurium, and particularly lead display the 1 strongest nonlinear optical properties (see US Pat. 5,805,326; H. S. Nalwa and J. S. Shirk, in 2 Phthalocyanines: Properties and Applications, Vol. 4, C. C. Leznoff and A. B. P. Lever, editors, 3 VCH Publishers, Inc., New York (1996) Ch. 3). In the divalent state, these metal ions do not 4 coordinate to axial ligands. Thus, such ligands cannot be utilized to block aggregation. Many of 5 these metal ions are labile and can be easily displaced by competing chelating structures. This 6 problem is particularly acute with the polyethylene oxide structure where the oxygen sites in this 7 polymer chain coordinate with the metal ion resulting in its consequent removal from the 8 phthalocyanine cavity and diminishment of nonlinear optical properties. 9

- 10
- 11

Summary of the Invention

Accordingly, one objective of the present invention is to provide a modified phthalocyanine 12 that forms a transparent film of high optical quality, free of scattering from solid or liquid crystalline 13 14 domains.

Another objective of the present invention is to provide a phthalocyanine material that has 15 been modified so that it is processable as an isotropic liquid or glass. Such processing includes: 16 filling confined very small spaces (0.01 to 100 micron) by capillary action; mechanically producing 17 a film by shearing between two flat surfaces; and casting a film by solvent evaporation. 18

A further objective of the present invention is to produce phthalocyanine films that display 19 large nonlinear optical absorptions suitable for use in optical limiting applications. 20

A further objective of the present invention is to produce phthalocyanine films that have a 21 large nonlinear thermal refraction to complement the nonlinear photochemistry in optical limiting 22 23 applications.

A further objective of the present invention is to provide a phthalocyanine material that has 24 been modified so that it is useful in the following applications: as a protective element in an optical 25 limiting component of direct view optical goggles, periscopes, gun sights, and binoculars; as the 26 active element in laser intensity control and passive laser intensity noise reduction devices; as an 27 optical switching element in an optical communications circuit; and as a component in compact 28

÷

PATENT APPLICATION

	Docket No.: N.C. 82,650 Inventor's: A.W. Snow, J.S. Shirk, E.M. Maya, R.G.S. Pong, & S.R. Flom
1	disks, DVD's, optical cache memories, and holographic memories.
2	These and other objectives of the present invention are accomplished through covalent
3	bonding of siloxane oligomer structures of appropriate number, chain length and size distribution
4	to connecting sites at the periphery of the phthalocyanine ring structure and by complexation of
5	appropriate heavy metal ions in the phthalocyanine cavity.
6	
7	Brief Description of the Drawings
8	A more complete appreciation of the invention will be readily obtained by reference to the
9	following 'Detailed Description of the Preferred Embodiments' section and these drawings.
10	Figure 1 is a graph showing the nonlinear transmission and optical limiting of a 4.2 μ m thick
11	sample of pure liquid PbPc(PDMS $_{10}$) ₄ .
12	Figure 2 is a graph depicting the increase in optical density as a function of wavelength for
13	PbPc(PDMS ₁₀) ₄ after visible excitation.
14	Figure 3 is a graph demonstrating the optical limiting in f/5 optics for a 4.2 μ m thick sample
15	of pure liquid $PbPc(PDMS_{10})_4$.
16	
17	Detailed Description of the Preferred Embodiments
18	Silicones have unique and useful properties as fluids and rubbers. Phthalocyanines have
19	unique properties for optical and electronic applications. Due to mutual incompatibility of silicones
20	and phthalocyanines, a combination of the unique and useful properties described above cannot be
21	achieved by simply blending these materials. However, this invention achieves a coupling of
22	silicones and phthalocyanine rings via covalent bonding into a single molecular substance which
23	results in a unique combination of the useful properties of each component. There are alternative
24	methods described herein for achieving this coupling of silicone chains to phthalocyanine rings.
25	The phthalocyanine material of the subject invention is described by the general structural
26	formula below. The central phthalocyanine substructure is the chromophore wherein resides the
27	nonlinear optical absorption of visible light. Critical features to the general structure that control this
28	and other important material properties are the nature of the W, X, Y, Z peripheral group

1

3

4

5

PATENT APPLICATION

substructures and the species M complexed in the cavity.





In the phthalocyanine structure, the numbered positions on the benzo ring substructures indicate 2 the peripheral positions where the group(s) W, X, Y, and Z may be covalently bonded. Each of the four benzo ring substructures may accommodate 0, 1 or 2 W-X-Y-Z substituents with the preferred arrangement being one W-X-Y-Z substituent on each benzo ring substructure. There are four possible positions for peripheral substitution on each of the benzo ring substructures. All combinations are 6 practicable, but the preferred arrangements are those of low symmetry so that the phthalocyanine 7 compound is a mixture of geometric isomers. This mixed isomer character is more effective in inhibiting 8 9 crystalline packed arrangements.

The peripheral group W-X-Y-Z is composed of four subunits with each having possible structural 10 variations. The variations are primarily determined by the synthetic route used in preparing the 11 phthalocyanine as described below, and the preferred arrangements are determined by both the facility 12 of the synthesis route as well as the desired physical properties. 13

The W component of the group W-X-Y-Z is an ether or thioether linkage, and is either diaryl or 14 arylalkyl. This is determined by the nitro displacement nucleophilic aromatic substitution reaction in the 15 synthesis in which a phenol or an alcohol or corresponding sulphur analog may be used. The diaryl ether 16 or thioether linkage is preferred because it has better photo-oxidative stability. When the phenol or 17

thiophenol is used to make the diaryl linkage, there are three possible linkage sites on the phenylene 1 group (1', 2', 3' or ortho, meta and para respectively) to which the X subgroup is bonded. While all as 2 well as mixtures are practicable, the 1' (or ortho) position is preferred. This occurs for synthesis as well 3 as property reasons. Substitution at the ortho position causes the W-X-Y-Z group to turn back toward 4 the face of the phthalocyanine ring resulting in a steric hindrance caused by cofacial aggregation. This 5 mechanism for depressing aggregation has a highly desirable effect on the nonlinear optical properties. 6

The X component is a variable length alkane chain. Its presence results from the hydrosilylation 7 coupling reaction between a terminal olefin and a silylhydride terminated siloxane. In principle, an 8 alkane of any chain length may perform this function and variations incorporating chain branching or 9 heteroatoms are workable. The preferred structure for subgroup X is a short chain length with the 10 optimum preference being a trimethylene group. This group is the most synthetically facile. Its short 11 chain length also has a minimal diluting effect on the thermal refractive optical property associated with 12 the silicone structure (subgroup Y). 13

The Y component is a siloxane chain of variable length. This substructure is responsible for the 14 liquid or glassy character of the phthalocyanine material and for the exceptionally large thermal refractive 15 nonlinear optical effect. There are three important variables within this substructure: the length, m, of 16 the siloxane chain, the dispersity of the siloxane chain length, and the identity of the pendent group B. 17 The siloxane chain length correlates with the glass transition temperature (Tg) and determines whether 18 the material will be a glass or a liquid. Very short chains (3 or 4 units) correlate with a Tg above ambient, 19 while longer ones (>6 units) depress the Tg below room temperature. For liquid phthalocyanine 20 materials, the viscosity correlates with the siloxane chain length; initially decreasing with increasing chain 21 length in opposition to the influence of the phthalocyanine substructure, then increasing with further chain 22 length reflecting the effect of the siloxane molecular weight. The longer the chain length (the greater the 23 volume fraction of the Y component), the more this phthalocyanine material's rheology and morphology 24 resemble the pure siloxane material. The longer chain lengths also reduce phthalocyanine aggregating 25 tendency by steric hindrance. However, the phthalocyanine structure's volume fraction must remain 26 significant (in the approximate range from a high of 25% to a low of 1%, which correlates with a siloxane 27 chain length between 3 and 100) if the nonlinear optical properties associated with this chromophore are 28

to be utilized in a thin film physical form. In general, the preferred chain lengths range from 7 to 28 units.
A polydispersity of siloxane chain length is a variation about an average chain length. While the current
invention may be practiced with either a monodisperse or polydisperse siloxane chain, polydispersity is
beneficial in that its breadth reduces a tendency for organized molecular packing which may result in
liquid crystal formation. The synthesis method for preparation of the silylhydride terminated siloxane
intermediates yields a polydisperse product, utilized without fractionation in the current invention.

7 The identity of the pendant group B on the siloxane chain is a very important variable in that this 8 feature offers a method of controlling the refractive index of the phthalocyanine material. The preferred 9 identity is methyl for reasons of availability of precursors, synthesis facility and associated useful optical, 10 physical and processing properties. However, the phthalocyanine material refractive index may be either 11 increased or decreased by substituting the phenyl or 3,3,3-trifluoropropyl respectively for the methyl 12 group in a fraction or all of the pendant B groups.

13 The Z component is a terminal or capping group on the free end of the siloxane chain. It is 14 typically an inert alkyl group from the alkyl lithium initiator used in preparing the siloxane polymer from 15 the cyclic trimer by anionic polymerization. This is the preferred embodiment as it confers a long term 16 stability and processability to the phthalocyanine material. However, this terminal group may also be a 17 reactive functional group such as a silylhydride. In this case, the phthalocyanine compound may couple 18 with other or similar functional groups to generate network structures. The phthalocyanine compound 19 may also bond to surfaces by reaction of the silylhydride group.

The M component is either a metal ion or two protons. The identity of the metal ion has a very important influence on the nonlinear optical absorption of the phthalocyanine chromophore. Previous teaching (US Pat. 5,805,326) has demonstrated that heavy metal ions, particularly lead, are the preferred embodiments. The invention will function with other metal ions as well as the two protons complexed in the phthalocyanine cavity although the efficiency in the optical limiting application is not as high.

The synthesis of phthalocyanine compounds is well known to those skilled in the art. The following references provide a comprehensive review: D. Whöle, G. Schnurpfeil and G. Knothe, *Dyes and Pigments*, **18**, 91-102 (1992); A. B. P. Lever, *Advances in Inorganic and Radiochemistry*, **58**, 27-114 (1965); C. C. Leznoff and A. B. P. Lever (editors), *Phthalocyanines: Properties and Applications*, VCH

Publishers, Inc., Vol. 1 (1989); F. H. Moser and A. L. Thomas, *The Phthalocyanines*, CRC Press, Inc.,
 Vols. 1 and 2 (1983); B. D. Berezin, *Coordination Compounds of Porphyrins and Phthalocyanines*, John
 Wiley & Sons (1981); N.B. McKeown, *Phthalocyanine Materials: Synthesis, Structure and Function*,
 Cambridge University Press (1998). Specific details for many particular phthalocyanine compounds may
 be found in the many articles cited by the above reviews.

The phthalocyanine materials of the subject invention are unique in that linear siloxane polymers б are tethered to the periphery of the phthalocyanine structure to obtain very novel and useful properties 7 (i.e. intrinsic liquid character, large refractive index - temperature dependence, isotropic thin film 8 formation, and chemical inertness) that have not been previously achieved by other peripherally bonded 9 structures. In the prior art, the only instance of tethering a siloxane group at the periphery of a 10 phthalocyanine ring involved a tris(trimethylsiloxy)silylalkyl group attached through a sulfamide linkage 11 to the phthalocyanine periphery (US Pat. 3,963,744). This highly branched and very symmetrical group 12 has a highly different chemistry, synthesis method, properties and purpose from the linear long chain 13 siloxane polymers used in the present invention. 14

15

16

17

The synthesis used in the present invention consists of a series of reactions depicted below:



The first step is preparation of the silylhydride terminated siloxane polymer, 3, by anionic 1 polymerization of the cyclotrisiloxane, 2, following a published procedure (see A. T. Holohan, M. H. 2 George, J. A. Barrie and D. G. Parker, Macromol. Chem. Phys., 195, 2965 (1994)). The siloxane chain 3 length is determined by the monomer: alkyl lithium initiator molar ratio. The product distribution is 4 narrow but not monodisperse. The identity of the alkyl capping group, Z, is determined by selection of 5 alkyl lithium initiator. The silylhydride terminal group is supplied by the dimethylchlorosilane 6 termination reagent. The pendant group, B, may be an alkyl group, phenyl group or a haloalkyl group 7 and is determined by selection of the cyclotrisiloxane monomer, 2. 8

The second step is preparation of the olefin terminated alkyl substituted phthalonitrile 9 intermediate, 6, by a nucleophilic aromatic nitro displacement reaction between the nitrophthalonitrile, 10 4, and the terminal olefin substituted alcohol or phenol, or corresponding sulphur analog, 5. There are 11 many possibilities for structural variation in these reagents. The nitro group in 4 may be substituted at 12 the 3- or 4-position. Substitution at the 3-position has been shown to reduce aggregation tendency in the 13 analog phthalocyanine compound (R. D. George, A. W. Snow, J. S. Shirk and W. R. Barger, J. 14 Porphyrins and Phthalocyanines, 2, 1-7 (1998)). For reagent 5, a terminal olefin substituted alkylphenol 15 or alkylthiophenol is the preferred embodiment. The use of terminal olefin substituted alcohols, such as 16 allyl alcohol, is practicable, however, the reaction yields are lower and the phthalocyanine analog 17 compound has less stability compared with using the phenol. While practically any phenol or thiophenol 18 with an olefin terminated alkyl substituent is preferred, a most preferred embodiment for reagent 5 is 2-19 allylphenol. This precursor is readily available, synthesis yields are good, phthalocyanine analog stability 20 is good, and phthalocyanine aggregation tendency is lowered. The volume fraction of this hydrocarbon 21 linkage substructure is significantly lower when compared with using phenols with larger olefin 22 terminated alkyl groups. Details of the preparation of this 4-(2-allylphenoxy)phthalonitrile key 23 intermediate are given in Example 1. 24

25

The third step is preparation of the polysiloxane substituted phthalonitrile intermediate, 7, by a hydrosilylation coupling reaction between the olefin terminated phthalonitrile, 6, and the silylhydride 26 terminated siloxane polymer, 3. This reaction requires a trace amount of a hydrosilylation catalyst, such 27 as chloroplatinic acid. (see Examples 2 and 3) 28

The fourth step is conversion of the siloxane substituted phthalonitrile, 7, to the corresponding 1 phthalocyanine, 1. Two frequently used conditions employing hydroquinone (see A. W. Snow, N. P. 2 Marullo, and J. R. Griffith, Macromolecules, 17, 1614 (1984)) or lithium pentoxide (P. A. Barret, D. A. 3 Frye, and R. P. Lindstead, J. Chem. Soc., 1938, 1157) as coreactants were not successful. The use of 4 DBU (1,8-diazabicyclo[5.4.0]undec-7-ene) or dimethylaminoethanol/metal salt as the coreactants are 5 practicable. However, the preferred route is to use lead (II) oxide as the coreactant. This yields the 6 desired lead phthalocyanine, 1 M = Pb, is good yield (Examples 5 and 6). This lead phthalocyanine may 7 be transformed to the corresponding metal-free phthalocyanine, $1 M = H_2$, by treatment with a small 8 amount of acid (Example 8). A wide variety of other metals may then be introduced into the 9 phthalocyanine cavity by treatment of the metal-free phthalocyanine with a solution of a basic salt (e.g. 10 an acetate) of the desired metal. 11

An alternate but less preferred synthetic route to the desired siloxane substituted phthalocyanine, 12 1, is to reverse the order of the third and fourth steps by converting the olefin terminated alkyl substituted 13 phthalonitrile intermediate, 6, to its corresponding tetraallylphenoxy phthalocyanine (Examples 4 and 7) 14 then couple the silylhydride terminated siloxane polymer, 3, to this tetraallylphenoxy phthalocyanine to 15 yield the siloxane substituted phthalocyanine, 1, using a non-acidic heterogeneous catalyst, such as 16 platinum-divinyl tetramethyldisiloxane. This route requires a large excess of the silylhydride terminated 17 siloxane polymer, 3, in the final step to insure total functionalization of the allylphenoxy phthalocyanine 18 which makes the purification of the final compound much more difficult. 19

The polysiloxane substituted phthalocyanines of the current invention, with the peripheral group 20 molecular structure falling within the ranges specified for the W-X-Y-Z component of the general 21 structure shown above, display characteristics of a very high quality optically transparent film. 22 Observations and physical measurements on phthalocyanine materials prepared in Examples 5, 6 and 8 23 verify these characteristics. When these materials are examined under high optical magnification (600 24 X) between crossed polarizers, no birefringence is observed. This is a sensitive test to directly diagnose 25 the existence of very small molecularly ordered anisotropic domains with liquid or solid crystalline 26 character. This observation is further supported by noting in the region of the optical spectrum where no 27 phthalocyanine absorption occurs (900-1200 nm), the base line is virtually flat. As a further observation, 28

no visually observed scattered light when the film is under intense laser irradiation. This is a clear 1 indication that the polysiloxane peripheral groups are successful in prevention of formation of ordered 2 domains whose dimension is comparable to the visible light wavelength or larger. 3 Quantitative measurements have also been made on the dimerization formation constant which 4 is a parameter by which aggregating tendency can be assessed. The results are presented in Table 1 for 5 the polysiloxane substituted phthalocyanine compounds of Examples 5 (PbPc(PDMS₁₀)₄ and 8 6 along with comparative data for the respective cumylphenoxy substituted $(H_2Pc(PDMS_{10})_4)$ 7 phthalocyanines ($PbPc(CP)_4$ and $H_2Pc(CP)_4$). 8 9 Table 1. Dimerization Formation Constants in Solution 10 $H_2Pc(CP)_4$ $K_D = 7000 M^{-1}$ PbPc(CP)₄ $K_D = 400 M^{-1}$ $H_2Pc(PDMS_{10})_4$ $K_D = 31 M^{-1}$ PbPc(PDMS_{10})_4 $K_D = 2 M^{-1}$ 11 12 13 These measurements clearly demonstrate that the polysiloxane substituent relative to the 14 cumylphenoxy hydrocarbon substituent reduces the tendency of the phthalocyanine to aggregate by a 15 factor of at least 15 in both the metal-free and lead substituted analogs. 16 Another very critical physical characteristic conferred on the phthalocyanine material by the 17 polysiloxane peripheral group is that of facile processability. Depending on the glass transition 18 temperature, this peripheral group renders the phthalocyanine an amorphous isotropic glass or liquid. As 19 such these materials can be processed as melts by simple application of heat to regulate the viscosity. The 20 phthalocyanines of the Examples 5, 6 and 8 have respective Tg's of 3, 10 and -3°C. These materials are 21 room temperature liquids and may be processed as thin films of very uniform and precisely controlled 22 thickness by using capillary action to fill short pathlength (1 to 50 micron) flat optical cells. Smaller 23 confined spaces down to 0.01 micron may also be filled by capillary action. 24 These polysiloxane phthalocyanines may also be processed by mechanically shearing a film 25 between two optical surfaces. Alternately, the phthalocyanine materials of this invention are soluble in 26 a variety of solvents and the simple generation of films by solvent casting or spraying and evaporation 27 is a practicable technique. Blending these phthalocyanines in polymers is another method of film 28

1 preparation.

These polysiloxane substituted phthalocyanine materials display an enhanced nonlinear optical 2 absorption attributable to the phthalocyanine chromophore and the species complexed within the cavity. 3 A reverse saturable absorption mechanism has been assigned to this photochemistry where an electronic 4 transition from a first excited state to a second excited state has a higher transition probability than from 5 the ground state to the first excited state. This transition from the first to the second excited state becomes 6 the dominant transition once a threshold population is reached in the first excited state. To reach the 7 critical first excited state population threshold, this state must have a sufficiently long lifetime. This long 8 lifetime is promoted by having heavy metal ions complexed in the phthalocyanine cavity and by a low 9 level of aggregation. Both the heavy metal ions and the polysiloxane peripheral groups are important 10 influences in the current invention. Figure 1 displays nonlinear transmission and optical limiting data of 11 a 4.2 micron film of the phthalocyanine material of Example 5. These measurements were made at 532 12 nm using f/5 optics and an f/5 optical limiter with a pulse width of 7 ± 1 ns. The sample transmission at 13 532 nm was 84%. The nonlinear transmission measurements give an approximate excited state 14 absorption cross-section of $1.0 \pm 0.2 \times 10^{-16} \text{ cm}^2$ and a ratio of the excited state to ground state extinction 15 coefficient of 36 at this wavelength. This excited state absorption is larger than that found in solutions 16 of PbPc(CP)₄, a known superior optical limiter (US Pat. 5,805,326). The relative difference in absorption 17 coefficients between the excited and ground states over a wavelength range of 430 to 600nm following 18 excitation at 606nm for the phthalocyanine material of Example 5 is depicted in Figure 2. This illustrates 19 the wavelength window over which this material will be an effective optical limiter. Thus, Figure 1 20 illustrates the magnitude of limiting for a single wavelength, and Figure 2 shows a breadth of wavelengths 21 where limiting will be effective. 22

In addition to the nonlinear optical absorption of the phthalocyanine chromophore, the polysiloxane peripheral group makes a further contribution to the optical limiting through its nonlinear thermal refraction. A rapid change in refractive index with temperature, dn/dT, shifts the focal point of focused light and lowers the quantity of light passing through a series of focused optics. Because the phthalocyanine chromophore is very efficient in converting absorbed light to heat, a medium with a large refractive index response to heat will accentuate this thermal refractive effect. The polysiloxane structure

has a very large refractive index response to heat, and by virtue of being bonded to the periphery of the 1 phthalocyanine ring is well-positioned to accentuate this effect. The temperature dependence of the 2 refractive index was measured for the polysiloxane phthalocyanine of Example 5 via ellipsometry to be 3 $-5.4 \pm 1 \times 10^{-4}$ °C⁻¹ between 25 and 40 °C and an average dn/dT of $-4 \pm 1 \times 10^{-4}$ °C⁻¹ between 25 and 95 4 °C. The latter value compares well with that found for linear polydimethylsiloxane liquids. Relative to 5 other polymers, polydimethylsiloxane has an exceptionally large dn/dT. This thermal refractive 6 enhancement to the optical limiting is depicted in Figure 1 by comparing the optical limiting curve with 7 that attributable to the only the nonlinear optical absorption. Figure 3 shows the optical limiting 8 measurements when carried to higher energies. 9

Other favorable properties that the polysiloxane peripheral groups confer on the phthalocyanine 10 materials are chemical inertness and moisture resistance. The heavy metal ions, particularly lead, are 11 labile to displacement from the phthalocyanine cavity. Competing complexing agents and the presence 12 acid and moisture promote this displacement. As noted in the prior art description section, peripheral 13 groups with coordination sites that will complex with a labile metal such as the polyethylene oxide 14 structure can play the role of a competing complexing agent. Water and/or a source of protons complete 15 the conversion to metal-free phthalocyanine. The oxygen atoms in the polysiloxane structure are very 16 weak coordinating sites and are sterically hindered by pendant groups attached to the siloxane chain. The 17 polysiloxane structure is also very hydrophobic. The lead phthalocyanine materials with peripheral 18 siloxane substitution in the present invention are less labile than other lead phthalocyanine materials 19 toward conversion to the metal-free analog. 20

21 22

EXAMPLES

23. The examples which follow serve to illustrate the practice of this invention and quantify the24 physical properties but are in no way intended to limit its application.

- 25
- 26 1. Synthesis and characterization of precursors
- 27 <u>Example 1</u>: Synthesis and purification of 4-(2-allylphenoxy)phthalonitrile(I)
- In a nitrogen atmosphere, 6.37 g (0.046 mol) of finely grounded anhydrous K_2CO_3 was added

1	to a solution of 3.89 g (0.029 mol) of 2-allylphenol (Aldrich) and 5.02 g (0.029 mol) of 4-
2	nitrophthalonitrile (Aldrich) in 25 mL of dry Me_2SO by 0.32 g additions at $\frac{1}{2}$ h intervals over an 6-h
3	period. The mixture was stirred 24 hours at room temperature under nitrogen. The undissolved salt is
4	filtered from the reaction mixture and the filtrate is dissolved in 100 mL of methylene chloride. The
5	solution is extracted 5 times with 50mL water. The organic phase was dried over anhydrous magnesium
6	sulfate, filtered and evaporated to dryness. The crude product is dissolved in minimum of toluene and
7	chromatographed on alumina with toluene elution. The toluene was evaporated and the resulting oil
8	vacuum dried to yield 5.28 g (70%) of I. The oil turns into a solid in few days.
9	¹ H-RMN (CDCl ₃ , 300 MHz) 3.23 (2H, d, CH ₂), 4.95 (2H, dd, =CH ₂), 5.78 (1H, m, =CH), 6.95 (1H, d,
10	Harom), 7.12-7.33 (5H, m, Harom), 7.68 (1H, d, Harom) ppm; ¹³ C-RMN (CDCl ₃ , 75 MHz) 34.0, 108.5,
11	114.9 and 115.4 (CN), 116.7, 117.6, 120.8, 120.9, 121.0, 126.7, 128.5, 131.6, 132.4, 135.3, 135.4, 151.1,
12	161.7 ppm; IR (NaCl) 3082 (=CH ₂), 2229 (CN), 1615 (C=C), 1595 and 1486 (C-C), 1246 cm ⁻¹ .
13	
14	<u>Example 2</u> : Synthesis and purification of $4-(H_9C_4[Si(CH_3)_2O]_9Si(CH_3)_2(CH_2)_3C_6H_4O)$ substituted
15	phthalonitrile (II)
16	A mixture of 1 g (3.84 mmol) of I and 4 drops of a 0.1 N isopropanol solution of $H_2PtCl_66H_2O$
17	(Aldrich) was heated at 60°C. Then 3 g (3.84 mmol) of hydrosilyl terminated PDMS precursor
18	(H ₉ C ₄ [Si(CH ₃) ₂ O] ₉ Si(CH ₃) ₂ H) (A.T. Holohan et al., <i>Macromol. Chem. Phys.</i> 195 , 2965(1994)) were
19	added dropwise. The mixture was stirred at 60 $^{\circ}\mathrm{C}$ for 1 h. The oil obtained was purified by silica column
20	chromatography using toluene as eluent. The solvent was evaporated to yield 2.20 g (55%) of a colorless
21	oil after vacuum dry.
22	Tg: $14 ^{\circ}$ C; $n_{D} = 1.4482$; ¹ H-RMN (CDCl ₃ , 300 MHz) 0.012-0.064 (60H, m, SiCH ₃), 0.51 (4H, m, SiCH ₂),
23	0.86 (3H, t, CH ₃), 1.29 (4H, m, CH ₂), 1.58 (2H, m, CH ₂), 2.49 (2H, t, CH ₂), 6.95 (1H, d, Harom), 7.14-
24	7.31 (5H, m, Harom), 7.68 (1H, d, Harom) ppm; IR (NaCl) 2966 (CH), 2229 (CN), 1602 and 1492 (C-C),
25	1254 (SiCH ₃), 1098 and 1033 (SiOSi), 806 (SiC) cm ⁻¹ .
26	
27	Example 3: Synthesis and purification of $4-(H_9C_4[Si(CH_3)_2O]_{18}Si(CH_3)_2(CH_2)_3C_6H_4O)$ substituted
28	phthalonitrile (III)

PATENT APPLICATION

1	The procedure is identical to that for example 2 except a longer hydrosilyl terminated PDMS
2	precursor $(H_9C_4[Si(CH_3)_2O]_{18}Si(CH_3)_2H)$ was used, in the same stoichiometric relationship.
3	Tg: 10 °C; $n_p = 1.4318$; ¹ H-RMN (CDCl ₃ , 300 MHz) 0.015-0.144 (114H, m, SiCH ₃), 0.54 (4H, m,
4	SiCH ₂), 0.88 (3H, t, CH ₃), 1.32 (4H, m, CH ₂), 1.55 (2H, m, CH ₂), 2.50 (2H, t, CH ₂), 6.95 (1H, d, Harom),
5	7.15-7.32 (5H, m, Harom), 7.70 (1H, d, Harom) ppm; IR (NaCl) 2966 (CH), 2235 (CN), 1608 and 1492
6	(C-C), 1272 (SiCH ₃), 1098 and 1033 (SiOSi), 800 (SiC) cm ⁻¹ .
7	
8	2. Synthesis and characterization of Lead Phtahlocyanines
9	The procedure for lead phthalocyanine (Pc) is very similar and analogous to those reported by
10	Lindstead and coworkers for unsubstituted metallophthalocyanines. The general reaction and
11	purification were as follows except where departures are specified.
12	To a 10x75 mm tube fitted with a magnetic stirring bar were added the corresponding
13	prescribed quantities of dicyano precursor (I, II, or III) and lead oxide (Fisher, yellow). The mixture
14	was carefully fused under vacuum (less than 0.1 torr) to remove residual solvents and air occluded in
15	the dicyano precursor and sealed under vacuum. The entire tube was heated with stirring for the
16	designed time and temperature. The crude product was purified by column chromatography on silica
17	(Fluka AG) using toluene as an elution solvent. The toluene was concentrated to yield a green liquid
18	chromophore which was dried under vacuum at 80°C for 2 h.
19	When dicyano precursor I was used, a green solid phthalocyanine was obtained which was
20	purified by column chromatography on alumina (neutral Bodman, activity 1).
21	
22	Example 4: $PbPc(2-allylphenoxy)_4$ (IV)
23	A mixture of 0.500 g (1.92 mmol) of I and 0.328 g (1.47 mmol) of PbO was reacted at 180° C
24	for 12 hours. Yield: 0.261 g (42%); m.p.> 250 °C; UV-vis (toluene) 721, 650, 346 nm; IR(NaCl)
25	3076 (=CH ₂), 2919 (CH), 1638 (C=C), 1608, 1485 (C-C), 1239 cm ⁻¹ .
26	
27	

PATENT APPLICATION

1	<u>Example 5</u> : PbPc(OC ₆ H ₄ (CH ₂) ₃ Si(CH ₃) ₂ [O Si(CH ₃) ₂] ₉ C ₄ H ₉) ₄ (V)
2	A mixture of 0.800 g (0.766 mmol) of II and 0.131 g (0.589 mmol) of PbO was reacted at
3	180°C for 12 hours. Yield: 0.512 g (61%); Tg: 3°C; UV-vis (toluene) 721, 648, 365 nm; IR(NaCl)
4	2959 (CH), 1608 and 1492 (C-C), 1253 (SiCH ₃), 1091 and 1014 (SiOSi), 800 (SiC) cm ⁻¹ .
5	Phthalocyanine V can also be prepared by hydrosilylation reaction over the phthalocyanine IV.
6	A mixture of 0.100 g (0.077 mmol) of IV and 8 drops of Platinum divinyltetramethyldisiloxane
7	complex in xylene (Gelest Inc) was dissolved in 2 mL of toluene and was heated at 60 °C. Then
8	0.481 g (0.616 mmol) of hydrosilyl terminated PDMS precursor (H ₉ C ₄ [Si(CH ₃) ₂ O] ₉ Si(CH ₃) ₂ H) were
9	dropwise added. The mixture was stirred at 60 °C for 6 h. and purified in the same way.
10	
11	<u>Example 6</u> : PbPc(O C ₆ H ₄ (CH ₂) ₃ Si(CH ₃) ₂ [O Si(CH ₃) ₂] ₁₈ C ₄ H ₉) ₄ (VI)
12	A mixture of 0.500 g (0.292 mmol) of III and 0.050 g (0.224 mmol) of PbO was reacted at
13	180°C for 12 hours. Yield: 0.226 g (44%); Tg: 10°C; UV-vis (toluene) 719, 647, 389, 367 nm;
14	v(NaCl) 2966 (CH), 1621 and 1486 (C-C), 1266 (SiCH ₃), 1091 and 1033 (SiOSi), 800 (SiC) cm ⁻¹ .
15	
16	3. Synthesis and characterization of Metal free Phtahlocyanines
17	Example 7: $H_2Pc(2-allylphenoxy)_4$ (VII)
18	To a $10x75$ mm tube fitted with a magnetic stirring bar were added 0.500 g (1.92 mmol) of I
19	and 0.052 g (0.48 mmol) of hydroquinone (Aldrich). The mixture was carefully fused under vacuum
20	(less than 0.1 torr) to remove residual solvents occluded in the dicyano precursor and sealed under
21 ·	vacuum. The entire tube was heated at 170°C with stirring for 12 h. The crude product was purified
22	by column chromatography on alumina (neutral Bodman, activity 1) using toluene as an elution
23	solvent. The toluene was concentrated and the blue solid obtained was dissolve in a minimum
24	amount of chloroform, and the phthalocyanine was precipitated by dropwise addition of methanol.
25	The product was collected and dried. Yield: 0.280 g (56%); m.p. > 250 °C; UV-vis (toluene) 703, 667,
26	$639, 605, 350 \text{ nm}; \text{IR}(\text{NaCl})3295 (\text{NH}), 3075 (=CH_2), 1638 (CH=CH_2), 1611 \text{ and } 1467 (C-C), 1228 \text{ cm}^{-1};$
27	¹ H-RMN (CDCl ₃ , 300 MHz) –4.1 (s, NH), 3.6 (m, CH ₂), 5.1 (m, =CH ₂), 6.1 (m, CH=), 6.8-7.7 (m, H-
28	arom) ppm; m/z 1091.

PATENT APPLICATION

1	
2	<u>Example 8</u> : $H_2Pc(O C_6H_4(CH_2)_3Si(CH_3)_2[O Si(CH_3)_2]_9C_4H_9)_4$ (VIII)
3	Metal free phthalocyanine VIII was obtained by displacement of a lead ion from the
4	phthalocyanine (V).
5	To a solution of 0.300 g (0.068 mmol) of V in 10 mL of methylene chloride were added three
6	drops of trifluoroacetic acid. The mixture was stirred at room temperature for 10 min. The methylene
7	chloride solution was extracted 3 times with 15 mL of 5% NaHCO ₃ . The organic phase was dried
8	over anhydrous magnesium sulfate, filtered and evaporated to dryness. The crude product was
9	purified by column chromatography on silica (Fluka AG) using toluene as an elution solvent. The
10	toluene was concentrated to yield a blue liquid which was dried under vacuum at 80°C for 2 h. Yield:
11	0.160 mg (56%); Tg: 6°C; UV-vis (toluene) 703, 666, 638, 605, 346 nm; IR(NaCl) 3295 (NH), 2959
12	(CH), 1615 and 1479 (C-C), 1259 (SiCH ₃), 1091 and 1027 (SiOSi), 807 (SiC) cm ⁻¹ ; m/z 4500-2200.
13	Compound VIII may also be prepared following a similar procedure to those reported by O.
14	Bekarôglu and co-workers (A. G. Gurek, O. Bekarôglu, J. Chem. Soc. Dalton Trans., 1994, 1419).
15	A mixture of 0.250 g (0.24 mmol) of II and 0.036 g (0,24 mmol) of DBU (1,8-
16	diazabicyclo[5.4.0]undec-7-ene) (Aldrich) was dissolved in 2 mL of pentan-1-ol. The mixture was
17	stirred at 136 °C for 7 h. The solvent was removed by vacuum distillation and the crude was purified
18	as above.
19	
20	Obviously, many modifications and variations of the present invention are possible in light of
21	the above teachings. Additional advantages and modifications will readily occur to those skilled in
22	the art. Therefore, the invention in its broader aspects is not limited to only the specific details and
23	representative embodiments shown and described herein. Accordingly, various modifications may be
24	made without departing from the spirit or scope of the general inventive concept as defined by the
25	appended claims and their equivalents.
26	
27	
28	

1 Abstract

2 The present invention is phthalocyanine compounds with peripheral siloxane substitution, as 3 well as methods for making these compounds and various uses thereof, having the basic structure:



4 wherein

-W-X-Y-Z are peripheral groups comprising individual W, X, Y, and Z subgroups; 5 W is a linkage represented by the formula: $-D-(R^{1})_{0,1}$, where D = S or O; 6 $-(CH_2)_n$, n = 2 to 8; 7 X is: Y is a siloxane chain; 8 Z is an aryl or alkyl terminal cap; 9 M is two protons or a metal ion; 10 and forms a transparent film of high optical quality with large nonlinear absorption and thermal 11 refraction, free of scattering from solid or liquid crystalline domains making them highly suitable for 12 use as the active component in thin films, protective eye wear, and optical data storage applications. 13 14



Figure 1. Nonlinear transmission and optical limiting of a 4.2 μ m thick sample of pure liquid PbPc(PDMS₁₀)₄.



Figure 2: Increase in optical density as a function of wavelength for $PbPc(PDMS_{10})_4$ after visible excitation.



Figure 3. Optical limiting in f/5 optics for a 4.2 μ m thick sample of pure liquid PbPc(PDMS₁₀)₄.